



SPECIFICATIONS FOR RAW MATERIALS

ISSUE : 05
SECTION : 8.0
REV : 00
DATE : JUN 2009
PAGE : 1 OF 1

RAW QUARTZ POWDER - 53 μ m

1. General : This Specification governs the Requirements of RAW QUARTZ POWDER - 53 μ m.
2. Application : To serve as one of the constituents in the manufacture of alumina porcelain body and Glaze for porcelain.
3. Particle Size : Below 53 μ m sieve shall be > 95 %.
4. Freedom from Defects: Shall be free from foreign materials. Free iron in powder shall not exceed 0.01%.
5. Chemical Composition : a) SiO₂ ... More than 98.0 %
b) L.O.I... Less than 0.5 %.

PREPARED BY

P.V. Satyasandha

P.V. SATYASANDHA

SR. ENGINEER / CERAMIC LABORATORY

APPROVED BY

S.K. Biswas

S.K. BISWAS

HEAD / SH & CERAMIC LABORATORY