

**Technical Delivery Conditions for Rolled & Welded Pipes made of IS 2062 Plates / IS 10748 Coils****1.0 SCOPE**

- 1.1 This Technical Delivery Conditions specify the requirements for electrically welded (ERW \ SAW) steel pipes.
- 1.2 The pipes are intended for water services (under Non-IBR Piping system only).
- 1.3 The pipes shall conform to the **size and quantity** as specified in the purchase order.

2.0 MATERIAL

- 2.1 The plates / coils used for pipe shall meet the requirements as per IS:2062 / IS:10748 including Chemical & Mechanical test requirements.
- 2.2 **Grade of Plate / Coil shall be selected to meet the minimum tensile strength 410Mpa.**

3.0 DIMENSIONAL TOLERANCES

- 3.1 The tolerances limits are:
- a) OD:- Upto NB 1600 mm: ± 4 mm; Above NB 1600 mm: ± 6 mm
 - b) Thickness:- Upto 14mm : +1.3mm / -0.8mm; Above 14 mm : +1.4mm / - 0.8mm.
 - c) Ovality (Difference between major and minor inside diameter): 0.5% maximum
 - d) Squareness of ends: The ends of pipe section shall not vary by more than 3mm at any point from a true plane perpendicular to the axis of the pipe and passing through the center of the pipe at the end.
 - e) Length, quantity and other tolerances as per P.O.

4.0 MANUFACTURING


- 4.1 The pipe shall be of longitudinally welded or spirally welded as indicated in the P.O.
- 4.2 The ends shall be edge prepared as indicated in the drawing / purchase order.
- 4.3 Circumferential seams shall be minimum 1500 mm apart from each other and from ends.
- 4.4 The offset between any two subsequent longitudinal joints **shall be more than 90deg.**
- 4.5 All pipes shall be completely finished and free from surface, sub surface defects such as pits, cracks, weld spatters & laminations etc..

5.0 CHEMICAL & MECHANICAL TESTS : Shall meet the plate/coil requirements.

- 5.1 **Product Analysis :-** One sample per heat per size.
- 5.2 **Tensile Test (Longitudinal or Transverse) :** One sample per heat per size.
- 5.3 **Transverse Guided Bend Test (Root + Face) :** One sample per heat per size.

6.0 NDE

- 6.1 For Pipe dia less than 1000mm:- 100 % Hydro test on each pipe + Radiography test for 100mm weld length at both the ends for 10% of the pipes.
- 6.2 For Pipe dia 1000 mm & above :-The NDT for each pipe shall be done by any one of the following options. The vendor shall indicate their choice in the offer.
- a) 100 % Hydro test along with Radiography test for 100mm weld length on both the ends of each pipe.
 - b) 100 % Ultrasonic test + 10 % Radiography test on weld length (including all T-joints and 100mm weld length at both the ends) for each pipe.
 - c) 100 % Radiography test on weld length of each pipe.
- 6.3 The Ultrasonic test / Radiography test shall be carried out as per ASME Sec-V and shall be accepted as per ASME B31.1 Cl:136.4.6 / Cl:136.4.5.

 Vivekananda Yellu Dy.Mgr/QA	 K. Rajitha AGM/MM	 C. Karunakaran AGM/Engg	 C Vaithianathan AGM/Quality
Prepared By	Reviewed By		Approved By

**7.0 INSPECTION**

- 7.1 All pipes shall be inspected by the vendor prior to BHEL / Customers' Inspection. BHEL or BHEL authorized inspector / Customer will select the pipes at random and carryout the inspection. The necessary Material Despatch Clearance Certificate is to be obtained by the vendor prior to the despatch of material.

8.0 PAINTING AND PACKING

- 8.1 The pipes if dispatched to BHEL Stores shall be coated with resin type translucent rust preventive on the outside unless otherwise specified in the P.O.
- 8.2 The pipes if dispatched to project site directly shall be coated outside & inside as indicated in P.O.
- 8.3 In case of any special coating like PU, Glass Flake, Solvent less Epoxy etc.. the vendor shall get BHEL approval for their QP and Procedure for application of coating.
- 8.4 Internal un-coated length (cut-back length) from both ends of the pipe shall be maintained as per drawing attached in P.O. to facilitate site joints.
- 8.5 Spiders are to be provided on both ends of the pipes as per the drawing indicated in the enquiry / Purchase Order.




9.0 MARKING

- 9.1 The pipes dispatched to **BHEL Stores** shall be paint stencilled & hard punched with the following details.
- 1) PO Number 2) Supplier's emblem/code 3) Size & Specification
4) Pipe number 5) Inspector's seal
- 9.2 The pipes despatched directly to project site as **DTS**, the following details (furnished in the P.O. or separately) shall be paint stencilled at one end of the pipe & hard punched at other end of the pipe in addition to the above.
- Work order & DU No
 - Project name (Only Paint Stencilling)
 - Weight per Pipe length
- 9.3 For the pipe dia 1000mm and above marking shall be done on internal surface in the uncoated area (i.e) within 100mm from pipe ends. The hard punching shall be done at one end and paint stencilling at other end. In case of pipes of dia less than 1000mm the marking shall be done on outside surface.

10.0 CERTIFICATES

- 10.1 Three original test certificates typed in English shall be submitted along with the inspection report.
- 10.2 The test certificate shall furnish the following details.
- a. BHEL P.O Number & Amendment Number(if any)
 - b. BHEL P.O. Serial Number
 - c. Test Certificate number.
 - d. Specification, grade, size, quantity
 - e. Heat number of plate (or pipe number with traceability to heat number)
 - f. Chemical composition and Mechanical properties
 - g. Hydrostatic test, UT, RT reports as applicable.
 - h. Dimensional report
 - i. Painting details

Records of Revn:00 :- Fresh Issue

 Vivekananda Yellu Dy.Mgr/QA	 K. Rajitha AGM/MM	 C. Karunakaran AGM/Engg	 C Vaithianathan AGM/Quality
Prepared By	Reviewed By		Approved By