

PAINTING SCHEDULE

ANNEXURE- IV.5-1

Worked by	Ashish 31/9/2016 (ASHISH GUPTA)		
Checked by	Rohit 05/10 (Rohit Kumar)		
Approved by	SKD/11 03/10/2016 (SHASHI KASHT)		QAX
	Name	Signature	Dept. Name Signature
Deptt.	HKE		CIE Agreed Depts

CLAUSE NO.		TECHNICAL REQUIREMENTS		PAINTING SCHEDULE PAGE 1 OF 7	
1.00.00		Specification of surface preparation & painting			
1.01.00		Surface preparation methods and paint/primer materials shall be of the type specified herein. If the contractor desires to use any paint/primer materials other than that specified, specific approval shall be obtained by the contractor in writing from the employer for using the substitute material.			
1.02.00		All paints shall be delivered to job site in manufacturers sealed containers. Each container shall be labelled by the manufacturer with the manuacturer's name, type of paint, batch number and colour.			
1.03.00		Unless specified otherwise, paint shall not be applied to surfaces of insulation, surfaces of stainless steel/nickel/ copper/brass/ monel/ aluminum/ hastelloy/lead/ galvanized steel items, valve stem, pump rods, shafts, gauges, bearing and contact surfaces, lined or clad surfaces.			
1.04.00		All pipelines shall be Colour coded for identification as per the NTPC Colour-coding scheme, which will be furnished to the contractor during detailed engineering..			
1.05.0		SURFACE PREPARATION			
1.05.01		All surfaces to be painted shall be thoroughly cleaned of oil. Grease and other foreign material. Surfaces shall be free of moisture and contamination from chemicals and solvents.			
1.05.02		The following surface preparation schemes are envisaged here. Depending upon requirement any one or a combination of these schemes may be used for surface preparation before application of primer. SP1 Solvent cleaning SP2 Application of rust converter (Ruskil or equivalent grade) SP3 Power tool cleaning SP4 Shot blasting (shot blasting shall be used as surface preparation method for hot worked pipes prior to application of primer) SP4* Shot blast cleaning/ abrasive blast cleaning to SA21/2 (near white metal) 35-50 microns SP5 Shot blasting/ abrasive blasting. SP6 Emery sheet cleaning/Manual wire brush cleaning.			
1.06.00		APPLICATION OF PRIMER/PAINT			
1.06.01		The paint/primer manuacturer's instructions covering thinning, mixing, method of application, handling and drying time shall be strictly followed and considered as part of this specification. The Dry film thickness (DFT) of primer/paint shall be as specified herein.			
1.06.02		Surfaces prepared as per the surface preparation scheme indicated herein shall be applied with primer paint within 6 hours after preparation of surfaces.			
1.06.03		Where primer coat has been applied in the shop, the primer coat shall be carefully examined, cleaned and spot primed with one coat of the primer before applying intermediate and finish coats.When the primer coat has not been applied in the shop, primer coat shall be applied by brushing, rolling or spraying on the same day as the surface is prepared. Primer coat shall be applied prior to intermediate and finish coats.			
1.06.04		Steel surfaces that will be concealed by building walls shall be primed and finish painted before the floor is erected.Tops of structural steel members that will be covered by grating shall be primed and finish painted before the grating is permanently secured.			
NORTH KARANPURA STPP (3X660 MW) EPC PACKAGE		TECHNICAL SPECIFICATIONS SECTION VI, PART-B BID DOC. NO. CS-4410-001-2		SUB-SECTION - A-10 SURFACE PREPARATION & PAINTING Page 1 of 7	

CLAUSE NO.	TECHNICAL REQUIREMENTS	PAINTING SCHEDULE PAGE 2 OF 7		
1.06.05	Following are the Primer/painting schemes envisaged herein: PS3 - Zinc Chrome Primer (Alkyd base) by brush/Spray to IS104. PS3* - Zinc Chrome primer (Alkyd base) by dip coat. PS4 - Synthetic Enamel (long oil alkyd) to IS2932. PS5 - Red Oxide Zinc Phosphate primer (Alkyd base) to IS 12744 PS9 - Aluminium paint to IS 2339. PS9* - Heat resistant Aluminium paint to IS-13183 Gr.-1 PS13 - Rust preventive fluid by spray, dip or brush. PS14 - weldable primer-Deoxaluminate or equivalent. PS16 - High Build Epoxy CDC mastic `15' . PS17 - Aliphatic Acrylic Polyurethane CDE134 , %V=40.0(min.) PS18 - Epoxy based TiO2 pigmented coat PS19 - Epoxy Zinc rich primer (92% zinc in dry film (min.), %VS=40.0(min.) PS-20 - Epoxy based finish paint			
1.06.06	All weld edge preparation for site welding shall be applied with one coat of weldable primer.			
1.06.07	For internal protection of pipes/tubes, VCI pellets shall be used at both ends after sponge testing and ends capped. VCI pellets shall not be used for SS components and composite assemblies.			
1.06.08	SG membrane walls and other Flue gas swept pressure part surfaces shall be applied with appropriate primer for protection of surfaces during transit, storage and erection.			
1.06.09	a) all un-insulated equipments, pipes, valves etc covered in sub-section A-06 (Steam Turbine & Auxiliary system) shall be painted with paint not inferior to Epoxy resin based paints with minimum DFT of 150 micron. The paint shall be applied in three stages i.e. primer, intermediate and finish coats in following manner: ▪ Primer coat – Epoxy based zinc phosphate ▪ Intermediate - Epoxy based TiO2 pigmented coat ▪ Finish coat - Epoxy based finish coat b) Equipment, pipes etc. with high temperature shall be painted with heat resistant aluminum paint (to be selected based on the service condition of component as per IS-13183). Two coats of paint shall be applied with total DFT 40 micron. c) Surface preparation before painting shall be carried out according to requirement indicated in this sub-section and international standard			
1.06.10	A) Specification for the application of Epoxy coating for internal protection of DM tank & other vessels/tanks (as applicable) shall be as follows: Primer : One coat of unmodified epoxy resin along with polyimide hardener. Paint : Two (2) coats unmodified epoxy resin along with Aromatic adduct hardener. Total thickness of primer and paint should not be less than 400 microns. B) Specification for application of chlorinated Rubber paint for external protection vessel, tanks, piping, valves & other equipments shall be as follows: i) For Indoor vessel, tanks, piping, valves & other equipments: (a) Surface preparation shall be done either manually or by any other approved method.			
NORTH KARANPURA STPP (3X660 MW) EPC PACKAGE		TECHNICAL SPECIFICATIONS SECTION VI, PART-B BID DOC. NO. CS-4410-001-2	SUB-SECTION - A-10 SURFACE PREPARATION & PAINTING	Page 2 of 7

CLAUSE NO.	TECHNICAL REQUIREMENTS			PAINTING SCHEDULE PAGE 3 OF 7	
	(b) Primer coat shall consist of one coat of chlorinated rubber based zinc phosphate primer having minimum DFT of 50 microns. (c) Intermediate coat (or under coat) shall consist of one coat of chlorinated rubber based paint pigmented with Titanium dioxide with minimum DFT of 50 microns. (d) Top coat shall consist of one coat of chlorinated rubber paint of approved shade and colour with glossy finish and DFT of 50 microns. Total DFT of paint system shall not be less than 150 microns. ii) For Outdoor vessel, tanks, piping, valves & other equipments: (a) Surface preparation shall be blast cleared using non-siliceous abrasive after usual wire brushing, which shall conform to Sa 2-1/2 Swiss Standard. (b) Primer coat shall consist of one coat of epoxy resin based zinc phosphate primer having minimum DFT of 100 microns. (c) Intermediate coat (or under coat) shall consist of epoxy resin based paint pigmented with Titanium dioxide with minimum DFT of 100 microns. (d) Top coat shall consist of one coat of epoxy paint suitable pigmented of approved shade and colour with glossy finish and DFT of 75 microns. Additionally finishing coat of polyurethane of minimum DFT of 25 microns shall be provided. The paint may be applied in one coat, in case high built paint is used, otherwise two coats shall be applied. Total DFT shall not be less than 300 microns.				
NORTH KARANPURA STPP (3X660 MW) EPC PACKAGE		TECHNICAL SPECIFICATIONS SECTION VI, PART-B BID DOC. NO. CS-4410-001-2		SUB-SECTION - A-10 SURFACE PREPARATION & PAINTING	Page 3 of 7


1.06.10 Primer/Painting Schedule

Sl. No	Description	Surface Preparation	Primer Coat			Intermediate Coat			Finish Coats			Total Min. Painting DFT (Microns)	Colour Shade	
			Type of Primer	No. of Coats	Min. DFT / coat (Microns)	Type of coating	No. Coats	Min. DFT/ Coat (Microns)	Type of coating	No. Coats	Min. DFT/ Coat (Microns)			
A) Power Cycle Piping														
1.	All insulated Pippings, fittings/ components, Pipe clamps, Vessels/Tanks, Equipments etc.	SP3/SP4	PS9*	1	20	-			PS9*	1	20	40	As per NTPC Colour shade/ coding scheme	
2.	All un-insulated Pippings, fittings/ components, Pipe clamps, Vessels/Tanks, Equipments etc.	SP3/SP4	PS 5	2	25	-			PS 4	3	35 \$	155 \$		
3	Constant Load Hanger (CLH) and Variable Load Hanger (VLH)	SP4*	PS19	1	35	-			PS17	1	30	70		
4	Piping hangers/ supports (other than (3) above. (un-insulated)	SP4 (SP6 - for cleaning of weld joints after erection,)	PS 5	1	40	PS 4	1	40	PS 17	1	40	120		
5.	Valves													
	a.) Cast / Forged Design Temo < 60 °C Design Temo > 60 °C	SP1/SP2 /SP3	PS9	1	20				PS 9	1	20	40		
			#PS9*	1	20	-	-	-	#PS9*	1	20	40		
NORTH KARANPURA STPP (3X 660 MW) EPC PACKAGE			BID DOC. NO. CS-4410-001-2			TECHNICAL SPECIFICATIONS SECTION VI, PART-B			TECHNICAL REQUIREMENTS			Sub-Section -A-10 Surface Preparation & Painting		Page 4 of 7

6.	All auxiliary Structural Steel components for pipe supports	Outside TG building and in SG envelope	SP4*	Inorganic Ethyl Zinc Silicate	1	75	PS18	1	75	a)Epoxy coat b)Final coat of paint PS17	2 1	35 30	250
		Within TG building	SP4*	-do-	1	35	PS18	1	35	a)Epoxy coat b)Final coat of paint PS17	2 1	25 30	150
7.	Weld Edges		SP6 (Hand cleaning by wire burshing)	PS13 (Weldable primer)	1	25	-	-	-	-	-	-	-
B) Steam Generator & Auxiliaries:													
1	All surfaces with temperature 95°C or less and which are insulated	All surfaces with temperature above 95°C and which are insulated	SP3/SP4	PS 5	2	30	-	-	-	PS 4	2 \$	20 \$	100 \$
2			SP3/SP4	PS9*	1	20	-	-	-	PS9*	1	20	40
Note: 1) SG membrane walls and other Flue gas swept pressure part surfaces shall be applied with appropriate primer for protection of surfaces during transit, storage and erection. 2) Painting specification for all other exposed steel surfaces not covered above shall be same as that given in Civil Sub-section, Part-B, Section VI for corrosion protection of steel structures.													
C) LOW PRESSURE PIPING													
1	All Pipes, fittings / components, valves, Equipments etc.	SP3/SP5	PS3/PS5	2	25	PS 4	1	30	PS 4	2	35	150	As per NTPC Colour

	Condensate storage tank, (External painting)	SP3/SP5	Epoxy paint minimum DFT 150 micron (finish paint to be preceded by suitable primer paint)	shade/ coding scheme
2	Condensate storage tank (Inside protection)	SP3/SP5	Solvent free epoxy coating (minimum two coats) of total DFT 200 microns.	As per NTPC Colour shade/ coding scheme
3	Drinking water tank (Protection of Internal surface)(if applicable)	Two coats of food grade epoxy paint.		
4	Stainless steel surface, Galvanized steel surface and gun metal surface.	No Painting		
5	On the internal surface for pipes 1000 Nb and above	A coat of primer followed by hot coal-tar enamel or coal tar epoxy painting (cold) shall be applied.		
6				
D) Fire Detection & Protection System, Compressed air system, Hydrogen generation plant and Air-conditioning & Ventilation System				
For Fire Detection & Protection System, Surface preparation and painting of Fire Water Storage Tanks, all Steel Surfaces (external) exposed to atmosphere (outdoor & indoor installation), Deluge Valves, Alarm Valves, Foam monitors, Water monitors, Foam Proportioning equipments, Foam makers, etc. should be as per the Part-B, Sub Section-A-16, Fire Detection & Protection System				
For Air Conditioning System, Surface preparation and painting of all the steel surfaces (external) exposed to atmosphere (outdoor & indoor installation), centrifugal fans – Casing etc. should be as per the Part-B, Sub Section-A-15, Air Conditioning System.				
For Ventilation System, Surface preparation and painting of all the steel surfaces (external) exposed to atmosphere (outdoor & indoor installation), centrifugal fans – Casing etc. should be as per the Part-B, Sub Section-A-23, Ventilation System.				
For compressed air system, Surface preparation and painting of all the steel surfaces should be as per the Part-B, Sub Section--A-14 compressed air system.				
For hydrogen generation plant, Surface preparation and painting should be as per the Part-B, Sub-Section-A-17 hydrogen generation plant.				



D) ESP												
1	All surfaces with surface temperature 95°C or less (with or without insulation)	SP3/SP4	PS3/ PS3*	1	25	-	-	-	PS 4	1	30	55
2	All surfaces with surface temperature above 95°C (with or without insulation)	SP3/SP4	PS5	2	30	-	-	-	-	-	-	60