

	<b>TECHNICAL SPECIFICATION FOR FINISH TO MASONRY &amp; CONCRETE</b>	SPECIFICATION NO. PE-TS-999-600-C009	
		VOLUME - II B	
		SECTION - D	SUB-SECTION – C9
		REV.NO. 00	
		SHEET 1	OF 8


**VOLUME – II B**  
**CIVIL, STRUCTURAL & ARCHITECTURAL WORKS**

**SPECIFICATION NO. PE-TS-999-600-C009**

**SECTION - D**

***GENERAL TECHNICAL SPECIFICATION***

**FINISH TO MASONRY & CONCRETE**



**Bharat Heavy Electricals Limited**  
**Project Engineering Management**  
**PPEI Building, Power Sector,**  
**Plot No. 25, Sector 16A,**  
**Noida (U.P.)-201301**

	<b>TECHNICAL SPECIFICATION FOR FINISH TO MASONRY &amp; CONCRETE</b>	SPECIFICATION NO. PE-TS-999-600-C009	
		VOLUME - II B	
		SECTION - D	SUB-SECTION – C9
		REV.NO.	00
		SHEET	2      OF      8

### TABLE OF CONTENT

CLAUSE NO.	DESCRIPTION	PAGE NO.
1.0.0	SCOPE	3
2.0.0	INSTALLATION	3
3.0.0	ACCEPTANCE CRITERIA	8
4.0.0	I.S. CODES	8

	<b>TECHNICAL SPECIFICATION FOR FINISH TO MASONRY &amp; CONCRETE</b>	SPECIFICATION NO. PE-TS-999-600-C009	
		VOLUME - II B	
		SECTION - D	SUB-SECTION – C9
		REV.NO.	00
		SHEET	3      OF      8

**TECHNICAL SPECIFICATION  
FOR  
FINISH TO MASONRY & CONCRETE**

**1.0.0      SCOPE**

This Specification covers furnishing, installation, repairing, finishing, curing, testing, protection, maintenance till handing over of finishing items for masonry and concrete. This shall also include the work to be done to make the surface suitable for receiving the finishing treatment. Before commencing finishing items the Contractor shall obtain the approval of the Engineer regarding the scheduling of work to minimise damage by other trades. He shall also undertake normal precaution to prevent damage or disfiguration to work of other trades or other installation.

**2.0.0      INSTALLATION**

**2.1.0      Preparation of Surface**

All joints in masonry walls shall be raked out to a depth of at least 10 mm with a hooked tool made for the purpose while the mortar is still green. Walls shall be brushed down with stiff wire brush to remove all loose dust from joints and thoroughly washed with water. All laitance shall be removed from concrete to be plastered.

For all types of flooring, skirting and dado work, the base cement concrete slab or masonry surface shall be roughened by chipping and cleaned of all dirt, grease or loose particles by hard brush and water. The surface shall be thoroughly moist to prevent absorption of water from the base course. Any excess of water shall be mopped up.

At any point, the level of base shall be lower than the theoretical finished floor level by the thickness of floor finish. Any chipping or filling to be done to bring the base in the required level shall be brought to the notice of the Engineer and his approval shall be taken regarding the method and extent of rectification work required.

Prior to commencement of actual finishing work, the approval or the Engineer shall be taken as to the acceptability of the base.

**2.2.0      Plastering**

**2.2.1      Mortar**

Mortar for plastering shall be as specified in the drawings.

	<b>TECHNICAL SPECIFICATION FOR FINISH TO MASONRY &amp; CONCRETE</b>	SPECIFICATION NO. PE-TS-999-600-C009	
		VOLUME - II B	
		SECTION - D	SUB-SECTION – C9
		REV.NO.	00

SHEET 4 OF 8

For sand cement plaster, sand and cement in the specified proportion shall be mixed dry on a watertight platform and minimum water added to achieve working consistency.

For lime gauged plaster, lime putty or hydrated lime and sand in the required proportion shall be mixed on a watertight platform with necessary addition of water and thoroughly ground in mortar mill. This mix shall then be transferred to a mechanical mixer to which the required quantity of cement is added and mixed for at least 3 minutes.

No plaster which has stood for more than half an hour shall be used; plaster that shows tendency to become dry before this time, shall have water added to it.

#### 2.2.2 Application of Plaster

Plaster, when more than 12 mm thick, shall be applied in two coats - a base coat followed by the finishing coat. Thickness of the base coat shall be sufficient to fill up all unevenness in the surface; no single coat, however, shall exceed 12 mm in thickness. The lower coat shall be thicker than the upper coat, the overall thickness of the coats shall not be less than the minimum thick-ness shown on the drawings. The undercoat shall be allowed to dry and shrink before applying the second coat of plaster. The under-coat shall be scratched or roughened before it is fully hardened to form a mechanical key. The method of application shall be 'thrown on' rather than 'applied by trowel'.

To ensure even thickness and true surface, patches of plaster about 100 mm to 150 mm square or wooden screed 75 mm wide and of the thickness of the plaster, shall be fixed vertically about 2000 mm to 3000 mm apart, to act as gauges. The finished wall surface shall be true to plumb, and the Contractor shall make up any irregularity in the brickwork with plaster.

All vertical edges of brick pillars, doorjambs etc. shall be chamfered or rounded off as directed by the Engineer. All drips, grooves, mouldings and cornices as shown on drawing or instructed by the Engineer shall be done with special care to maintain true lines, levels and profiles. After the plastering work is completed, all debris shall be removed and the area left clean. Any plastering that is damaged shall be repaired and left in good condition at the completion of the job.

#### 2.2.3 Finish

Generally, the standard finish shall be used unless otherwise shown on drawing or directed by the Engineer. Wherever any special treatment to the plastered surface is indicated, the work shall be done exactly as shown on the drawings, to the entire satisfaction of the Engineer regarding the texture, colour and finish.

##### a) Standard Finish

	<b>TECHNICAL SPECIFICATION FOR FINISH TO MASONRY &amp; CONCRETE</b>	SPECIFICATION NO. PE-TS-999-600-C009	
		VOLUME - II B	
		SECTION - D   SUB-SECTION - C9	
		REV.NO. 00	
		SHEET 5	OF 8

Wherever punning is indicated, the interior plaster shall be finished rough. Otherwise the interior plaster shall generally be finished to a smooth surface. The exterior surface shall generally be finished with a wooden float.

**b) Neat Cement Finish**

Immediately after achieving a true plastered surface with the help of a wooden straight edge, the entire area shall be uniformly treated with a paste of neat cement at the rate of one (1) kg. per Sq.M. and rubbed smooth with a trowel.

**c) Coloured Plaster Finish**

This shall be done in the same way as specified in Clause 2.2.2 but using coloured cement in place of ordinary cement. When coloured plastering is specified in more than one coat, the top coat only shall be made with coloured cement.

Coloured cement shall be either ready mixed material or may be obtained by mixing pigments and cement at site, as approved by the Engineer. The pigments to be mixed with cement shall conform to Appendix-A of IS:2114 latest edition. Samples of colouring material shall be submitted to the Engineer for approval and material procured, shall conform in all respects to the approved samples, which shall remain with the Engineer. All coloured cement and/or pigments shall be stored in an approved manner in order to prevent deteriorations.

**d) Pebble-dash Finish**

Mortar of required thickness consisting of 1 part cement and 4 parts sand by volume shall be applied in the usual manner as described under plastering Clause 2.2.2. While the mortar is still plastic small pebbles or crushed stone of size generally from 10 mm to 20 mm as approved by the Engineer shall be thrown on the plastered surface. The aggregate shall be lightly tapped into the mortar with a wood float or the flat end of a trowel, in order to ensure satisfactory bond between the dashing and the mortar.

**e) Rough-Cast Finish**

A wet plastic mix of 3 parts coloured cement 6 parts sand and 4 parts aggregate by volume (gravel or crushed stone of size from 6 mm to 12 mm as approved by the Engineer) shall be thrown on to the wall by means of a plaster's trowel and left in the rough condition.

	<b>TECHNICAL SPECIFICATION FOR FINISH TO MASONRY &amp; CONCRETE</b>	SPECIFICATION NO. PE-TS-999-600-C009	
		VOLUME - II B	
		SECTION - D	SUB-SECTION – C9
		REV.NO.	00
		SHEET	6      OF      8

**f) Scraped Finish**

Ordinary plaster as described under Clause 2.2.2 after being levelled and allowed to stiffen for a few hours, shall be scraped with a steel straight edge to remove the surface skin. The pattern shall be as approved by the Engineer.

**g) Textured Finish**

Mortar consisting of 1 part cement and 3 parts sand by volume shall be applied in a manner as specified under "Plastering" Clause 2.2.2. Ornamental treatments in the form of horizontal or vertical rib texture fan texture etc. shall be applied by means of suitable tools to the freshly applied plastered surface, as approved by the Engineer.

**2.2.4 Curing**

All plastered surfaces after laying, shall be watered, for a minimum period of seven days, by an approved method, and shall be protected from excessive heat and sunlight by suitable approved means. Moistening shall commence, as soon as the plaster has hardened sufficiently and not susceptible to damage. Each individual coat of plaster shall be kept damp continuously, for at least two days, and then dried thoroughly, before applying the next coat.

**2.3.0 Pointing to Masonry**

All joints of brickwork shall be raked out to a depth of 10 mm with a hooked tool made for the purpose while the mortar is still green. The brickwork shall then be brushed down with a stiff wire brush, so as to remove all loose dust from the joints and thoroughly washed with water. Mortar consisting of 1 part cement and 3 parts clean, sharp, well graded sand by volume shall be pressed carefully into the joints and finished with suitable tools to shape as shown on the drawings. Any surplus mortar shall be scraped off the wall face leaving the surface clean.

The pointed surface shall be kept wet for at least three days for curing.

**2.4.0 Plaster with Metal Lath**

The supports, hangers, brackets, cleats etc. shall be as shown on drawings and/or as approved by the Engineer. These shall have a coat of prime paint before and another coat of approved paint after erection.

The metal lath shall be expanded metal, with 12 mm x 38 mm mesh, 16 BG thick and 3 mm wide strands. Side laps shall be minimum 12 mm and end laps 25 mm minimum. The plastering shall be minimum 20 mm thick measured from the back of lath and applied in two layers.

	<b>TECHNICAL SPECIFICATION FOR FINISH TO MASONRY &amp; CONCRETE</b>	SPECIFICATION NO. PE-TS-999-600-C009	
		VOLUME - II B	
		SECTION - D   SUB-SECTION - C9	
		REV.NO. 00	
		SHEET 7	OF 8
<p>The mortar for plastering shall consist of 1 part cement, 1/2 part lime and 4 parts sand by volume, or 1 part cement and 4 parts sand by volume mixed as specified in plastering, Clause 2.2.1. The application, finish etc. shall be as specified under relevant clause above. A 2 mm Plaster of Paris punning shall be applied over plaster as a finishing coat to give perfectly smooth and even finish.</p>			
2.5.0	<b>Lime Punning</b>	<p>For plastered surfaces, where an even smooth surface is specified, lime punning with 5 parts of shell lime properly slaked, strained and aged, mixed with 1 part clean, washed, sieved, fine sand by volume shall be done. The thickness of lime punning shall be not less than 2 mm and more than 3 mm. The plastered surface shall be saturated with water before application of the lime punning. The punning shall be applied by skilled workman and given a smooth and even finish free from undulations, cracks etc. and to the satisfaction of the Engineer.</p>	
2.6.0	<b>Plaster of Paris Punning</b>	<p>Plastered surfaces, where specified shall be finished with Plaster-of-Paris punning. The material shall be from approved manufacturers and approved by the Engineer. The thickness of the punning shall be 2 mm and shall be applied by skilled workmen. The finish shall be smooth, even and free from undulation, cracks etc.</p> <p>Before bulk work is taken in hand, a sample of punning shall be done on roughly 10 Sq.M. area and approval of the Engineer taken. The work shall then be taken in hand as per approved sample.</p>	
2.7.0	<b>Stone Facing</b>	<p>Stone facing where specified shall be done as shown on design drawings and approved shop drawings. The stone shall be as specified on drawings. Samples of stone shall be submitted to the Engineer for approval and then bulk purchase made. The Contractor shall submit three copies of shop drawing for the Engineer's approval before commencing the work.</p> <p>The thickness of facing stone shall be not less than 25 mm unless otherwise specified on drawings.</p> <p>The stone slabs shall be cut and finished to sizes as per pattern shown on drawings. They shall be fastened to wall with suitable noncorrodable anchorage as approved by the Engineer. Where mild steel clamps, stays etc. are used for anchorage, they shall be galvanised (weight of zinc coating shall not be less than 700 gms per square meter of surface) to prevent rust stains developing on the finished surface. There shall be at least 12 mm gap between the stone and masonry, which shall be filled up and packed by a mortar of 1 part cement and 3 parts of sand by volume. After the mortar is set and cured for at least four days, the exposed surface shall be rubbed and polished as approved by the Engineer.</p>	

	<b>TECHNICAL SPECIFICATION FOR FINISH TO MASONRY &amp; CONCRETE</b>	SPECIFICATION NO. PE-TS-999-600-C009	
		VOLUME - II B	
		SECTION - D   SUB-SECTION - C9	
		REV.NO. 00	
		SHEET 8	OF 8
<p>The completed surface shall be neat, or uniform texture and acceptable to the Engineer.</p> <p>Where pointing is specified on drawings it shall be done by mortar as specified on drawings.</p>			
3.0.0	<b>ACCEPTANCE CRITERIA</b>	<p>Finish to masonry and concrete shall fully comply instructions of the Engineer with respect to lines, levels, thickness, colour, texture, pattern and any other special criteria as shown on drawings.</p>	
4.0.0	<b>I.S. CODES</b>	<p>Important relevant code for this Section :</p> <p>a) IS:1661 : Code of practice for cement and cement-lime plaster finish on walls &amp; ceilings.</p> <p>b) IS:4101 : Code of practice for external facings and veneers.</p>	