



**BHARAT HEAVY ELECTRICALS LIMITED**  
IVP GOINDWAL SAHIB  
MM DEPARTMENT

**Date: 12.08.2022**

**Corrigendum-I**

**Reference:** Tender Enquiry no. Enquiry 2223-029E Dated 06.08.2022 for the procurement of “Miscellaneous Fasteners”.

Due date of submission of quotations of above referred tender enquiry has been extended up to 18.08.2022 at 1400 Hrs. Tender will be opened on 18.08.2022 at 1530 Hrs.

TDC 5: 164 as mentioned in the Drawing of Item Sr. no. 2 and Sr. 4 has uploaded.



**Product: CARBON & ALLOY STEEL FASTENERS (STUDS, BOLTS & NUTS) FOR VALVES, OIL FIELD EQUIPMENT (OFE) AND OTHER APPLICATIONS**

Revision Record: 00: 17.01.90: First issue. Rev: 01:21.06.90 Editorial corrections. Rev 02:21.04.91 TC for studs/bolts added. Rev 03: 04.04.96: Annexure I amended. CI 3.3.3 & 5.3 modified. Rev 04:20.10.96: NDT, Acid pickling added & re-written. Rev 05: 28.04.98: CI 3 modified to include MPI, certificate modified & CI 7.4 deleted. Rev 06:15.06.99: Title, CI 1 to 5 & 7.1 modified. CI 7.2 changed to CI 7.3. CI 7.3 changed to 7.4 and modified. CI 7.2 Galvanizing added. Test certificate sample format modified.

**Rev 07: 15/06/2017:** TDC: 5:166 for CS & AS Nuts has been merged with this TDC. Totally revised in line with changed requirements and Xylan coating requirements added.

**Rev 08: 14/09/2019:** CI 1.0, 2.0, 3.0, 4.0, 5.0 modified in line with API 6A 21<sup>st</sup> Ed 2018 Errata 1 and for better clarity.

## 1.0 MATERIAL SPECIFICATIONS:

All the codes, standards, specifications, drawings & procedures, etc., referred in this TDC shall be of latest revision as on the date of Purchase Order, unless specified otherwise.

<b>Studs/Bolts - Alloy Steel</b>	:	ASME/ASTM SA/A 193 Gr B7, B7M & B16.
<b>Nuts - Carbon Steel</b>	:	ASME/ASTM SA/A 194 Gr 2H & 2HM
<b>Alloy Steel</b>	:	ASME/ASTM SA/A 194 Gr 4 & 7
Additional Requirements	:	As listed below (Supplementary to the above material specifications)
Size and Quantity	:	As per Purchase Order (PO) & Applicable Drawing

## 2.0 GENERAL REQUIREMENTS:

- i. This TDC is applicable for Valves, OFE (API 6A 21<sup>st</sup> Ed 2018 Errata 1 & 16C 2<sup>nd</sup> Ed 2015 Addendum 1 Errata 4) and other applications including NACE MR0175 / ISO 15156:2015 Parts 1, 2 & 3. The products shall be manufactured to the relevant requirements specified in the applicable drawings, specifications, PO & this TDC.
- ii. *Studs / Bolts / Nuts used for OFE application:*
  - a. *Studs / Bolts / Nuts shall be qualified and manufactured in accordance with BSL 1 of API 20E. The qualification & requalification records as per API 20E shall be maintained by the Supplier. The supplier shall prepare and Manufacturing Process Specification(MPS) to include as a minimum allowable levels for all Studs/Bolts/Nuts manufacturing parameters including process control variables and heat treatment parameters as per API 20E and this TDC.*
  - b. *Raw material shall be fully wrought. Reduction ratio based on starting material diameter shall be a minimum of 4:1. The steel shall conform to the respective material specifications. Intentional addition of Boron is not allowed. All elements intentionally added to the heat shall be reported in the Test Certificate.*
  - c. *Furnace calibration shall be in accordance with API 6A Annex M; SAE AMS 2750; or SAE AMS H6875. For induction or direct resistant heat treatment, calibration shall be in accordance with manufacturer's written procedure. For forging furnaces, calibration shall be in accordance with manufacturer's written procedure*
- iii. Nuts shall be hot/cold forged or manufactured from hot rolled/cold drawn bars. If made from hexagonal bars, 100% MT is to be done on bars as per ASTM E709 to ensure freedom from surface/sub-surface defects.
- iv. Hot rolled & cold drawn bars, if used (for studs/bolts or nuts), shall be machined at least 2 mm (minimum) in radius (i.e. 4 mm in diameter) to remove the seams completely. After machining, at least 10% of the bars shall be tested by MPI as per ASTM E709 to ensure freedom from surface/sub-surface defects.
- v. Heat treatment of finished studs/bolts shall be carried as per the material specification requirements for corresponding grades. For heat treatment of finished components, salt bath



Product: CARBON & ALLOY STEEL FASTENERS (STUDS, BOLTS & NUTS) FOR VALVES, OIL FIELD EQUIPMENT (OFE) AND OTHER APPLICATIONS

or controlled atmosphere furnace shall be used. After heat treatment, the threads shall be thoroughly cleaned to remove all deposits. If acid pickling is done for cleaning, it shall be as per Cl. 6 (v) of this TDC.

- vi. Cadmium Plating (Cl 6 (i) of this TDC), Electroplating (Cl 6 (ii) of this TDC) and/or Xylan Coating (Cl 6 (iii) of this TDC) shall be done on the fasteners if specified in Drawing/PO. For all other cases, rust preventive coating (Cl 6 (iv) of this TDC) shall be done.

### 3.0 CHEMICAL, MECHANICAL PROPERTIES & NDE:

- i. Mill certificate from steel manufacturer for conformance to chemistry heat-wise shall be submitted. Additionally, product analysis shall be done on one sample/heat by the stud/bolt/nut manufacturer. *Methods and practices for chemical analysis shall be in accordance with ASTM A 751.*
- ii. *The microstructure and macrostructure shall conform to the requirements of the respective material specifications.*
- iii. **Tensile Testing for Studs/Bolts:** One tensile test/heat/size/ HT batch shall be carried out in the finished heat treated condition as per SA / A 193 and shall meet the material specification requirements for corresponding grades.
- iv. **Hardness Testing for Studs/Bolts:**

*Hardness testing, including specimen preparation, shall be performed in accordance with ASTM A 370 including Annex A3, except that testing shall also be in conformance with ASTM E10 or ASTM E18.*

- a) **For SA / A 193 Gr B7 & B16:** Hardness check shall be carried out on finished stud/ bolt as per SA / A 193, at least on 10% of the finished studs/bolts.  
*Gr B7: Hardness: 25 to 34 HRC or 253 to 319 HBW.*  
*Gr B16: Hardness: 25 to 35 HRC or 253 to 321 HBW.*

- b) **For SA / A 193 Gr B7M:**  
Hardness check on 100% of studs/bolts as per SA193.  
*Gr B7M: Hardness: 94 to 99 HRB or 201 to 235 HBW.*

v. **Mechanical Testing for Nuts:**

- a) **For SA / A 194 Gr 2H, Gr 4, & Gr 7:**  
Hardness check on finished nuts shall be as per SA / A 194 (including quantum of testing).  
*Gr 4: Hardness: 24 to 35 HRC or 248 to 327 HBW.*  
*Gr 2H & Gr 7: Hardness: 24 to 34 HRC or 248 to 319 HBW.*
- b) **For SA / A 194 Gr 2HM:**  
Hardness check on 100% of finished nuts shall be carried out as per SA / A 194.  
*Gr 2HM: Hardness: 159 to 235 HBW.*
- c) **Proof load test shall be done as per SA / A 194 for all grades of nuts** and shall meet the requirements of corresponding grades of the material specification.
- d) After final heat treatment, sample nuts shall be heat treated as per Table 1 and meet the corresponding hardness requirements.

Table 1.

Grade	Temperature (°C)	Soaking Time (Hr)	Cooling	Minimum Hardness (HBW) at room temperature
2H	540	24	Slow Cool	179
2HM	540	24	Slow Cool	159
4, 7	590	24	Slow Cool	201



**Product: CARBON & ALLOY STEEL FASTENERS (STUDS, BOLTS & NUTS) FOR VALVES, OIL FIELD EQUIPMENT (OFE) AND OTHER APPLICATIONS**

e) **Cone Stripping Test:** This test shall be performed as per SA / A 194 in case of visible surface discontinuities. On such cases Proof load shall be as per SA / A 194.

vi. **NDE:**

Magnetic particle inspection shall be carried out as per ASTM E709 in at least 10% of the finished studs/bolts of all grades. Cracks, linear indications (length  $\geq$  3 times its width) are unacceptable.

**4.0 SAMPLING INSPECTION:**

All inspection shall be in accordance with relevant drawing or BPS (Boiler Plant Standard), PO, this TDC and SA / A 193 for studs/bolts and SA / A 194 for nuts. The threads shall be checked with calibrated ring gauges for studs/bolts & plug gauges for nuts in the final heat treated condition for black variety and in final plated/coated condition for the cadmium plated/electroplated/ xylan coated items.

Visual, dimensional checks and their acceptance shall be as per applicable drawing and ASME SA / A 193 for studs/bolts & SA / A 194 for nuts.

**5.0 MARKING & PACKING:**

- i. Punch/emboss each finished component with applicable material grade (B7/ B7M/ B16 for studs/bolts; 2H/2HM/4/7 for nuts) and supplier's emblem. Studs/bolts of grade B7M and nuts of Gr 2HM shall have a line under the grade symbol.
- ii. Punch/emboss serial number also in B7M studs/bolts and Gr 2HM nuts in addition to the above, to correlate with hardness. Protect the threaded ends with plastic end caps. Pack in wooden box/ gunny bag of convenient size for easy handling and transportation. Mark quantity in each box/gunny bag.
- iii. *In addition to the above, studs / Bolts / Nuts for OFE applications shall marked with unique heat lot identification and followed by "20E1". Each piece 1 in. nominal diameter and larger shall be marked. For studs / Bolts / Nuts less than 1 in. nominal diameter, the studs / Bolts / Nuts shall be securely containerized to maintain heat lot identification and traceability. Multiple heat lots shall not be mixed in a single container. Containers used in the processing, storing, and shipping of studs / Bolts / Nuts not individually marked shall be clearly labeled with all marking information required by the relevant material specifications and API 20E.*

**6.0 SPECIAL REQUIREMENTS:**

**i. CADMIUM PLATING:**


- a) Clean the fasteners to make them free from rust, grease, oil, scale, etc., before plating. When pickling is considered essential, it shall be done as per CI 6 (v) of this TDC.
- b) Apply Cadmium Plating to the specified thickness on specified areas. Thickness shall be measured on 5% of the PO quantity of fasteners.
- c) After plating, bake the parts at 175°C to 205°C for a minimum period of 3 hours. The elapsed time between plating and baking shall not exceed 8 hours.
- d) Apply a Chromate Conversion coating after plating and baking.

**ii. ELECTROPLATING OF ZINC CHROMATE:**

- a) Clean the fasteners to make them free from rust, grease, oil, scale, etc., by suitable organic solvents/ hand tool methods before electroplating. Then, pickling shall be done as per CI 6 (v) of this TDC.
- b) The fasteners shall then be electroplated as per the method and to the minimum coating thickness specified in the applicable drawing. Thickness shall be measured on 5% of the PO quantity of fasteners.

**iii. XYLAN COATING:**

- a) Clean the fasteners by blast cleaning to Sa2.5 to make them free from rust, grease, oil, scales, etc., before xylan coating.
- b) The fasteners shall then be xylan coated as per the requirements and to the minimum coating thickness specified in the applicable drawing.

	<b>BHEL – Tiruchirappalli - 620014, India.</b> Quality Assurance Department <b>TECHNICAL DELIVERY CONDITIONS</b>	DOC No: <b>TDC:5:164 Rev: 08</b> Effective Date: <b>14/09/2019</b> Page: <b>4 of 6</b>
	<b>Product: CARBON &amp; ALLOY STEEL FASTENERS (STUDS, BOLTS &amp; NUTS) FOR VALVES, OIL FIELD EQUIPMENT (OFE) AND OTHER APPLICATIONS</b>	

**c) Tests for Xylan Coating:**

The following test shall be carried out on Xylan coated fasteners and results to be reported in the Test certificate (in addition to the Test Certificate for the fastener material and other inspections requirements):

**i) Thickness measurement:**

Dry film thickness of Xylan coating to be measured using a magnetic induction or Eddy current type electronic gauge and the reading shall meet the drawing/PO requirement for thickness of coating of Xylan 1070. The thickness measurements shall be made in accordance with ASTM D7091. Thickness shall be measured on 5% of the PO quantity of fasteners.

**ii) Cure Test:**

This test method is for ensuring the completeness of cure of Xylan 1070 coating by evaluating the resistance of the cured coating to a solvent known to attack uncured film. The testing method shall be as per Whitford test method 115B (as recommended by the Xylan coating supplier).

**Acceptance criteria:** No white precipitate or stain shall be available after the test.

**iii) Adhesion Test using Cross-hatch and Cello Tape:**

Test as per ASTM D-3359 Method B for measuring Adhesion by Tape Test.

**Acceptance Criteria:** No loss of adhesion (5B Classification).

**iv) Salt Spray Test:**

Xylan coated fasteners should pass a minimum requirement of 500 hours of salt spray test as per ASTM B117. Certificate of compliance for meeting the salt spray test requirements shall be provided.

**iv. RUST PREVENTIVE FLUIDS/COATING REQUIREMENTS:**

a) Clean the fasteners to make them free from rust, grease, oil, scale, etc., by hand tool/ manual cleaning method.

b) Apply one coat of rust preventive fluid, of any of the following brands of the suppliers (Table 2), to obtain dry film thickness of 20 microns minimum:

**Table 2. Rust Preventive Fluid/Coatings Brands**


SI No	Brand/Chemical	Supplier Name and Address
1	BONITA-RPF	M/s Bonita Chemicals, 64, Industrial Estate, Nunhai, Agra-282 006
2	CHAMPION-RPF	M/s Guardian Chemicals, 8, Rajaji IInd st, West Lake Area, Nungambakkam, Madras-600 034
3	ECONOL RPF (non-drying type)	M/s Process Aids, Bangalore
4	TECTYL 506	M/s Plastipeel Chemicals and Plastics (P) Ltd, Thane-400 604
5	TRPF	M/s Sundaram Paints Pvt. Ltd., Thanjavur-613 004
6	TRPF	M/s Solar Paints, Pudukkottai.
7	WICOR-P	M/s Western India Paint and Color Co P. Ltd, Madras-600 017

Use of any other brand/chemical shall be done with the prior approval of BHEL.

**v. ACID PICKLING:**

a) Wherever pickling done, it shall be done using Hydrochloric acid of 5-10% concentration for a period of 5 to 10 minutes at room temperature with suitable inhibitor.







b) After pickling thorough rinsing shall be carried out with water to remove acid residues & further DM water rinsing. After thorough rinsing with DM water, the rinsing shall not show any red color (free acidity) when tested with methyl orange indicator.

	<b>BHEL – Tiruchirappalli - 620014, India.</b> <b>Quality Assurance Department</b> <b>TECHNICAL DELIVERY CONDITIONS</b>	<b>DOC No: TDC:5:164 Rev: 08</b> <b>Effective Date: 14/09/2019</b> <b>Page: 5 of 6</b>
	<b>Product: CARBON &amp; ALLOY STEEL FASTENERS (STUDS, BOLTS &amp; NUTS) FOR VALVES, OIL FIELD EQUIPMENT (OFE) AND OTHER APPLICATIONS</b>	

**7.0 CERTIFICATION:**

The manufacturer shall provide Test Certificates (TC) duly countersigned by the Authorized Inspecting Authority nominated by BHEL in P.O. (if specified) along with raw material TC from Steel Maker. Manufacturer's TC shall contain the following details as per the sample format attached as Annexure-1 to this TDC:

- i. BHEL PO No & PO Date
- ii. Technical Delivery Condition (TDC) No & its Revision No, Drawing & its revision no
- iii. Melt/Heat No, Serial No (if applicable)
- iv. Raw Material TC Number and Date
- v. Chemical and Mechanical properties for Studs/Bolts and Nuts
- vi. Heat treatment details (temperature, time, cooling medium, etc.)
- vii. NDE Results with reference and acceptance criteria
- viii. Type of Surface coating & its coating thickness – Cadmium Plating, Chromate conversion coating, Electroplating, Xylan Coating, Rust preventive coating, etc.
- ix. Test methods and results on Xylan Coating
- x. Baking details for cadmium plating, electroplating & Xylan coating
- xi. Manufacturers' identification mark
- xii. Certify soundness & confirmation to PO requirements.

 14/09/19	 14/09/19	 14/09/19	 14/09/19	 14/09/19	 14/09/2019
Abdur Rahman Sultan	N Nagamuthu Pandian	P Arun kumar	S Lakshmi	A Wilfred Joseph	J V V Aruna Kumar
SQAE/QA	DM/QA	SPE / Valves Engg	DGM/QA	AGM / Valves Purchase	SDGM / QA
<b>Prepared By</b>		<b>Reviewed By</b>		<b>Approved By</b>	



BHEL – Tiruchirappalli - 620014, India.  
Quality Assurance Department  
TECHNICAL DELIVERY CONDITIONS

DOC No: TDC:5:164 Rev: 08  
Effective Date: 14/09/2019  
Page: 6 of 6

Product: CARBON & ALLOY STEEL FASTENERS (STUDS, BOLTS & NUTS) FOR VALVES, OIL FIELD EQUIPMENT (OFE) AND OTHER APPLICATIONS

**Annexure-1. Test certificate for Studs/Bolts & Nuts– Sample format**

TC No:	Date:
Customer :	PO No./ Amd :
TDC No./Rev.:	DC No. :
Product :	Drg. No./Rev :
Description : (Spec, dia, pitch, length)	Thread Spec. :
Quantity :	

<u>Requirement</u> :	<u>Records/ Observation</u>
Size of bar - Before machining :	
- After machining :	
Type of furnace used for hardening :	

<b>TDC Clause no.</b>	Raw Material mill TC No:	TC Date:
	Melt/Heat Number:	
2.0 & 3.0	<b>a) Heat Treatment Details:</b>	
	Hardening Temperature: °C; Soaking time: Cooling Medium:	Tempering Temperature: °C; Soaking time: Cooling Medium:
3.0	<b>b) Additional Tempering for Nuts (after final tempering):</b>	
	Temperature: °C; Soaking time: Cooling Medium:	
3.0	<b>a) Product analysis for chemistry</b>	
	<b>Report No &amp; Date:</b>	
	Spec	C Mn P S Si Cr Mo V Ni Others
	Min.	
	Max.	
	Actual	
	<b>b) Tensile test after H &amp; T and final drying (Finished heat treated condition) – For Studs/Bolts</b>	
		UTS (MPa) YS (MPa) %Elongation %Red in Area
	Reqd/Spec Value	
	Test result	
	Spec Value Test result Remarks	
	c) Hardness Test Result (for Studs/Bolts, Nuts):	
	d) Hardness Test Result (for Nuts after 24 hrs of tempering):	
	e) Proof load (kN) for nuts & result	
	f) Result of Cone Stripping test for nuts	
	g) NDE Result for Studs/Bolts:	
4.0	Visual and dimensional checking as per applicable drawing and ASME SA193 for studs/bolts & SA194 for nuts:	
5.0	Punching details (identification): End cap for threaded portion:	
6.0	<b>a) Type of coating:</b> Cadmium Plating /Chromate Conversion / Electroplating/ Xylan /Rust preventive coating <b>(Tick applicable coating)</b>	
	<b>Coating thickness/DFT:</b>	
	<b>b) Tests for Xylan Coating</b>	<b>Results</b>
	<b>c) Pickling Acid:</b>	<b>Concentration:</b>
	Drying after pickling. Temperature: °C; Soaking time:	
This is to certify that the above results are correct and the parts meet specification and PO requirements.		
Signature with date Supplier: In-charge of Quality		Signature with date BHEL / Authorized Inspection Agency

Note: Additional Sheets may be attached, if required.