

	<h1 style="margin: 0;">CORPORATE PURCHASING SPECIFICATION</h1>	<div style="border-bottom: 1px solid black; padding-bottom: 2px;">AA10119</div> <div style="border-bottom: 1px solid black; padding-bottom: 2px;">Rev No. 15</div> <div style="padding-bottom: 2px;">PAGE 1 of 2</div>																		
<h2 style="margin: 0;">STRUCTURAL STEEL - WELDABLE QUALITY</h2> <p style="margin: 0;">(PLATES, SECTIONS, STRIPS, FLATS AND BARS)</p> <h3 style="margin: 10px 0 0 0;">ORDERING DESCRIPTION</h3>																				
<p>1.0 GENERAL:</p> <p>The material shall conform to IS 2062 – 2011, E250-Gr.BR (with mandatory Impact Test) or DIN EN 10025-2:2005, Gr. S275JR and comply with following additional requirements.</p> <p>2.0 APPLICATION:</p> <p>For general engineering purposes, suitable for welding.</p> <p>3.0 CONDITION OF DELIVERY:</p> <p>3.1 Bars & Sections shall be supplied in Hot rolled in straight lengths without twists and bends.</p> <p>3.2 The material shall be supplied as per IS: 2062 – 2011, E250 Gr.BR (with mandatory Impact Test) or as per DIN EN 10025-2:2005 Gr. 275JR.</p> <p>3.3 Any other additional requirement as per BHEL Purchase order.</p> <p>4.0 DIMENSIONS AND TOLERANCES:</p> <p>4.1 Sizes:</p> <p>Material shall be supplied to the dimensions specified in BHEL Order.</p> <p>4.2 Tolerances:</p> <p>The tolerances on hot rolled material shall comply with IS: 1852 or any other equivalent national standard.</p> <p>4.3 Straightness for hot rolled bars:</p> <p>Unless otherwise specified, the permissible deviation in straightness shall not exceed 5 mm in any 1000 mm length.</p> <p>5.0 TEST SAMPLES:</p> <p>The selection of test pieces for all tests like Chemical, Mechanical etc. shall be as per IS: 2062, E250-Gr.BR or DIN EN 10025-2, Gr. S275JR.</p>																				
<table border="1" style="width: 100%; border-collapse: collapse;"> <tr> <td colspan="3" style="padding: 5px;"> Revisions: Clause No. 1, 3, 5 & 8 revised (as per MOM of 38th MRC meeting), Clause 10 added </td> <td colspan="3" style="text-align: center; padding: 5px;"> APPROVED: INTERPLANT MATERIAL RATIONALISATION COMMITTEE – MRC(S&GPS) </td> </tr> <tr> <td style="width: 20%; padding: 5px;">Rev No.15</td> <td style="width: 20%; padding: 5px;">Amd No.</td> <td style="width: 20%; padding: 5px;">Reaffirmed</td> <td style="width: 20%; padding: 5px;">Prepared</td> <td style="width: 20%; padding: 5px;">Issued</td> <td style="width: 20%; padding: 5px;">Dt. of 1st Issue</td> </tr> <tr> <td style="padding: 5px;">Dt:11-03-2014</td> <td style="padding: 5px;">Dt:</td> <td style="padding: 5px;">Year:</td> <td style="padding: 5px;">HPEP, Hyderabad</td> <td style="padding: 5px;">Corp.R&D</td> <td style="padding: 5px;">June, 1976</td> </tr> </table>			Revisions: Clause No. 1, 3, 5 & 8 revised (as per MOM of 38th MRC meeting), Clause 10 added			APPROVED: INTERPLANT MATERIAL RATIONALISATION COMMITTEE – MRC(S&GPS)			Rev No.15	Amd No.	Reaffirmed	Prepared	Issued	Dt. of 1 st Issue	Dt:11-03-2014	Dt:	Year:	HPEP, Hyderabad	Corp.R&D	June, 1976
Revisions: Clause No. 1, 3, 5 & 8 revised (as per MOM of 38th MRC meeting), Clause 10 added			APPROVED: INTERPLANT MATERIAL RATIONALISATION COMMITTEE – MRC(S&GPS)																	
Rev No.15	Amd No.	Reaffirmed	Prepared	Issued	Dt. of 1 st Issue															
Dt:11-03-2014	Dt:	Year:	HPEP, Hyderabad	Corp.R&D	June, 1976															

CORPORATE PURCHASING SPECIFICATION



6.0 ULTRASONIC EXAMINATION:

Plates shall be ultrasonically examined in accordance with BHEL standard AA0850120 (or ASTM-A435) as detailed below and shall comply with the acceptance standards specified therein.

6.1 For plates above 40 mm thick:

Shall be ultrasonically examined unless when otherwise specified in order.

7.0 TEST CERTIFICATES:

Unless otherwise specified, three copies of test certificates shall be supplied.

In addition, the supplier shall ensure to enclose one copy of the test certificate along with their dispatch documents to facilitate quick clearance of the material.

The test certificate shall bear the following information:

AA10119 - Rev.No.15/ IS: 2062-Gr: BR (with mandatory Impact test) or DIN EN 10025-2, Gr. S275JR,

BHEL order No.

Melt No, Size & Quantity, Batch No with heat treatment details, Results of Chemical analysis,

Mechanical tests & NDT, Supplier's name, Identification No, TC No, Signature of Competent Authority, etc.

8.0 PACKING AND MARKING:

Plates shall be transported suitably to avoid damage during transit.

Each plate shall be marked with Melt No. Material grade and specification, BHEL Order No, Supplier's Name Identification No, Size & weight, on any one corner and encircled with paint preferably of white colour.

9.0 REJECTION AND REPLACEMENT

If the material does not comply with the requirements of this specification during receipt inspection at BHEL or if any defect is found during further processing of material, BHEL reserves the right to reject the whole consignment and the supplier shall replace the material free of cost. The rejected material shall be taken back by the supplier after fulfilling the commercial terms and conditions.

10.0 REFERRED STANDARDS (Latest publications including amendments):

1) IS: 1852

2) ASTM - A435

3) AA0850120