

H F SUPER REFRACTORY CASTABLE RHF

HOT FACE SUPER REFRACTORY CASTBLE TO THE FOLLOWING SPECIFICATION :- AL2O3 % min
91.5 Fe2O3 % max 0.5 CCS Kg/sq.cm min @ 110 deg.C -
350 min @ 800 deg.C - 220 min @1550 deg.C - 260 SWT deg.C
min- 1800 PLC % - 1550 deg.C-+0.6 DRY DENSITY - KG/CUBIC MTR - 2800.