

HIGH ALUMINA CASTABLE RHF

HIGH ALUMINA CASTABLE AS PER THE FOLLOWING SPECIFICATION: Al₂O₃: % MIN 70 Fe₂O₃ : %
MAX 4 SWT : DEG.C MIN = 1550-1600 CCS : Kg/sq.cm MIN = AT 110 deg.c - 300 AT 1300
deg.c - 250 SINTERING TEMPERATURE : deg.c 1225-1250 BD : gm/cc MIN 2.2 to 2.3