

AIR SETTING CEMENT POWDER

AIR SETTING CEMENT POWDER SPECIFICATION: siO₂ % min :90 GRAIN SIZE :95% through 100 Mesh (0.8mm) CCS kgs/sq.centimetre min: 150 after setting 250-300 @1000 degree centigrade for 8hrs SINTERING TEMP.degree centigrade:600 RUL ta DEGREE CENTIGRADE min: 1250 (with 1kg/sq.centi metre load)