



TD-106-1 Rev No. 5 Form No.		PRODUCT STANDARD SWITCHGEAR HYDERABAD		Product STD NO.	SG 80063																																							
		Rev No 00																																										
		Page 1 of 4																																										
<u>Membrane Electrode Assembly (MEA)</u> <u>Material code: SG9780063013</u>																																												
<p>1. DESCRIPTION: Membrane electrode assembly (MEA) for high power fuel cell</p> <p>2. TECHNICAL DETAILS:</p>																																												
<table border="1"> <thead> <tr> <th>SL.NO.</th> <th>DESCRIPTION</th> <th>SPECIFICATIONS</th> </tr> </thead> <tbody> <tr> <td>1</td> <td>Members Electrode Assembly (MEA) as per drawing details</td> <td>MEAs will be supplied as per drawing. Gas diffusion layer centered: (181 X 259)mm</td> </tr> <tr> <td>2</td> <td>MEA thickness tolerance</td> <td>Total Avg. MEA thickness in μm : 550 +/-20, Membrane Avg. thickness in μm:17+/-1</td> </tr> <tr> <td>3</td> <td>Feed reactants stoichiometric ratios</td> <td>Hydrogen: 1.05 to 1.20, Proportional Stoic ratio of Air is : 1.8 to 2.25. MEA is operated at recommended Stoichiometric ratio.</td> </tr> <tr> <td>4</td> <td>Required Current density of 1 A/cm²-1.5 A/cm² at 0.65 VDC/Cell</td> <td> Operating conditions: <ol style="list-style-type: none"> 1. Operating tem.: 60° to 70° C 2. 0.5-1 bar at cathode, 0.5-1 bar at anode 3. Electrical conductivity of 50-55 S/cm 4. Dew point of : Air 45-55°C, Hydrogen 35-45° C 5. 60 wt% of DI water, 40 wt% of Ethylene glycol MEA operates at cell voltage of 0.65V at 1.1 A/cm² current density, from testing of Sample MEAs. </td> </tr> <tr> <td>5</td> <td>Operational stability</td> <td>More than 5000 hr.</td> </tr> <tr> <td>6</td> <td>Performance degradation rate in case of continuous operation</td> <td>Below 8-10mV/1000hr.</td> </tr> <tr> <td>7</td> <td>Electrolyte base material</td> <td>PFSA</td> </tr> <tr> <td>8</td> <td>Degradation rate for 5000 ON/OFF cycle over a period of 5000 hr. cumulative operation</td> <td>Below 10-12mV/1000 cycles</td> </tr> <tr> <td>9</td> <td>Reinforcement of Non active area of MEA</td> <td>Confirmed the reinforcement of Non active area of MEA</td> </tr> <tr> <td>10</td> <td>Differential pressure (DP) between anode and cathode</td> <td>Minimum differential pressure of 0.5 bar.</td> </tr> <tr> <td>11</td> <td>Low temperature stability</td> <td>Below 0 Deg. C</td> </tr> <tr> <td>12</td> <td>Thickness of Non-active area (1)</td> <td>< 85μm</td> </tr> </tbody> </table>						SL.NO.	DESCRIPTION	SPECIFICATIONS	1	Members Electrode Assembly (MEA) as per drawing details	MEAs will be supplied as per drawing. Gas diffusion layer centered: (181 X 259)mm	2	MEA thickness tolerance	Total Avg. MEA thickness in μm : 550 +/-20, Membrane Avg. thickness in μm :17+/-1	3	Feed reactants stoichiometric ratios	Hydrogen: 1.05 to 1.20, Proportional Stoic ratio of Air is : 1.8 to 2.25. MEA is operated at recommended Stoichiometric ratio.	4	Required Current density of 1 A/cm ² -1.5 A/cm ² at 0.65 VDC/Cell	Operating conditions: <ol style="list-style-type: none"> 1. Operating tem.: 60° to 70° C 2. 0.5-1 bar at cathode, 0.5-1 bar at anode 3. Electrical conductivity of 50-55 S/cm 4. Dew point of : Air 45-55°C, Hydrogen 35-45° C 5. 60 wt% of DI water, 40 wt% of Ethylene glycol MEA operates at cell voltage of 0.65V at 1.1 A/cm ² current density, from testing of Sample MEAs.	5	Operational stability	More than 5000 hr.	6	Performance degradation rate in case of continuous operation	Below 8-10mV/1000hr.	7	Electrolyte base material	PFSA	8	Degradation rate for 5000 ON/OFF cycle over a period of 5000 hr. cumulative operation	Below 10-12mV/1000 cycles	9	Reinforcement of Non active area of MEA	Confirmed the reinforcement of Non active area of MEA	10	Differential pressure (DP) between anode and cathode	Minimum differential pressure of 0.5 bar.	11	Low temperature stability	Below 0 Deg. C	12	Thickness of Non-active area (1)	< 85 μm
SL.NO.	DESCRIPTION	SPECIFICATIONS																																										
1	Members Electrode Assembly (MEA) as per drawing details	MEAs will be supplied as per drawing. Gas diffusion layer centered: (181 X 259)mm																																										
2	MEA thickness tolerance	Total Avg. MEA thickness in μm : 550 +/-20, Membrane Avg. thickness in μm :17+/-1																																										
3	Feed reactants stoichiometric ratios	Hydrogen: 1.05 to 1.20, Proportional Stoic ratio of Air is : 1.8 to 2.25. MEA is operated at recommended Stoichiometric ratio.																																										
4	Required Current density of 1 A/cm ² -1.5 A/cm ² at 0.65 VDC/Cell	Operating conditions: <ol style="list-style-type: none"> 1. Operating tem.: 60° to 70° C 2. 0.5-1 bar at cathode, 0.5-1 bar at anode 3. Electrical conductivity of 50-55 S/cm 4. Dew point of : Air 45-55°C, Hydrogen 35-45° C 5. 60 wt% of DI water, 40 wt% of Ethylene glycol MEA operates at cell voltage of 0.65V at 1.1 A/cm ² current density, from testing of Sample MEAs.																																										
5	Operational stability	More than 5000 hr.																																										
6	Performance degradation rate in case of continuous operation	Below 8-10mV/1000hr.																																										
7	Electrolyte base material	PFSA																																										
8	Degradation rate for 5000 ON/OFF cycle over a period of 5000 hr. cumulative operation	Below 10-12mV/1000 cycles																																										
9	Reinforcement of Non active area of MEA	Confirmed the reinforcement of Non active area of MEA																																										
10	Differential pressure (DP) between anode and cathode	Minimum differential pressure of 0.5 bar.																																										
11	Low temperature stability	Below 0 Deg. C																																										
12	Thickness of Non-active area (1)	< 85 μm																																										
COPYRIGHT AND CONFIDENTIAL The information on this document is the property of BHARAT HEAVY ELECTRICALS LIMITED, It must not be used directly or indirectly in any way detrimental to the interest of the company.																																												
Revisions: Refer to record of revisions:		Prepared: K. SANGEETHA	Approved: LVRK	Date: 20.06.2023																																								

TD-106-1 Rev No. 5	Form No.		PRODUCT STANDARD SWITCHGEAR HYDERABAD		Product STD NO.	SG 80063			
COPYRIGHT AND CONFIDENTIAL The information on this document is the property of BHARAT HEAVY ELECTRICALS LIMITED, It must not be used directly or indirectly in any way detrimental to the interest of the company.				<p>3. TEST CERTIFICATES:</p> <p>The following certificates shall be submitted by supplier</p> <ol style="list-style-type: none"> a) Duly signed manufacturers test certificate b) Country of origin on supplier's letter head in case of foreign vendor c) Guarantee Certificate <p>4. GUARANTEE CERTIFICATE:</p> <p>A guarantee certificate for 18 months of trouble free performance from the date of shipment or 12 months from the date of commissioning whichever is earlier shall be furnished.</p> <p>5. PACKING:</p> <ol style="list-style-type: none"> a) MEA shall be packed individually in a box. Such boxes shall be packed in a cardboard case with adequate cushioning material to withstand normal transit risks. b) The item shall be stored in a covered shed for long periods before installation. The packing shall be suitable for such storage. <p>6. MARKING:</p> <p>The following details shall be marked on the packing case.</p> <ol style="list-style-type: none"> a) Manufacturer's name or trade mark b) BHEL purchase order no. 			Rev No 00		
				Revisions: Refer to record of revisions:	Prepared: K. SANGEETHA	Approved: LVRK	Date: 20.06.2023		
						Page 2 of 4			

