

#### BHEL JHANSI SPECIFICATION OF LEATHER SHOES (NORMAL)

BHEL/HR/WLF/01 Rev. No.: 00

Page 1 of 2

### Black Leather Shoes (Normal)

#### 1.0 Scope

This standard covers the requirement of Leather shoe (Normal) with PU DIP sole for protection of feet.

#### 2.0 Technical Requirement

- 1. The shoe upper and bottom sole shall be joined together by direct injection process.
- 2. Upper leather shall be of good quality Cow/Buffalo softy leather in black colour.
- 3. The shoe shall be provided with lasting inner sole.
- 4. The Eye lets shall be of Brass/ Aluminum and shall be 4/5 pairs.
- 5. The shoes are to be machine stitched and no nails shall be used.
- 6. Total weight shall be approximately 900 Grams per pair.
- 7. Laces shall be round in shape and slip knot Resistant.
- 8. Shoe size shall be as per "BATA" standard.

#### 3.0 Sample

Alongwith offer, sample and conformance certificate as per specification no. BHEL/HR/WLF/01, (Clause no-4.1) shall be submitted. Maximum three samples can be submitted alongwith offer by each bidder. Each sample shall have a permanent non-removable hanging type tag of maximum size 2"X2" with the following details.

- 1. Tender Enquiry No.:
- 2. Article/Model no.
- 3. Name of tenderer.
- 4. Signature along with name.

#### 4.0 Test Certificate

4.1 Supplier shall submit sample with conformance certificate along with the offer as per the following technical parameters (clause no-4.1) Test certificate shall be submitted alongwith bulk supply after carrying out test as per the following technical parameter on each lot of supply against BHEL order.

Technical Parameters

Type of test	Required value
1. Sh	noe upper (Leather)
(a) Tear Strength Test Based on IS 15298 (Part-2) 2002	Minimum - 120 Newton
(b) Balley Flexing Test Based on SATRA TM 55	No Damage/Crack till 1,00,000 Cycles.
<u>2. So</u>	ie PU (DIP)
(a) Bennewart Flexing Test As per IS 15298 (Part-2) 2002	Cut growth not more than 4 mm before 30,000 Cycles
(b) Aberration Resistance Test	Maximum 250 mm <sup>3</sup>
(c) Peel strength test between upper and sole. Based on SATRA TM 411	Minimum 4 Newton/mm
7 - (	

- 4.2 Test Certificate submitted along with supply shall indicate the following.
  - (a) BHEL Purchase Order No.
  - (b) Batch no & date
  - (c) Type of test, its required and observed values as per technical parameter (clause 4.1)

#### 5.0 Packing

Each pair of shoes shall be packed in a card board box and one polythene carrying bag is required for each pair of shoe.

#### 6.0 Marking

# The shoe shall be marked with the following information

- (a) Size of the shoe on sole and shoe socks.
- (b) MRP on shoe socks.
- (c) Suppliers identity
- (d) Article no/Model no
- (e) Month/Year of the manufacturing /Size on cardboard box.

## 7.0 BHEL Inspection

Final inspection will also be carried out at our works with reference to the approved sample and test report submitted alongwith supply and as per purchase order. BHEL Jhansi may inspect at manufacturer's work at its discretion with reference to the approved sample, technical parameters and as per Purchase Order. The supplier shall give inspection call before dispatch of shoe.

## 8.0 Gaurantee Certificate

Six months free replacement guarantee certificate shall be given for manufacturing defects along with its consignment from the date of receipt at BHEL.