

Technical Specifications

SL. No	Description and Technical Specification of the item	QTY	UNIT	Delivery
1	<p>SMAW ELECTRODE DIA 3.2/3.15 MM T92/P92</p> <p>SMAW ELECTRODE FOR SA213T92 AND SA335P92 WELDING SIZE DIAMETER 3.15/3.2 MM AND LENGTH 350 TO 450MM as per Technical Annexure 1. Creep data is required along with supply.</p>	500.00	KG	120 DAYS
2	<p>SMAW ELECTRODE DIA 4.0 MM for T92/P92</p> <p>SMAW ELECTRODE FOR SA213T92 AND SA335P92 WELDING SIZE DIAMETER 4 MM AND LENGTH 350 TO 450MM as per Technical Annexure 1. Creep data is required along with supply.</p>	6,000.00	KG	120 DAYS

Technical Annexure 1

ALLOY 92 ELECTRODE FOR SHIELDED METAL ARC WELDING E9015-B92.
DIAMETER 2.5mm/2.4mm.
LENGTH 300mm/350mm.

Mention the diameter and length of electrode, brand name of electrode in the technical offer.

1- CHEMICAL COMPOSITION

The Chemical composition of as deposited weld metal chemistry shall conform to the requirements of ASME SFA-5.5 and the additional restrictions as denoted below.

C(0.08-0.13%),
Mn(0.35-1.20%),
P(0.01% maximum),
S(0.01% maximum),
Si(0.15-0.30%),
Cr(8.5-10.0%),
Mo(0.30-0.60%),
W(1.50-2.00%),
Cu(0.25% maximum),
Ni(0.60% maximum),
V(0.15-0.30%),
Nb(0.02-0.05%),
N(0.04-0.07%),
Al(0.015% maximum),
B(0.002-0.006%),
Ti(0.01% maximum),
Zr(0.01% maximum).

Sn+Sb+As to be equal or less than 250 PPM and Single Element(Sn/Sb/As) value to be equal or less than 120 ppm.

Ni+Mn to be equal or less than 1.2%

When Nitrogen (N) is supplied below 0.04 the following equation shall be satisfied: N to be equal or more than $(0.52 \cdot Al + 0.032)$

The test certificate shall contain the following results after actual tests done. Actual Chemical Composition of "As Deposited Weld Metal" meeting the chemical composition as above.

R Arivazhagan
R. ARIVAZHAGAN
Senior Manager
Welding Technology Centre
BHEL, TRICHY - 620 014

Page 1 of 3

Aditya Kumar
ADITYA KUMAR
Deputy Manager
Welding Technology Centre
BHEL, Trichy - 620014.

Technical Annexure 1

2- Mechanical Test

Following Guaranteed Mechanical Properties for Weld Metal after PWHT 760°C ±10°C (degree Celsius) for 2 hours.

- a) Tensile Strength: 620MPa (minimum),
- b) Yield Strength: 530 MPa (minimum),
- c) % Elongation: 17%,
- d) Impact energy at +20 degree Celsius: 40J (minimum).
- e) Actual Hardness of weld metal (202 HV to 320 HV).

3- COVERING:

The core wire and covering shall be free of defects and shall ensure uniform deposition of weld metal. The flux coating shall be uniform and concentric around the core wire such that the performance of welding is not affected and no tapered burning of electrode is permitted. Covering shall not exhibit any cracking during welding at maximum current recommended by manufacturer. The electrode shall not become red hot upon continuous welding through the length of electrode.

4- CORE WIRE, COVERING, EXPOSED CORE, IDENTIFICATION,

Electrodes shall meet the requirements of clause 3.2 ,3.3 and 3.4 of SFA-5.02.

5- PACKAGING:

- 5.1 A standard quantity of electrodes with the net weight of each package not exceeding 5Kg shall be packed in hermetically sealed containers or moisture proof cardboard with polythene encapsulated packets.
- 5.2 Electrode packets shall be shipped in wooden crates lined with waterproof material. Net weight of each crate shall not exceed 1000Kg.
- 5.3 Marking of packages shall be as per clause 3.6 of SFA-5.02
- 5.4 The package shall be marked clearly with brand name, classifications, lot number/batch number, Manufacturer Name, Size and Quantity of electrode with net weight, health and safety warnings


ADITYA KUMAR
Deputy Manager
Welding Technology Centre
BHEL, Trichy - 620014.

Page 2 of 3


R. ARIVAZHAGAN
Senior Manager
Welding Technology Centre
BHEL, TRICHY - 620 014

Technical Annexure 1

6- Diffusible hydrogen

The diffusible hydrogen test shall be performed as prescribed by SFA-5.5/SFA-5.5M. The electrode shall be certified as meeting the requirement for the H4 diffusible hydrogen designator.

7- Testing and Certification:

7.1 Batch or Lot classification shall be Class C5 of SFA-5.01 Filler metal procurement guidelines of ASME Sec.II. Part C

7.2 The level of testing shall be Schedule K of SFA 5.01 Filler metal procurement guidelines of ASME Sec.II. Part -C.

7.3 Original certified material test report in English signed by the manufacturer giving details of test done in compliance with additional specific requirement as per Technical Annexure 1 and ASME Sec.II.C, SFA-5.5, E9015-B92 shall also be complied.

7.4 The testing authority(manufacturer) shall certify that supplies made against the Batch confirms to the requirements of the Latest Edition and Addenda (Applicable on the date of issue of purchase order) of ASME Sec II C, SFA-5.5, E9015-B92.

7.5 "A copy of valid IBR Approval Certificate for the brand being supplied to be submitted along with supply. It is mandatory that, Manufacturer should possess a valid IBR certificate (for the brand being supplied) during the manufacturing period".

OR

"Original test certificates in English countersigned by Inspecting Authority (latest) approved by IBR for country of origin giving details of the tests done in compliance with additional specific requirement as per Technical Annexure 1 and ASME Sec.II.C, SFA-5.5, E9015-B92 shall be sent".

Special Note: Creep Stress Rupture Testing Details is required along with supply.

Creep (Creep Stress Rupture Testing) data shall be provided for the following condition

Testing Hours (Minimum) = 1000 Hours.

Testing Temperature (°C) = 665 °C

Minimum Rupture Stress (MPa) = 93 MPa

Page 3 of 3


ADITYA KUMAR
Deputy Manager
Welding Technology Centre
BHEL, Trichy - 620014.


R. ARIVAZHAGAN
Senior Manager
Welding Technology Centre
BHEL, TRICHY - 620 014

Sl. No.	Pre -Qualification Criteria (134619728)	Bidder remark
1	If Bidder is a manufacturer, Confirm "Yes or, No" in bidder remark.	
2	Bidder shall be a manufacturer of the Quoted items or an authorized dealer of the same. If the offer is quoted by agent, letter of authorization or agreement duly signed by the manufacturer is required to consider the offer. Tender Enquiry details must available on Letter of authorization or agreement to consider the offer.	
3	Quoted Welding Consumables Brand Name/Product Name	
4	Quoted Product Catalogue	
5	Manufacturing Plant Address / Mill Address	
6	Manufacturer/Bidder shall submit manufacturing process flow chart (Raw material to finished product) along with offer for Quoted Item.	
7	Manufacturer/Bidder shall submit a valid ISO 9001 certificate or Quality management system certificate or Written down procedure for ISO 9001 or A valid ISO 45001 certificate or Written down procedure for Quality inspection.	
8	Manufacturing Plant capacity for SMAW E9015-B92 electrode.	

Seal and Sign of Authorized Person

ad, h
KADITYA KUMAR
 Deputy Manager
 Welding Technology Centre
 BHEL, Trichy - 620014.

R. Arivazhagan
R. ARIVAZHAGAN
 Senior Manager
 Welding Technology Centre
 BHEL, TRICHY - 620 014

Sl. No.	Pre –Qualification Criteria (134619728)	Bidder remark						
9	Bidder should confirm and full fill the Technical Annexure 1. Any deviation from the Specification are to be mentioned in the "Bidder remark Space". If There is no deviation vendor should indicate "No Deviation".							
10	Seal and sign on Technical Annexure 1 for confirmation.							
11	Technical Annexure 1 (E9015-B92) Diameter details and Length details							
12	Creep (Creep Stress Rupture Testing) data shall be provided for the quoted SMAW Welding Consumables for the following condition- <table border="1" data-bbox="260 1064 1066 1160"> <thead> <tr> <th>Testing Hours (Minimum)</th> <th>Testing Temp (°C)</th> <th>Minimum Rupture Stress (MPa)</th> </tr> </thead> <tbody> <tr> <td>1000</td> <td>665</td> <td>93</td> </tr> </tbody> </table> <p>Note: Creep Stress Rupture Testing Details is required along with supply</p>	Testing Hours (Minimum)	Testing Temp (°C)	Minimum Rupture Stress (MPa)	1000	665	93	
Testing Hours (Minimum)	Testing Temp (°C)	Minimum Rupture Stress (MPa)						
1000	665	93						
13	IBR certificate status to be provided for E9015-B92							
14	Manufacturer Name (For quoted item)							
15	Manufacturer shall have successful experience for supplying of E9015-B92 / E9015-B91 to any govt. Organizations/ PSUs/ Public Ltd./ Company/Reputed Industries etc. Purchase orders copies/ related documents to be submitted along with offer to consider the offer. Note: Successful experience means – supplied and accepted.							

Seal and Sign of Authorized Person

Aditya Kumar
ADITYA KUMAR
Deputy Manager
Welding Technology Centre
BHEL, Trichy - 620014.

R. Arivazhagan
R. ARIVAZHAGAN
Senior Manager
Welding Technology Centre
BHEL, TRICHY - 620 014

Sl. No.	Pre-Qualification Criteria (134619728)	Bidder remark
16	<p>Self-declaration from Manufacturer Supplier (As per PQC 14) is required against PQC Sl. No. 15 for "successfully supplied and accepted by customer".</p> <p>Self-declaration shall have following details.</p> <ol style="list-style-type: none"> 1- Supplied quantity. 2- PO /related document Reference 3- Brand Name. 	
17	<p>"A copy of valid IBR Approval Certificate for the brand being supplied to be submitted along with supply. It is mandatory that, Manufacturer should possess a valid IBR certificate (for the brand being supplied) during the manufacturing period".</p> <p style="text-align: center;">OR</p> <p>"Original test certificates in English countersigned by Inspecting Authority (latest) approved by IBR for country of origin giving details of the tests done in compliance with additional specific requirement as per Technical Annexure 1 and ASME Sec.II.C, SFA-5.5, E9015-B92 shall be sent".</p>	
18	<p>Creep data status to be provided for quoted brand.</p> <p>Note:</p> <ol style="list-style-type: none"> 1- Creep Stress Rupture Testing Details is required along with supply. 2- Creep (Creep Stress Rupture Testing) data shall be provided for the following condition <ul style="list-style-type: none"> • Testing Hours (Minimum) = 1000 Hours. • Testing Temperature (°C) = 665 °C • Minimum Rupture Stress (MPa) = 93 MPa 	

Seal and Sign of Authorized Person

Aravazhagan
R. ARVAZHAGAN
Senior Manager
Welding Technology Centre
BHEL, TRICHY - 620 014

Aditya Kumar
ADITYA KUMAR
Deputy Manager
Welding Technology Centre
BHEL, Trichy - 620014.

Annexure – A- Additional Terms and Conditions for GeM Enquiry

The terms and condition mentioned in this document are applicable in addition to the GeM General Terms and Conditions. Bidders shall furnish pointwise confirmation/details.

<i>To be filled by bidder</i>		
Description of the Equipment:		
GeM Tender No. & Date		
Name of the firm (Bidder)		:
Address		:
Contact person 1		Contact person 2
Name:		Name:
Designation:		Designation:
Office Phone:		Office Phone:
Mobile:		Mobile:
e-mail:		e-mail:
Offer/Quotation reference with date		:
Sl	Terms and conditions	Vendor's confirmation
1.	Inspection by BHEL/as per Technical specification(if any).	
2.	<p>Payment terms:</p> <ol style="list-style-type: none"> 1. Payment terms for Non MSME Suppliers: Within 90 days after CRAC 2. Payment terms for Micro & Small Enterprises (MSEs): Within 45 days after CRAC. The supplier should upload UDYAM Registration Certificate in proof of MSE. 3. Payment terms for Medium Enterprises: Within 60 days after CRAC. The supplier should upload UDYAM Registration Certificate in proof of Medium Enterprises. <p>Note: Deviation in above payment terms is not acceptable. In case of Auto PRC/CRAC, Payment due date shall be calculated from CRAC date or material acceptance date by BHEL whichever is later.</p>	
3.	Response to Tenders for Indigenous supplier will be entertained only if the vendor has a valid GST registration number which should clearly mentioned in the offer. Indicate the GST registration number. If any specific exemption is available, a declaration with due supporting documents need to be furnished for considering the offer.	GST Registration No. _____
4.	Performance Bank Guarantee: Not Applicable	
5.	Kindly Indicate the HSN Code for all items	HSN CODE : _____
6.	Rate quoted in GeM portal should be on FOR destination basis inclusive of all taxes, P&F, freight etc. Transit Insurance is under Supplier scope. Please indicate how much GST percentage is included in quoted price.	GST in %: _____

Vendor's Seal & Signature

/ On Bidder's office letter pad /

Self-Declaration

Enquiry No.	
Enquiry Date	

In line with Government public procurement order Number P-45021/2/2017-B.E-II dated 15.06.2017, and further modified order dt. 28.05.2018, 29.05.2019 & order 04.06.2020 issued by DPIIT

I / We hereby declare that I / We are a "Local Supplier" meeting the requirement of minimum local content (..... %) defined in the above government notification for the goods against above mentioned enquiry Number.

Details of location at which local value addition will be made is as follows:

Door No.	
Street / Address 1	
Street / Address 2	
District	
State	
Country	
PIN Code	

We also understand that the false declarations will be in breach of the code of Integrity under rule 175(1)(i)(h) of the General financial rules for which a bidder or its successors can be debarred for up to two years as per Rule 151(iii) of the General Financial Rules along with such other actions as may be permissible under law.

For Company Name:

Seal:

Signature:

Date:

Place:

Note:

" Local Content "means the amount of value added in India which shall ,unless otherwise prescribed by the Nodal Ministry, be the total value of the item procured(excluding net domestic indirect taxes) minus the value of imported content in the item(including all customs duties) as a proportion of the total value, in percent. "Local Supplier "means a supplier or service provider whose product or service offered for procurement meets the minimum local content.

The above declaration shall be submitted mandatorily along with the offer in company letter head with seal & signature.

(Please fill all the yellow color field)