




	<b>Technical Delivery Condition (TDC)</b> for <b>Cold rolled carbon sheet coils</b>	Doc Ref:	TDC:RTA:408
		Rev .No.	04
		Date:	23.09.2024
		Page No	1 of 4

## TECHNICAL DELIVERY CONDITIONS FOR COLD ROLLED CARBON SHEET COILS


### PREPARED BY:


DEPARTMENT	NAME & DESIGNATION S/Shri	SIGNATURE
QA	Ranjith .K / s.m	

### REVIEWED BY:

DEPARTMENT	NAME & DESIGNATION S/Shri	SIGNATURE
ENGG (APH)	V. PRADEEP KUMAR	
MATERIAL PLANNING	SHYAM SUNDAR.V.P	
QC (PROCUREMENT)	ZEEESHAN ALI	
QUALITY	D. ARAVINDHAN/DGM	

### APPROVED AND ISSUED BY:

DEPARTMENT	NAME & DESIGNATION S/Shri	SIGNATURE
QUALITY & BE	K.SAKETHARAMAN AGM / Q&BE	

	<b>Technical Delivery Condition (TDC)</b> <b>for</b> <b>Cold rolled carbon sheet coils</b>	<b>Doc Ref:</b>	<b>TDC:RTA:408</b>
		<b>Rev .No.</b>	<b>04</b>
		<b>Date:</b>	<b>23.09.2024</b>
		<b>Page No</b>	<b>2 of 4</b>

## 1.0 SCOPE

- 1.1 This TDC specifies the requirements for cold rolled sheets of deep drawing quality to specification IS 513 GR-CR3 / JIS G 3141 SPCE-SD.

## 2.0 CHEMICAL & MECHANICAL PROPERTIES

### 2.1 IS 513

1. Chemistry and Bend test shall be as per IS 513.
2. Erich son cupping value shall be as per Figure 1 of IS 513.
3. Tensile, Yield and Elongation as per IS 513
4. Hardness shall be 57 HRB Max as per JIS G3141

### 2.2 JIS G3141


1. Chemistry shall be as per material specification (JIS G 3141)
2. Hardness shall be 57 HRB MAX
3. Bendability shall be as per material specification (JIS G 3141)
4. Erich son cupping test shall be conducted and the value shall be as per Figure 1 of IS 513.

## 3.0 SUPPLY CONDITION

- 3.1 The coils shall be free from slit edges, visual scales and rust etc.
- 3.2 The tolerance thickness and width shall be as follows:  
On width : Plus 0.00 to Minus 1.5 mm.  
On thickness : Plus 0.07 mm to Minus 0.00 mm
- 3.3 The camber, out of flatness, bend shall be permitted only to the extent specified in the applicable standard.
- 3.4 The ID of the coil shall be 500 mm  $\pm$  20 mm, OD of the coil shall be 1400 mm (max) and coil weight 5 to 10 MT.
- 3.5 **Surface condition**
  - 3.5.1 Cold rolled with matt finish with an oil coat to protect rusting. When ordered as per the Japanese standard, it shall be SPCE-SD that is, skin rolled-dull finished by roll whose surface is made rough mechanically or chemically.

## 4.0 PACKING

- 4.1 Before packing, the coils shall be given a sufficient coat of rust preventive fluid on the outer part to prevent rusting.
- 4.2 Three binding strips through eye of the coil at equal spacing shall tightly be secured.

	<b>Technical Delivery Condition (TDC)</b> <b>for</b> <b>Cold rolled carbon sheet coils</b>	<b>Doc Ref:</b>	<b>TDC:RTA:408</b>
		<b>Rev .No.</b>	<b>04</b>
		<b>Date:</b>	<b>23.09.2024</b>
		<b>Page No</b>	<b>3 of 4</b>


- 4.3 Polythene sheet (thickness more than 20 microns) shall be wrapped over the coil. Subsequently coil shall be wrapped with Hessian cloth.
- 4.4 ID rings shall be provided at both the sides of the coil to protect the coil edges.
- 4.5 Entire circumference of the coil shall be covered with GI sheet / painted sheet. Subsequently, both the faces shall be protected with metal sheets i.e full coil is to be covered.
- 4.6 Three cross strapping shall be tightly secured through the ID of the coil at equal spacing.
- 4.7 Two more strapping along the periphery shall be provided ensuring tight strapping. The outer label containing details as in 5.1 shall be pasted on the packed OD of the coil.
- 4.8 A metal label containing the detail as in 5.1 shall be secured at once of the outer cross strapping.

## 5.0 IDENTIFICATION

- 5.1 The following details shall be ensured in outer label pasted on the ID of the coil.
  - a. Vendors Name
  - b. Purchase Order Number
  - c. Coil Number
  - d. Specification & Grade
  - e. Net Weight
- 5.2 Two more labels containing all the details as in 5.1, shall be pasted, one on the eye and another on the outer surface of the packed coil.

## 6.0 TEST CERTIFICATE

- 6.1 The TC shall be in English and containing the following details
  - i. Purchase Order Number
  - ii. Specification and Grade
  - iii. Coil Number
  - iv. Nominal thickness and width
  - v. Chemical composition – melt wise.
  - vi. Bend test result
  - vii. Max. camber
  - viii. Gross and net weight
  - ix. Hardness and Erichson cupping values
  - x. Tensile, Yield and elongation – melt wise
  - xi. Surface finish
- 6.2 BHEL reserves the right to carry out tests and reject the item wherever non-conforming to the requirement of Purchase Order and Technical Delivery Condition.

	<b>Technical Delivery Condition (TDC) for Cold rolled carbon sheet coils</b>	<b>Doc Ref:</b>	<b>TDC:RTA:408</b>
		<b>Rev .No.</b>	<b>04</b>
		<b>Date:</b>	<b>23.09.2024</b>
		<b>Page No</b>	<b>4 of 4</b>

### RECORD OF REVISIONS

Rev No	Date	Revision details
00	26.02.1996	TDC RTA 008 REV 04 revised and renumbered as TDC RTA 408/REV/00.
01	29.11.2002	Clause 4.0 and Clause 4.1 revised to change tolerance on thickness plus 0.00 to plus 0.015 mm.
02	10.05.2002	TDC totally reviewed and revised.
03	27.04.2021	IS 513 GR.DD terminology based on obsolete standard is revised as IS 513 GR-CR3 based on latest revision. MOM dated 24.04.2021 (Meeting with Engineering, M&S, Purchase, Material Planning, Marketing, QA and QC- Procurement) recommends the above.
04	23.09.2024	<p>Incorporated the changes in Amendment A1 in TDC clause no. 1.1, 2.1 (JIS 3141, sl. No. 1, sl. No. 3), 3.5.1 – changes made based on feedback from QC – Procurement. and Clause No. 3.4 (OD of the coil changed from 1500 mm (max) to 1400 (max) based on feedback from OP&amp;C and M&amp;S vide email dated 10.04.2023</p> <p><b>Changes in Rev. 04 as below:</b>  Mechanical properties (Tensile, Yield and elongation) included in Clause no. (2.1, Sl. No. 5) and Clause no. 6.1 (Sl. No. x) based on NTPC Quality plan requirements.</p> <p>TDC Clause no. 2.1 (Sl. No. 4) – Hardness value in line with JIS G3141 included as the same is not specified in IS 513 standards.</p> <p>Tolerance on thickness (Clause no. 3.2) updated from plus 0.00 mm to minus 0.00 mm for better clarity.</p> <p>TDC clause no. 6.1 (xi) – Surface finish included.</p>

**Issued By Quality Assurance**