

Enquiry items along with quantities:

It. No.	Size & Item description	Technical requirement	Quantity in kg
1	63mm dia X 3000mm – 6000 mm LG	1.5% Ni-Cr-Mo, Hot Rolled, Hardened and tempered steel round bars to material specification AA10501 Rev14. Original material test certificate covering all the chemical and mechanical properties as per BHEL spec AA10501 Rev14 shall be furnished along with supply. Inspection at source by BHEL or BHEL appointed third party shall be done as per QAP No.-QAP/TSD/FMS/10501 only. All other details as per spec. AA10501 Rev-14.	11000
2	80mm dia X 3000mm – 6000 mm LG		19800
TOTAL			30800 kg

Quantity variation as per below:

Item-1, Supplies quantity are to be restricted between 11000 kg & 9000 kg.

Item-2, Supplies quantity are to be restricted between 19800 kg & 16200 kg.

Pre-qualification criteria:

Sl. No.	Description of pre-qualification requirement	Vendor Response	
		Complied (YES / NO)	Supporting Documents required to accept compliance
1	Manufacturer or their authorized dealer/distributor of steel products like-Round bar/ Square bar/Flat.		Certificate of being manufacturer (for manufacturer). Authorized representative has to submit valid authorization letter from original manufacturer. Original manufacturer name, address, email and contact no. from whom material is intended to be supplied to be furnished.
2	Offers of those parties will be considered who or their Manufacturer has supplied “Steel Bar/ Steel Flat/ Steel Forgings” of minimum value INR 11.14 Lakh (Rs. ELEVEN LAKH & FOURTEEN THOUSAND only) during 05 (FIVE) years from the date of tender opening. The relevant documents as a proof of supply (Invoice copy/ completion certificate etc.) to be submitted with technical offer.		The relevant PO copies along with proof of supply (Invoice copy with value / GEM CRAC/ Completion certificate / Test Certificate) to be submitted with technical offer.
3	Company shall be certified with ISO 9001 or equivalent. In case of authorized representative, Valid ISO certificate of manufacturer is required.		Valid certificate to be submitted.
4	Startups and Micro & Small Enterprises (Manufacturer of quoted item as per Sl no.-2 of PQC) are exempted for submission of PO and proof of supply of prior experience.		

Note: -

1. BHEL has right to verify information / confirmation furnished by asking additional documents, proof etc.

ALL THE ABOVE POINT WISE PRE-QUALIFICATION REQUIREMENT ARE TO BE NECESSARILY ACCEPTED BY THE BIDDERS FOR THEIR OFFERS TO BE CONSIDERED FAILING WHICH OFFERS SHALL BE REJECTED.

MAKE IN INDIA format (to be filled by OeMs of the participating bidders)

BHARAT HEAVY ELECTRICALS LIMITED, BHOPAL

MATERIAL MANAGEMENT – STEEL DIVISION

For this Procurement, Government of India Public Procurement (Preference to Make in India), Order 2017 with its amendments and subsequent Orders issued by the respective nodal ministries shall be applicable even if issued after issue of this NIT but before finalization of contract/PO/WO against this NIT.

*As per the Provisions of this order, please submit **a self-certification complying with the conditions below on company letterhead duly signed by competent authority.***

I, hereby declare on behalf of M/s. that we are participating in the Enquiry No. floated by BHEL, Bhopal (MP), India and shall comply with following:

1. Public Procurement (Preference to Make in India), Order 2017 *with its amendments* and subsequent Orders issued by the respective nodal ministries shall be applicable even if issued after issue of this NIT but before finalization of contract/PO/WO against this NIT.

- (a) A supplier will be treated as **Class-I Local Suppliers**, if the items quoted by bidder have local content equal to or more than 50%.
- (b) '**Local Content**' means the amount of value added in India, which shall be total value of item quoted (excluding net domestic indirect taxes) minus the value of imported content in the item (including all custom duties) as a proportion of the total value, **in percent**.

2. I hereby declare that our firm qualifies as **Class-I Local Suppliers**.

a. The Local Content in the items quoted under this Enquiry is Percent

b. Details of location(s) in India where this value addition shall be done, is/are as follows:

- (a)
- (b)
- (c)

(.....)

For M/s.

(Seal & Sign)

Annexure-1

DECLARATION (To be given by Bidder)

GeM Bid No.....

Item Description:

With reference to above reference bid, we M/s..... (Bidder's Name)
confirm/declare the following.

1. Quoted Make-.....
2. We are OEM or Reseller -
3. Valid OEM Authorization certificate with OEM's Contact Details attached (In case of reseller)
- Yes / NA
4. We confirm Nil deviation from GeM bid document (NIT).

Note:

1. OEM details such as name, designation, address, e-mail Id and Phone number required to be furnished along with the technical bid. (also refer ATC clause).
2. Commercial Deviation/deviation in delivery shown separately or found hidden in the offer, will not be taken cognizance of.

(Vendor's Seal & Sign)

386049/2024/HEP-CRX34500

STANDARD QUALITY PLAN

QAP NO:		QAP/TSD/FMS/10501		REV.00	Date: 02/01/2018					
CUSTOMER:		BHEL BHOPAL			VENDOR NAME:					
DESCRIPTION MATERIALS:		1.5% Ni-Cr-Mo HOT ROLLED/ FORGED STEEL BARS - H&T								
SPECIFICATION		AA10501		Rev. No.	14					
P.I./ENQ.NO. /P.O. NO.				Date:						
Sr. No.	Characteristics	Class	Quantum of check	Reference Document	Acceptance Norm	Type of record	Inspection Agency			Remarks
							P	W	V	
01	Chemical composition	Maj	Each melt	AA 10501	As per spec	TC	2	1	-	
02	Grain Size	Maj	Each melt	ASTM E112	ASTM E112	TC	2	-	1	
03	Nonmetallic Inclusion	Maj	Each melt	ASTM E45 Method A	ASTM E45 method A	TC	2	-	1	
04	Macro	Maj	Each melt	ASTM E381	ASTM E381	TC	2	-	1	
05	Visual Examination	Maj	100% of each lot/Melt	AA 10501	Free From surface defect & shall be smooth	TC	2	1	-	10% Witness by TPIA
06	Dimensional Inspection	Maj	10% of each lot/Melt	AA 10501	As per Spec	TC	2	1	-	
07	Heat Treatment	Maj	100% of each lot/Melt	AA 10501	As per spec	TC	2	-	1	HT Charts review per batch each melt
08	Identification of test sample	Maj	10% of each lot/Melt	AA 10501	As per spec	TC	2	1	-	As per Sample Requirement
09	Ultrasonic Test	Maj	100% of Bars	ASTM A388/BHEL Spec (Dia. 40 mm above)	As per spec	TC	2	1	-	
10	Mechanical properties (Tensile strength, Yield, Elongation hardness etc.)	Maj	Each Heat	AA 10501	As per spec	TC	2	1	-	Random Sample as per Spec.
11	Stamping & Marking	Maj	100% of Bars	AA 10501	As per spec		2	-	1	
12	Documentation: TC & Inspection Report	Maj	Verification	AA10501	As per spec		2	-	1	TC & Reports Endorsed by TPIA

STANDARD QUALITY PLAN

Legends: Maj = Major, V= Verification, P=Perform, W=Witness, TC= Test Certificate. 1=BHEL/BHEL appointed TPIA, 2= Vendor/Sub/Vendor

Prepared By

Anand K

~~Checked By~~

Approved By

21/11/24
जी. एस. नेताम / G.S. NETAM
उप प्रबंधक (त.से.) / Dy. Manager (T.S.)
तकनीकी सेवा विभाग / Tech. Services Deptt.
बी.एच.ई.एल., भोपाल / BHEL, BHOPAL

386015/2024/HEP-CRX34500



CORPORATE PURCHASING SPECIFICATION

AA10501

Rev No. 14

PAGE 1 of 4

1.5% NICKEL-CHROMIUM-MOLYBDENUM HOT ROLLED/FORGED STEEL BARS- H & T

1.0 GENERAL:

This specification governs the quality requirements of 1.5% Nickel-Chromium-Molybdenum Hot rolled/forged Steel Bars, Gr: 40Ni6Cr4Mo3 in Hardened and Tempered condition.

2.0 APPLICATION:

For the manufacture of bolts, studs and various components of machines.

3.0 CONDITION OF DELIVERY:

Hot Rolled / Forged; Hardened and tempered.

Note: Sizes up to 100mm in hot rolled
>100 to 180mm in hot rolled or forged
above 180mm in forged

The ends of bars shall be reasonably square and true.

The bars shall be supplied in straight lengths without twists and bends.

4.0 COMPLIANCE WITH NATIONAL STANDARDS:

The material shall comply with the requirements of the following National standard and also meet the requirements of this specification.

IS: 5517 – 1993 Gr: 40Ni6Cr4Mo3, Type: J
Hardened & Tempered

Steels for Hardening and Tempering -
Specification

5.0 DIMENSIONS AND TOLERANCES:

5.1 Sizes: Bars shall be supplied to the dimensions specified on the order.

5.1.1 Length: Unless otherwise specified, hot rolled bars shall be supplied in 3 to 6 metres length or in multiples with maximum 10%, shorts down to 1 metre.

Forged bars shall be supplied in lengths of 1.5 to 3.0 metres

Revisions:

Revised as per email dt 18.12.08 from Shri
Gopal Bhatt from Bhopal.

APPROVED:

INTERPLANT MATERIAL RATIONALISATION
COMMITTEE – MRC(S&GPS)

Rev No.14

Amd No.

Reaffirmed

Prepared

Issued

Dt. of 1st Issue

Dt:18-12-2008

Dt:

Year:2014

HEP, Bhopal

Corp.R&D

April, 1977

386015/2024/HEP-CRX34500

AA10501	CORPORATE PURCHASING SPECIFICATION	
Rev No. 14		
PAGE 2 of 4		

5.2 Tolerance:

5.2.1 Hot rolled bars: The bars shall not vary from specified diameter or distance across flats by more than $\pm 2\frac{1}{2}$ %.

5.2.2 Forged bars: The tolerance on the forged bars shall be as follows.

<u>Diameter, mm</u>	<u>Tolerance, mm</u>
50 mm to 175 mm	+ 8.0 mm
Above 175 mm	+ 12.5 mm

Note: (Hot rolled & forged bars).

Insignificant surface defects in the form of dent and ripple marks are permissible provided their depth does not exceed half the tolerance on each size.

6.0 MANUFACTURE:

Material shall be manufactured from fully killed steel.

7.0 HEAT TREATMENT:

The recommended heat treatment is as follows:

Harden in oil / water from a temperature of 830 – 850°C.

Temper at a suitable temperature between 550 – 660°C.

8.0 FREEDOM FROM DEFECTS:

The bars shall be sound, straight and free from internal and surface defects, such as seams, laps, cracks or any other defects which may impair the end use.

9.0 CHEMICAL COMPOSITION:

The melt analysis of steel and the permissible variation in the composition of the finished product from the melt analysis shall be follows:

Element	Melt analysis percent		Permissible variation, percent, in product analysis
	Min.	Max.	
Carbon	0.35	0.45	± 0.02
Silicon	0.10	0.35	± 0.03
Manganese	0.40	0.70	± 0.04
Nickel	1.25	1.75	± 0.05
Chromium	0.90	1.30	± 0.05
Molybdenum	0.20	0.35	± 0.03
Sulphur	---	0.035	+ 0.005
Phosphorus	---	0.035	+ 0.005



CORPORATE PURCHASING SPECIFICATION

AA10501

Rev No.14

PAGE 3 of 4

10.0 TEST SAMPLES:

10.1 One sample shall be taken from each melt for chemical analysis.

10.2 One sample shall be taken from each heat treatment batch for testing of mechanical properties. Test pieces for mechanical tests shall be taken in the longitudinal direction of the piece.

For ruling section up to & including 40mm, the test piece shall be machined coaxially from the test bars. For ruling section above 40mm the longitudinal axis shall be at least 12.5 mm from surface of the test bars.

Test methods for determining mechanical properties shall be as per IS: 1598 (For IZOD impact test)/IS: 1757 (For impact test in ISO-V Charpy) and IS: 1608 (For tensile test) or any other reputed International Standard.

10.3 For ruling section above 200mm, tensile test samples can be taken in tangential or transverse direction.

11.0 MECHANICAL PROPERTIES (In Hardened and Tempered Condition):

Ruling section, mm	Tensile strength, N/mm ²	0.2%PS/YS N/mm ² min	%E $5.65\sqrt{S_0}$ min	* IZOD impact J, min	Hardness ** BHN
up to 30	1200, min	1000	10	30 (25)	360 – 420
> 30 to = 63	1100 – 1250	880	11	41 (35)	330 – 390
> 63 to = 100	1000 – 1150	800	13	48 (42)	300 – 350
>100 to = 150	900 – 1050	700	15	55 (50)	270 – 300
>150	800 – 950	600	16	55 (50)	240 – 285

* Average of 3 samples applicable for sizes above 16 mm ruling section only. Values in bracket are in ISO - V Charpy.

** Hardness shall be reported for information only.

12.0 ULTRASONIC TEST:

12.1 Each bar above 100 mm shall be tested ultrasonically in accordance with BHEL standard AA0850118 to ensure freedom from internal defects.

The norms of acceptance shall be as per category 2 of the above standard.

12.2 **Optional tests:** If specified on order, each bar > 40 to 100 mm shall be tested ultrasonically in accordance with BHEL standard AA0850118 to ensure freedom from internal defects and the norms of acceptance shall be as per category 2.

386015/2024/HEP-CRX34500

AA10501

Rev No. 14

PAGE 4 of 4

CORPORATE PURCHASING SPECIFICATION



13.0 TEST CERTIFICATES:

Three copies of test certificates shall be supplied, unless otherwise stated on the order. In addition, the supplier shall ensure to enclose one copy of the test certificate along with their dispatch documents to facilitate quick clearance of the material.

The test certificate shall bear the following information:

BHEL References:

AA10501, Rev.No.14: 1.5% Nickel-Chromium-Molybdenum Hot Rolled/Forged Steel Bars- H&T
BHEL order No,

Supplier's References:

Name:

Identification No:

Melt No:

Details of heat treatment:

Result of Tests:

Dimensional inspection.

Results of chemical analysis, mechanical and & Ultrasonic tests.

14.0 PACKING AND MARKING

The bars shall be suitably packed in bundles to prevent corrosion and damage during transit.

Each bar equal to or greater than 50 mm in diameter or of equivalent cross sectional area shall be stamped with 'AA10501' and melt number on the side near the end or on the face.

Bars below 50 mm shall be bundled together and tied with wire at 3 to 4 places along the length of the bars.

A metal label shall be securely attached to each bundle and shall bear the following information:

AA10501: 1.5% Nickel-Chromium-Molybdenum Hot Rolled/Forged Steel Bars- H & T.

BHEL Order No.:

Consignment/Identification No.:

Melt No.:

Size and Weight:

Supplier's Name:

15.0 REFERRED STANDARDS (Latest Publications Including Amendments):

1. IS: 1598

2. IS: 1608

3. IS: 1757

4. IS: 5517

5. AA0850118