



उत्पाद मानक
PRODUCT STANDARD
HYDROGENERATOR ENGINEERING

HG – 10046

REV. 02

PAGE - 1 OF 4

गोपनीय एवं अधिकार सुरक्षित इस प्रपत्रा पर दी गई जानकारी भारत हेवी इलेक्ट्रिकल्स लिमिटेड की सम्पत्ति है इसे प्रत्यक्ष या अप्रत्यक्ष रूप से कम्पनी के हितों को नुकसान पहुँचाने के लिए कदापि उपयोग नहीं किया जावे ।

MAGNETIC STEEL SHEET-COLD ROLLED GR.450

1.0 GENERAL:

This specification gives the quality requirements of high permeability magnetic steel sheet cold rolled, having a minimum 0.2% proof value of 450 N/mm².

2.0 APPLICATION:

Pole Laminations of Hydro Generators / Lift Irrigation Motors.

3.0 CONDITION OF DELIVERY:

Cold Rolled with trimmed edges in straight lengths (sheet form) in the ordered thickness & size as specified on BHEL order.

Material shall be supplied coated with rust preventive oil coating on both sides and shall not contain any welds. The sheets shall be stacked so that their edges are superimposed in a regular manner.

4.0 DIMENSIONS AND TOLERANCES:

4.1 Sizes:

Magnetic steel sheet shall be supplied to the dimensions specified on BHEL order.

The thickness shall preferably be selected from the following standard sizes 0.8 / 1.00 mm. Sheets shall be supplied in straight lengths & shall be flat & edges cleanly sheared & truly squared.

4.2 Tolerances:

4.2.1 Thickness:

| Nominal Thickness (mm) | | Permitted thickness tolerances for widths (mm) |
|------------------------|------|--|
| Above | Upto | Upto 1250 |
| 0.8 | 1.0 | +/-0.05 |

संशोधन:02, Dated 02/01/2018.

Reviewed Clause no.3, 4.1, 4.2.5, 5 & 6.

[Signatures]
 JSY DKC / RG / AD AB

हाइड्रोजनरेटर इंजीनियरिंग विभाग भारत
 हेवी इलेक्ट्रिकल्स लिमिटेड

| तैयारकर्ता -sd- | अनुमोदनकर्ता -sd- | जारी करने की दिनांक |
|------------------------|----------------------|---------------------|
| P. CHAUDHAURI / JKB | S.LOMASH | 16/06/2004 |



उत्पाद मानक
PRODUCT STANDARD
HYDROGENERATOR ENGINEERING

HG – 10046
REV. 02

PAGE - 2 OF 4

गोपनीय एवं अधिकार सुरक्षित इस प्रपत्रा पर दी गई जानकारी भारत हेवी इलेक्ट्रिकल्स लिमिटेड की संपत्ति है इसे प्रत्यक्ष या अप्रत्यक्ष रूप से कम्पनी के हितों को नुकसान पहुँचाने के लिए कदापि उपयोग नहीं किया जावे ।

4.2.2 Width (Trimmed Edges)

| Width (mm) | | Permitted Width tolerances (mm) | |
|------------|------|---------------------------------|-------|
| From | Upto | Plus | Minus |
| - | 1250 | 7 | 0 |
| 1250 | 2000 | 10 | 0 |

4.2.3 Length:

| Length (mm) | Permitted length tolerances | |
|-------------|-----------------------------|-------|
| | Plus | Minus |
| Upto 2000 | 15 mm | 0 |
| Above 2000 | 0.75% of length | 0 |

4.2.4 Flatness:

The maximum distance between the lower face of the sheet and the flat horizontal surface shall not exceed the values given below;

| Length (mm) | Maximum distance for nominal thickness (mm) |
|----------------|---|
| Less than 1250 | 8 |
| 1250 & above | 10 |

4.2.5 Edge Camber:

The gap which characterizes the edge camber shall not exceed $0.4\% \times \text{Length}$ of the sheet for material supplied with trimmed edges.



उत्पाद मानक
PRODUCT STANDARD
HYDROGENERATOR ENGINEERING

HG – 10046

REV. 02

PAGE - 3 OF 4

गोपनीय एवं अधिकार सुरक्षित इस प्रपत्रा पर दी गई जानकारी भारत हेवी इलेक्ट्रिकल्स लिमिटेड की सम्पत्ति है इसे प्रत्यक्ष या अप्रत्यक्ष रूप से कम्पनी के हितों को नुकसान पहुँचाने के लिए कदापि उपयोग नहीं किया जावे ।

5.0 FREEDOM FROM DEFECTS:

The surface of the material, before application of rust preventive oil coating, shall be smooth and clean, free from grease, rust, loose scale and other surface defects such as burrs, cutting distortions, dents, waviness, scratches, blisters, cracks, pitting, cracked edges etc.

6.0 TEST SAMPLES:

One bend test and one hardness test shall be carried out from each lot of material or part thereof, per melt per consignment.

Where materials of more than two thicknesses are rolled from the same melt, one additional bend test shall be made for each thickness.

Test pieces shall be out so that the axis of the bend is parallel to the direction of rolling i.e. bending shall be in perpendicular direction of rolling

7.0 PROPERTIES:

The material, when tested as detailed in BS EN 10265 at a temperature of 27+/-2 °C shall show the following properties:


7.1 Mechanical:

| | |
|----------------------------------|---------------------------------|
| Tensile Strength | : 550-650 N/mm ² |
| 0.2% Proof Stress | : 450 N/mm ² minimum |
| Elongation on 80 mm Gauge length | : 14% minimum |

7.2 Magnetic :

The material when tested on a Epstein frame at an AC Magnetic field in amperes/meter shall show the following minimum corresponding value of magnetic flux density in Tesla.

| Magnetic field strength (A/m) | Minimum Magnetic flux Density (Tesla) |
|-----------------------------------|---------------------------------------|
| 5000 | 1.6 (For information) |
| 15000 | 1.8 (Guaranteed) |

| | | |
|---|--|--|
| <p>गोपनीय एवं अधिकार सुरक्षित इस प्रपत्रा पर दी गई जानकारी भारत हेवी इलेक्ट्रिकल्स लिमिटेड की सम्पत्ति है इसे प्रत्यक्ष या अप्रत्यक्ष रूप से कम्पनी के हितों को नुकसान पहुँचाने के लिए कदापि उपयोग नहीं किया जावे ।</p> | <div style="text-align: center;">  <p>उत्पाद मानक PRODUCT STANDARD HYDROGENERATOR ENGINEERING</p> </div> | <div style="text-align: right;"> <p>HG – 10046 REV. 02</p> <p>PAGE - 4 OF 4</p> </div> |
| | | |
| | | |
| | <p>8.0 TEST CERTIFICATE:</p> <p>Three copies of Test Certificate shall be supplied unless otherwise agreed to.</p> <p>In addition, the supplier shall ensure to enclose one copy of the test Certificate along with their dispatch documents, to facilitate quick clearance of the material.</p> <p>The test certificate shall bear the following information:</p> <p>Material grade, BHEL Order No, Supplier's Name/Grade/Identification No., Size & Weight, Packet/Bundle No, Test Results of – a)Dimensions & Tolerances, b) Mechanical Properties & c) Electromagnetic properties viz: Magnetic Flux Density in Tesla – Guaranteed at 15000 A/m & For information at 5000 A/m and B.H. Curve from 0 to 15000 A/m.</p> <p>9.0 PACKING AND MARKING:</p> <p>9.1 Packing:</p> <p>Magnetic steel sheets shall be supplied in bundles. The packing shall be sea worthy and shall protect the material from damage in transit. Proper supports are to be provided to avoid bulging/ distortion of the sheets.</p> <p>Each sheet shall be marked with supplier's grade/ references. These markings shall be along the rolling direction.</p> <p>NOTE :</p> <p>a) Water proof paper lining shall be preferably volatile corrosion inhibitor (V.C.I.) coated paper with additional polythene (100 micron) enveloped.</p> <p>b) Approximate weight of each bundle shall be 2 to 3 metric tonnes. Bundle weighing 2 metric tonnes is however preferred.</p> <p>c) The packing shall ensure that there is no seepage of moisture and the sheets reach BHEL in completely rust free condition. It shall be strong enough to withstand handling at the docks, sea and on the road.</p> <p>9.2 Marking:</p> <p>A metal label/tag shall be securely attached with each bundle, outside its wrapping and shall be legibly marked with the following information:</p> <p>BHEL Order No, Supplier's Name / Grade / Identification No, size & weight, Melt No, Packet / Bundle No.</p> | |