



CORPORATE STANDARD

AA 085 01 29

PAGE 1 OF 1

ACCEPTANCE STANDARDS FOR LIQUID PENETRANT EXAMINATION OF WELDS

1.0 SCOPE:

- 1.1 This standard covers the "Acceptance Standards For Liquid Penetrant Examination Of Wleds".
- 1.2 The procedure for liquid penetrant examination shall be as per Corporate Standard AA 085 01 31: Procedure For Liquid Penetrant Examination.
- 1.3 This standard is based on ASME Section 8, Division 1, Appendix 8.

2. DEFINITION OF INDICATIONS:

Relevant indications are those which result from mechanical discontinuities. Indications with major dimensions greater than 1.6 mm only shall be considered relevant.

- 2.1 Linear indications are those indications in which the length is more than three times the width.
- 2.2 Rounded indications are those indications which are circular or elliptical with the length equal to or less than 3 times the width.
- 2.3 Any questionable or doubtful indications shall be retested to verify whether or not they are relevant.
- 2.4 Localised surface imperfections, such as may occur from machining marks, surface conditions or incomplete bond between base metal and cladding may produce similar indications which are not relevant to the detection of unacceptable discontinuities.

3. ACCEPTANCE STANDARDS:

All surfaces to be examined shall be free from:

- a) relevent linear indications.
- b) relevent rounded indications greater than 4.8 mm.
- c) four or more rounded defects in line separated by 1.6 mm or less (edge to edge) except where the specification for the material establishes different requirements for acceptance so far as defects are concerned.

COPYRIGHT AND CONFIDENTIAL
The information on this document is the property of BHARAT HEAVY ELECTRICALS LIMITED.
It must not be used directly or indirectly in any way detrimental to the interest of the company.

Revisions :

Approved :

INTERPLANT
STANDARDIZATION COMMITTEE- WG
(NDT)

Rev. No.

Rev. Date

Revised :

Prepared

Issued

Date

HYDERABAD

CORP. R&D

SEP. '87