

BHEL JHANSI
Specification of Men's Uniform Cloth (Shirt)
Ref: BHEL/JHS/HR/WLF/uniform/01

Annexure-02

(3)

1. Scope of the specification covers the requirement of uniform (Shirt) cloth for men.

2. Sample of Uniform Cloth

The vendor will submit sample and conformance certificate as per specification No: BHEL/JHS/HR/WLF/uniform/01 along with their quotation. Maximum three samples can be submitted with offer by each bidder. Each sample should be at least 50X50 cm piece of cloth and shall have name and signature of the bidder and tender enquiry no.

3. Test Certificate: Test certificate shall be submitted along with bulk supply after carrying out test as per the technical parameters mentioned in point 7 on each lot of supply against BHEL order.

4. Packing & Marking: Each piece of cloth should be packed in a polythene bag. Blend composition and name of the manufacturer will be printed on the cloth.

5. Inspection of the cloth: Final inspection will also be carried out at our works with reference to the approved sample and BHEL/JHS/HR/WLF/Uniform/01/2010 and test report submitted along with supply and as per purchase order. BHEL Jhansi may inspect at manufacturer's work at its discretion with reference to the approved sample and technical parameters with reference to BHEL/JHS/HR/WLF/Uniform/01/2010. The supplier shall give inspection call before dispatch of cloth.

6. Qualification of the vendor: The vendor should be original cloth manufacturer and must have executed order of minimum Rs. 3 lakh in last three years to Govt./PSU/private organizations.

Shri Rajeev Agnihotri
(MM)

Signature

7. Technical parameters with reference IS: 15852/2009 for shirt cloth

Technical Parameters	
1. Colour of Cloth	Smoke Grey
2. Blend Composition	67 % /33 +/-2%
3. Cut Length	2.20-2.50 meter
4. Width	90 Cms +/-1 Cm
5. Yarn Number - NE - Warp Weft	2/80s PC +/-5% 2/80s PC +/-5%
6. Thread Density Per Inch: - Ends Picks	140 +/-5% 80 +/-5%
7. Weight Per Sq - Mtr - Grams	140.0 +/-5%
8. Breaking Strength - KGF 20 x 5 Cms Ravel led Strip - Warp	80 Kgf (Min) 45 Kgf (Min)
9. Shrinkage When Heated % - Warp - Weft	2.0 Max 2.9 Max
10. Relaxation Shrinkage % - Warp - Weft	1.0 Max 1.0 Max
11. Ph of Aqueous Extract.	6 -9.5
12. Water Soluble	1% Maximum
Colour Fastness Test	4 or better
a) Lighting - Class	4 or better
b) Washing - Change in Colour - Staining on Undyed Piece	4 or better
c) Perspiration	4 or better
Acidic - Change in Colour - Staining on Undyed Piece	4 or better
Alkaline - Change in Colour - Staining on Undyed Piece	4 or better
13. Fibre Composition - Warp P/C - Weft P/C	67/33 +/-2% 67/33 +/-2%
14. Rubbing (Pilling)	4 or better
15. Weave	Plain

Annex