

दिनांक एवं हस्ताक्षर SIGN- 		संस्थान क्रय विनिर्देश (हीप - हरिद्वार) PLANT PURCHASE SPECIFICATION (HEEP - HARIDWAR)	HW 19386 मुख पृष्ठ PREFACE SHEET
सामग्री सूची संख्या को SUPERSEDES INVENTORY NO.		ALLOY STEEL FORGINGS FOR HIGH TEMPERATURE SERVICE- H & T (Gr : 21CrMoNiV4-7)	
COPYRIGHT AND CONFIDENTIAL The information on this documents is the property of Bharat Heavy Electrical Limited. It must not be used directly or indirectly in any way detrimental to the interest of the company.		केवल आंतरिक प्रयोग हेतु प्रदायक को देने से पूर्व इस मुखपृष्ठ को निकाल दें । FOR INTERNAL USE ONLY REMOVE THIS PREFACE BEFORE ISSUE TO SUPPLIERS. समतुल्य मानक/सूची आदि COMPARABLE STANDARDS / CATALOGUES ETC. } :NIL	
स्वत्वाधिकार एवं गोपनीय इस प्रलेख में दी गई सूचना भारत हेवी इलेक्ट्रिकल्स की सम्पत्ति है इसका प्रयुक्त एवं अप्रत्यक्ष रूप से किसी भी तरह प्रयोग, जो कि कंपनी के हित में हानिकारक हो न किया जाए ।		सुझाए/सम्भावित प्रदायक एवं श्रेणी SUGGESTED / PROBABLE SUPPLIERS AND GRADES. } :AS PER PMD	
दिनांक एवं दिनांक SIGN & DATE 		कोई अन्य जानकारी ANY OTHER INFORMATION } : BASED ON TLV 9187 02 04/2011	
सामग्री सूची संख्या INVENTORY NO. P-1044	REV 03 17.03.18	स्वीकृति : संस्थान मानक समिति APPROVED : PLANT STANDARDS COMMITTEE निर्माण : PREPARED : MTE	जारी : मानक विभाग ISSUED : STANDARDS DIVISION दिनांक : DATE : 07.01.1984 GP NO 2.60

दिनांक एवं हस्ताक्षर SIGN & DATE		संस्थान क्रय विनिर्देश (हीप - हरिद्वार) PLANT PURCHASE SPECIFICATION (HEEP - HARIDWAR)		HW 19386 पृष्ठ का Page 1 of 4																																																													
		SUPERSEDES INVENTORY NO. TLV 9187/02, 04/11																																																															
COPYRIGHT AND CONFIDENTIAL The information on this document is the property of Bharat Heavy Electrical Limited. It must not be used directly or indirectly in any way detrimental to the interest of the company.		ALLOY STEEL FORGINGS FOR HIGH TEMPERATURE SERVICE- H & T (Gr : 21CrMoNiV4-7)																																																															
		1.0 GENERAL: This specification governs the quality requirements of Alloy Steel Forgings for High Temperature Service (Gr: 21CrMoNiV4-7; material no. 1.6981) in Hardened and Tempered condition. 2.0 APPLICATION: Used for steam turbine components such as discs, rings, bushings, bars etc. 3.0 CONDITION OF DELIVERY: Forged or rolled. Hardened and Tempered. Unless otherwise specified in BHEL order / drawing, rough machining of the forgings shall be carried out. 4.0 DIMENSION AND TOLERANCES: Forging shall be supplied to the dimensions and tolerances as per the ordering drawing. 5.0 MANUFACTURING: Degassed steel shall be used. Note: Raw material like Ingots/Blooms/Billets required for forgings shall be procured from BHEL approved sources along with test certificate." 6.0 HEAT TREATMENT: Hardening: 900 - 950°C / air, oil, polymer * or water dipping* * With center cooling rate comparable to oil quenching Tempering: 680 - 720 °C (Min. 2 hours) The duration of tempering as well as the controlled cooling rate are to be chosen to achieve minimum residual stress. 7.0 CHEMICAL COMPOSITION: Heat analysis in weight % shall be as follows: <table border="1"> <tr> <td>C</td> <td>0.17 - 0.25</td> <td>Si</td> <td>0.15 - 0.35</td> <td>Mn</td> <td>0.35 - 0.85</td> </tr> <tr> <td>P</td> <td>≤ 0.020</td> <td>S</td> <td>≤ 0.020</td> <td>Cr</td> <td>0.90 - 1.20</td> </tr> <tr> <td>Mo</td> <td>0.65 - 0.80</td> <td>Ni</td> <td>0.50 - 0.80</td> <td>V</td> <td>0.25 - 0.35</td> </tr> <tr> <td>Al_{tot.}</td> <td>≤ 0.015</td> <td></td> <td></td> <td></td> <td></td> </tr> </table>				C	0.17 - 0.25	Si	0.15 - 0.35	Mn	0.35 - 0.85	P	≤ 0.020	S	≤ 0.020	Cr	0.90 - 1.20	Mo	0.65 - 0.80	Ni	0.50 - 0.80	V	0.25 - 0.35	Al _{tot.}	≤ 0.015																																								
C	0.17 - 0.25	Si	0.15 - 0.35	Mn	0.35 - 0.85																																																												
P	≤ 0.020	S	≤ 0.020	Cr	0.90 - 1.20																																																												
Mo	0.65 - 0.80	Ni	0.50 - 0.80	V	0.25 - 0.35																																																												
Al _{tot.}	≤ 0.015																																																																
स्वतंत्रता एवं गोपनीय इस प्रलेख में दी गई सूचना भारत हेवी इलेक्ट्रिकल्स की सम्पत्ति है इसका प्रत्यक्ष एवं अप्रत्यक्ष रूप से किसी भी तरह प्रयोग, जो कि कंपनी के हित में हानिकारक हो न किया जाए ।		<table border="1"> <tr> <td>TSX</td> <td>B.CHOUDHARY</td> <td>19.01.12</td> <td>अनुवादक</td> <td>TRANSLATED BY</td> <td></td> </tr> <tr> <td>IPSc</td> <td>V.K.CHAUHAN</td> <td></td> <td>निर्माणकर्ता</td> <td>WORKED BY</td> <td>PANKAJ AGARWAL</td> </tr> <tr> <td>STE</td> <td>D.K.RAY</td> <td>06.1.12</td> <td>जांचकर्ता</td> <td>CHECKED BY</td> <td>ASHISH RANJAN</td> </tr> <tr> <td>QAX</td> <td>S. AGRAWAL</td> <td></td> <td>पर्यवेक्षणकर्ता</td> <td>SUPERVISED BY</td> <td>GOPAL KRISHNAN</td> </tr> <tr> <td>सहमत विभाग</td> <td>नाम</td> <td>दिनांक एवं हस्ताक्षर</td> <td colspan="3"></td> </tr> <tr> <td>AGREED DEPTT.</td> <td>NAME</td> <td>DATE & SIGNATURE</td> <td colspan="3"></td> </tr> <tr> <td colspan="3"> स्वीकृति : संस्थान मानक समिति APPROVED : PLANT STANDARDS COMMITTEE </td> <td colspan="3">GP NO 2.60</td> </tr> <tr> <td colspan="3"> REV 03 (REAFFIRMED) Dt. 17.03.18 </td> <td colspan="3"> निर्माण : PREPARED : MTE </td> </tr> <tr> <td colspan="3"></td> <td colspan="3"> जारी : मानक विभाग ISSUED : STANDARDS DIVISION </td> </tr> <tr> <td colspan="3"></td> <td colspan="3"> दिनांक : DATE : 07.01.1984 </td> </tr> </table>				TSX	B.CHOUDHARY	19.01.12	अनुवादक	TRANSLATED BY		IPSc	V.K.CHAUHAN		निर्माणकर्ता	WORKED BY	PANKAJ AGARWAL	STE	D.K.RAY	06.1.12	जांचकर्ता	CHECKED BY	ASHISH RANJAN	QAX	S. AGRAWAL		पर्यवेक्षणकर्ता	SUPERVISED BY	GOPAL KRISHNAN	सहमत विभाग	नाम	दिनांक एवं हस्ताक्षर				AGREED DEPTT.	NAME	DATE & SIGNATURE				स्वीकृति : संस्थान मानक समिति APPROVED : PLANT STANDARDS COMMITTEE			GP NO 2.60			REV 03 (REAFFIRMED) Dt. 17.03.18			निर्माण : PREPARED : MTE						जारी : मानक विभाग ISSUED : STANDARDS DIVISION						दिनांक : DATE : 07.01.1984		
TSX	B.CHOUDHARY	19.01.12	अनुवादक	TRANSLATED BY																																																													
IPSc	V.K.CHAUHAN		निर्माणकर्ता	WORKED BY	PANKAJ AGARWAL																																																												
STE	D.K.RAY	06.1.12	जांचकर्ता	CHECKED BY	ASHISH RANJAN																																																												
QAX	S. AGRAWAL		पर्यवेक्षणकर्ता	SUPERVISED BY	GOPAL KRISHNAN																																																												
सहमत विभाग	नाम	दिनांक एवं हस्ताक्षर																																																															
AGREED DEPTT.	NAME	DATE & SIGNATURE																																																															
स्वीकृति : संस्थान मानक समिति APPROVED : PLANT STANDARDS COMMITTEE			GP NO 2.60																																																														
REV 03 (REAFFIRMED) Dt. 17.03.18			निर्माण : PREPARED : MTE																																																														
			जारी : मानक विभाग ISSUED : STANDARDS DIVISION																																																														
			दिनांक : DATE : 07.01.1984																																																														


दिनांक एवं हस्ताक्षर SIGN & DATE		संस्थान क्रय विनिर्देश (हीप - हरिद्वार) PLANT PURCHASE SPECIFICATION (HEEP - HARIDWAR)		HW 19386 पृष्ठ का Page 2 of 4											
		8.0 TEST SAMPLES: A hardness test shall be performed on all forgings. The mechanical properties are to be determined at one forging per melt and heat treatment batch. In case of rings, the specimens (1 tensile specimen, 3 impact specimens) are to be taken out from tangential ring. In case of discs and solid material, the specimens have to be taken at a distance d/3 or a/3 and b/3 from the respective surfaces. In this case, transverse specimens are also allowed. In case of other geometries the specimens are to be taken out from prolongations of the forging. When different dimensions are produced within the same heat and heat treatment batch, the heaviest one shall be used for the determination of the mechanical properties. The tangential test ring or the sample for determination of the mechanical properties shall be cut from the forging after all heat treatment operations. If re-tempering is necessary, the test ring shall be placed by the forging.													
सामग्री सूची संख्या को अधिकृतित करता है	SUPERSEDES INVENTORY NO.	9.0 MECHANICAL PROPERTIES: Following properties must be achieved at room temperature:													
		<table border="1"> <thead> <tr> <th>0.2% Proof Stress (N/mm²)</th> <th>Tensile Strength (N/mm²)</th> <th>Elongation (%)</th> <th>Red. in area (%)</th> <th>Impact¹ Joule</th> <th>Hardness HB30</th> </tr> </thead> <tbody> <tr> <td>550 - 700</td> <td>≥ 700</td> <td>≥ 15</td> <td>≥ 40</td> <td>≥ 24</td> <td>≥ 215</td> </tr> </tbody> </table> ¹ Average of 3 Charpy V-notch specimens, longitudinal or transverse minimum value = 17 J				0.2% Proof Stress (N/mm ²)	Tensile Strength (N/mm ²)	Elongation (%)	Red. in area (%)	Impact ¹ Joule	Hardness HB30	550 - 700	≥ 700	≥ 15	≥ 40
0.2% Proof Stress (N/mm ²)	Tensile Strength (N/mm ²)	Elongation (%)	Red. in area (%)	Impact ¹ Joule	Hardness HB30										
550 - 700	≥ 700	≥ 15	≥ 40	≥ 24	≥ 215										
8.0 TEST SAMPLES: A hardness test shall be performed on all forgings. The mechanical properties are to be determined at one forging per melt and heat treatment batch. In case of rings, the specimens (1 tensile specimen, 3 impact specimens) are to be taken out from tangential ring. In case of discs and solid material, the specimens have to be taken at a distance d/3 or a/3 and b/3 from the respective surfaces. In this case, transverse specimens are also allowed. In case of other geometries the specimens are to be taken out from prolongations of the forging. When different dimensions are produced within the same heat and heat treatment batch, the heaviest one shall be used for the determination of the mechanical properties. The tangential test ring or the sample for determination of the mechanical properties shall be cut from the forging after all heat treatment operations. If re-tempering is necessary, the test ring shall be placed by the forging.		10.0 NONDESTRUCTIVE TESTING: 10.1 Following NDE shall be performed in delivery condition: - Visual inspection - Material verification test - 100% UT- inspection according to EN 10228-3 (table 3). Depending on the forging geometry, following inspection types are applicable: - for bar shape components; type 1 (inspection may also be carried out as per EN10308 for type 1) - for discs and plate- like components: type 2 - for ring or bushing- like components: type 3b and 3c 10.2 Criteria for registration and decision: Regarding the UT- inspection quality class 3 (table 5) according to EN10228-3 shall be applied. The decision limit for loss of back wall echo is 4 dB and for the real reflector length 10 mm.													
11.0 PRODUCT AND PROCESS QUALIFICATION: 11.1 General Product and process qualification procedures must be conducted for first order. Such product and process qualification is required for each of the manufacturer's fabrication sites and for every raw material source.		11.0 PRODUCT AND PROCESS QUALIFICATION: 11.1 General Product and process qualification procedures must be conducted for first order. Such product and process qualification is required for each of the manufacturer's fabrication sites and for every raw material source.													
हस्ताक्षर एवं दिनांक SIGN & DATE	दिनांक एवं हस्ताक्षर SIGN & DATE	REV 03													
सामग्री सूची संख्या INVENTORY NO.	सामग्री सूची संख्या को अधिकृतित करता है	निर्माणकर्ता WORKED BY	A. Ranjan		06.01.12										
P-1044	सामग्री सूची संख्या को अधिकृतित करता है	जांचकर्ता CHECKED BY	Gopal Krishnan		06.01.12										



COPYRIGHT AND CONFIDENTIAL

The information on this documents is the property of Bharat Heavy Electrical Limited. It must not be used directly or indirectly in any way detrimental to the interest of the company

स्वत्वाधिकार एवं गोपनीय

इस दस्तावेज में दी गई सूचना भारत हेवी इलेक्ट्रिकल्स की सम्पत्ति है इसका प्रत्यक्ष एवं अप्रत्यक्ष रूप से किसी भी तरह प्रयोग, जो कि कंपनी के हित में हानिकारक हो न किया जाए।

दिनांक एवं हस्ताक्षर SIGN & DATE			संस्थान क्रय विनिर्देश (हीप - हरिद्वार) PLANT PURCHASE SPECIFICATION (HEEP - HARIDWAR)		HW 19386 पृष्ठ का Page 3 of 4	
सामग्री सूची संख्या को SUPERSEDES INVENTORY NO.		Depending on the complexity of the product and/or process and the experience from the first order, additional product and process qualification procedures may have to be implemented for subsequent orders. Prior to the start of manufacture, the manufacturer has to submit a manufacturing and testing plan to BHEL in which the quality assured process workflow, i.e. the sequence of process activities (manufacturing, testing and inspection steps) are specified in chronological order. The internal and external codes, standards, drawings, specifications and records applied to each sub process step must be noted along with the information about the equipment and test and inspection scopes used and, where related, any related subcontracting. BHEL may inspect/review supplier internal documents also. If any change in the manufacturing and testing process is required, prior approval from BHEL is to be taken. Depending on the type and scope and thus the significance of any given change, BHEL will decide whether it is necessary to requalify the product and/or process.				
COPYRIGHT AND CONFIDENTIAL The information on this documents is the property of Bharat Heavy Electrical Limited. It must not be used directly or indirectly in any way detrimental to the interest of the company		11.2 The following additional tests have to be performed during qualification: 11.2.1 Tensile tests at elevated temperature: In accordance with EN 10002-5 a tensile test (in the same direction as at room temperature) has to be performed at 560°C. The following properties must be achieved: 0.2% Proof Stress $\geq$ 290 Mpa, Tensile Strength $\geq$ 400 MPa, Elongation $\geq$ 18 % Reduction in area $\geq$ 68% 11.2.2 Microstructure Examination: The homogeneity of the microstructure has to be checked and documented by micro section. The microstructure must be uniform and free from porosity, excessive segregation and other inhomogeneities. The inclusion content has to be determined in accordance with ASTM E 45. The grain size must be measured after all heat treatments have been performed in accordance with ASTM E 112 or ISO 643. Grain size 4 or finer must be achieved. A deviation from the average grain size of more than 2 grain sizes is not permissible. 12.0 RECTIFICATION OF DEFECTS: Rectification of defects in forgings shall not be carried out by the supplier without the prior written permission of BHEL. 13.0 TEST CERTIFICATES: Unless otherwise stated in the order, three copies of test certificates shall be supplied as per 3.1 of EN10204. In addition, the supplier shall ensure to enclose one copy of the test certificate along with their dispatch documents to facilitate quick clearance of the material.				
स्वत्वाधिकार एवं गोपनीय इस प्रलेख में दी गई सूचना भारत हेवी इलेक्ट्रिकल्स की संपत्ति है इसका प्रत्यक्ष एवं अप्रत्यक्ष रूप से किसी भी तरह प्रयोग, जो कि कंपनी के हित में हानिकारक हो न किया जाए।						
दिनांक एवं हस्ताक्षर SIGN & DATE						
सामग्री सूची संख्या INVENTORY NO.	P-1044	REV 03	निर्माणकर्ता WORKED BY	A. Ranjan		06.01.12
			जांचकर्ता CHECKED BY	Gopal Krishnan		06.01.12

दिनांक एवं हस्ताक्षर SIGN & DATE			संस्थान क्रय विनिर्देश (हीप - हरिद्वार) PLANT PURCHASE SPECIFICATION (HEEP - HARIDWAR)		HW 19386 पृष्ठ का Page 4 of 4		
सामग्री सूची संख्या को SUPERSEDES INVENTORY NO.		Following details shall be furnished in the test certificate: HW19386 : Alloy Steel Forgings for high temperature service- H & T (Gr : 21CrMoNiV4-7) BHEL order Heat No. , and melting type. Dimensional inspection Details of all heat treatment cycle followed. Results of chemical analysis including trace elements. Results of mechanical tests, including hardness test. All individual values shall be reported. Results of ultrasonic tests Confirmation of the visual inspection Confirmation of the verification inspection Results of additional tests called for in the drawing/order Mill test certificate					
COPYRIGHT AND CONFIDENTIAL The information on this documents is the property of Bharat Heavy Electrical Limited. It must not be used directly or indirectly in any way detrimental to the interest of the company		14.0 DEVIATIONS: Any deviation from this delivery specification has to be reported to BHEL immediately using Proforma PU-25 supplied with the order. Any deviation is generally accepted only if this has been approved by BHEL in a written form. 15.0 CLEARANCE FOR DELIVERY: The clearance for dispatch is based on the total results of all tests performed considering the service stresses of the component. BHEL has the right to accept deviations of the specified values, if it is shown by individual judgment that the service properties are not reduced. The clearance does not release the manufacturer from the responsibility for hidden defects that are detected at later stage of manufacturing.					
स्वत्वाधिकार एवं गोपनीय इस प्रलेख में दी गई सूचना भारत हेवी इलेक्ट्रिकल्स की सम्पत्ति है इसका प्रत्यक्ष एवं अप्रत्यक्ष रूप से किसी भी तरह प्रयोग, जो कि कंपनी के हित में हानिकारक हो न किया जाए ।		16.0 PACKING AND MARKING: Forgings shall be suitably packed to prevent corrosion and damage during transit. Machined surfaces shall be properly protected with anti-corrosive compounds. Each package or forging (when supplied separately) shall be legibly marked with the following information: HW19386, BHEL Order No., Drawing no., Batch No., Weight, Supplier's name. 17.0 REFERRED STANDARDS (Latest Publications Including Amendments): 1. EN 10228-3. 2. EN10308 3. ASTM E45 4. ASTM E 112 5. ISO 643 6. EN 10002, Part 5 7. EN10204					
हस्ताक्षर एवं दिनांक SIGN & DATE							
सामग्री सूची संख्या INVENTORY NO.	P-1044	REV 03		निर्माणकर्ता WORKED BY	A. Ranjan		06.01.12
				जांचकर्ता CHECKED BY	Gopal Krishnan		06.01.12