

ANNEXURE - A

Major Properties to be adhered in the Test Certificates	Standard Results
1. Drying time @ 27 degree C	
a) Surface dry, Max (In Hours)	4 hours
b) Hard dry, Max (In Hours)	16 hours
c) Curing time, Max (In Hours)	Max 7 days
2. Finish	Eggshell
3. Colour	Grey/Yellow/Green/Red
4. Dry film thickness per coat, Min (In Microns)	35-40 Microns
5. Volume solids, percent by mass, Min	40-50%
6. Flexibility and adhesion	Good
7. Flash point	Not less than 24 degree C

