

 RANIPET	Bharat Heavy Electricals Limited Boiler Auxiliaries Plant Ranipet – 632 406	BHEL DOC NO.	PS: Mouda FGD: G503
		REVISION NO.	02
		DATE	14.05.2019

MOUDA FGD PACKAGE

PAINTING SCHEME for FGD SYSTEM, BOOSTER FAN& GATES& DAMPERS

NTPC CONTRACT NO: CS-9561-109(113)-9-FC-N0A-6722 Dt.18.09.2018

NTPC DRG NO: 9561-109-RP-PVM-H-396

BHEL RANIPET Customer No(s).: G503-G504

Prepared By	Reviewed & Approved By
	
Rajamanickam M Dy.Manager/QA	K.C. Gandhi Parimalam DGM/QA

SI No	SURFACE LOCATION	PGMA	SURFACE PREPARATION	PRIMER		FINISH		TOTAL DFT IN (μ min.)
				PAINT	DFT (μ min.)	PAINT	DFT (μ min.)	

RECORD OF REVISION

REV NO	DATE	DETAILS OF REVISION						
00	06.02.2019	Original Issue - First Submission						
		Revised Issue						
		NTPC comments: ACW/ECW system shall be included						
		BHEL reply: We would like to submit that ACW/ECW system comes under BHEL-PEM and they will be submitting their painting scheme for their scope of supply. Also, we would like to stress that FGD is a system comparable to SG& TG and supplied by seven units namely Ranipet, PEM, ISG& EDN, Bangalore, Bhopal, Hyderabad and Trichy. Hence, we have made this painting scheme for Ranipet scope of supply for which PGMA are released by Ranipet Engg.						
		NTPC comments: Furnish painting scheme for chimney and its associated components						
		BHEL reply: We would like to submit that as stated above, chimney and its associated components doesn't fall under Ranipet scope of supply and it comes under BHEL-PEM. Hence this painting scheme does not cover painting for chimney and its associated components. We request M/s NTPC to consider and approve the painting scheme envisaged.						
		NTPC comments: Color shade shall be as per NTPC standard document doc no: QS-01-DIV-W-4 with latest revision.						
		BHEL reply: We would like to submit that all the color shades mentioned in this document are as per the NTPC standard document doc no: QS-01-DIV-W-4 (latest).						
		NTPC comments: Sl no: 6 of Fans, how is this line with spec?						
		BHEL reply: We wish to submit that Booster fan canopy for motor has been given painting as per the clause 1.04.00 of Part-A, section-VI as its part of FGD system. Also, the painting envisaged as per the spec provides superior resistance to corrosion and polyurethane finish paint provides glossy surface finish. Hence this painting is in line with the specification only and we request M/s NTPC to approve the painting envisaged as the same painting is approved for Barh-I and II projects.						
		NTPC comments: Sl no: 7 of Fans, what is the basis?						
		BHEL reply: Axial booster fan rotor is housed inside the housing and is flue gas path. The rotor needs protection till erection only. Therefore, the painting envisaged is only the primer as once the fan is commissioned, paint will be completely peeled off as it is in flue gas path. Hence, we request M/s NTPC to approve the painting envisaged. Also, we would like to submit that this was approved for Barh-I & II painting schemes as same reason was explained.						
		NTPC comments: Sl no: 10& 11 of Fans, what is the basis of selecting shade?						
		BHEL reply: We would like to submit that we have devised color shades as per NTPC standard document: QS-01-DIV-W-4 (latest). In the document, for fans it was grey white, hence we have given the same color shade for booster fan and its associated equipment also. We request you to kindly approve the same shade envisaged similar to approved Barh-I& II painting schemes.						
		NTPC comments: Sl no: 01 of FGD, why is this selected?						
		BHEL reply: We submit that the paint given was as per clause no 7.05.00 as the surfaces was similar. Slurry recirculation pumps were indoor and kept in a building. This surface was only available under clause 7.5.00. This same comment was raised for Barh-I and II as well. When we explained the reason, NTPC Engg wanted to follow clause 1.04.00 itself for slurry recirculation pumps, hence we changed						
01	27.04.2019	Different structural members						

SI No	SURFACE LOCATION	PGMA	SURFACE PREPARATION	PRIMER		FINISH		TOTAL DFT IN (μ min.)
				PAINT	DFT (μ min.)	PAINT	DFT (μ min.)	

				for Barh-I and Barh-II. Similarly, we have changed for Mouda also as per clause 1.04.00. We request NTPC to approve the painting envisaged.				
				<p>NTPC comments: Sl no: 02 of FGD, basis of selecting shades?</p> <p>BHEL reply: We would like to submit that basis of selecting shades is as per NTPC standard document for color coding. These internals along with their supports will be placed inside the absorber.</p>				
				<p>NTPC comments: Sl no: 10,11,12& 13 of FGD, why is this selected?</p> <p>BHEL reply: We wish to submit that, sl no: 10, Emergency Quench water tank inside surfaces, Primer is only envisaged as liner is given in the inside surfaces of the tank. Sl no: 11 and 12 are given painting as per clause 20.03.00 as temperature is less than 95 deg C. The clause 20.03.00 is used as painting surface under this PGMAAs are not covered under any other clause. For sl no: 13, since it is of duct supports, painting is given as per the civil specification. The same was approved in Barh-I & II also. We have given the same painting specification for Mouda, North Karanpura and Barh-I & II as painting specification is same for all projects. Hence, we request M/s NTPC to kindly approve the same.</p>				
				<p>NTPC comments: Sl no: 17,18, 19& 20 of FGD, shall be in line with specification</p> <p>BHEL reply: We wish to submit that painting is as per clause 20.03.00 and is line with the specification only. The reason for giving this specification is the temperatures are of flue gas temperature before absorber and 60 deg C after absorber of FGD system. Hence this surface will be insulated outside and flue gas swept surface inside. Hence Heat resistant paints is given in the insulated side. Since insides are of flue gas swept surface, primers are only given as paint will be peeled off during commissioning. This same painting was approved for Barh-I & II as well. Hence, we request NTPC to kindly consider and approve the painting envisaged.</p>				
				<p>NTPC comments: Sl no: 31, 32 & 33 of FGD, Provide basis</p> <p>BHEL reply: We wish to submit that Sl no: 31 & 33 of FGD are given painting as per the civil specification as surfaces are exposed to atmosphere. For sl no: 32, slurry pumps are of indoor surfaces and housed in a building. Hence, we have proposed this painting as per clause 7.05.00 as that clause only contains the painting for that type of surface. Hence we request M/s NTPC to approve the painting envisaged as approved for Barh painting schemes.</p>				
				<p>NTPC comments: SL no: 39 of FGD, Painting surface of inside surface of Limestone Silo (cylindrical portion) shall be same as painting scheme of Limestone silo- outside surface</p> <p>BHEL reply: We wish to state that the painting envisaged is until erection only. Once the system is commissioned, paint will peel off completely and application of intermediate and finish paints will become redundant, therefore we have proposed only primer. Also, primer given is of Inorganic Zinc silicate which offers superior protection against corrosion, abrasion and chemical resistance. Hence, we request you to kindly consider and approve the painting envisaged.</p>				
01	27.04.2019			<p>NTPC comments: Note 12 to be incorporated</p> <p>BHEL reply: Incorporated in the document.</p>				
02	14.05.2019			<p>NTPC comments: As per that document not all structures are in RAL 9002, there is distinction between primary and secondary member color shade, same shall be incorporated</p> <p>BHEL reply: We wish to submit that we have selected colour shades as per the NTPC colour coding scheme only. Since all these structures are supporting structures, we have taken reference as Sl no: 10. The distinction between primary and secondary member colour shade is indicated in Sl no: 13, which are not applicable for our type of structures. Hence we request you to kindly consider and</p>				

SI No	SURFACE LOCATION	PGMA	SURFACE PREPARATION	PRIMER		FINISH		TOTAL DFT IN (μ m min.)
				PAINT	DFT (μ m min.)	PAINT	DFT (μ m min.)	

02	14.05.2019	approve our painting schedule. Also we would like to submit that same shade only has been envisaged and approved by M/s NTPC for Barh-I, Barh II, North Karanpura, Patratu and Dadri projects also.													
		NTPC comments: Liner can be provided over paint also. BHEL to follow specification.													
		BHEL reply: We would like to submit that Emergency quenching tank will be provided with rubber lining at site. For rubber lining at site, paint has to be peeled off to make rubber with metal contact. Therefore, we had envisaged red oxide zinc phosphate primer which can provide protection till erection and can be easily removed for making rubber lining at site. In this regard, we request you to kindly consider and approve the painting envisaged. Also we would like to submit that we had envisaged the same reason for Barh-I, Barh-II, North Karanpura and Patratu projects and same was approved by M/s NTPC.													
		NTPC comments: It should be as per spec.													
		BHEL reply: We would like to submit that we had given the same reason for Barh-I, Barh-II, North Karanpura, Dadri painting schemes in which the inside surfaces of lime stone silo will be given primer only and same was approved by M/s NTPC. We would like to stress the point that paint will be peeled off completely in the inside surfaces. Once the system is commissioned, application of intermediate and finish paints is redundant. For outside surfaces, we have given all the coats as surfaces will be exposed to atmosphere. At this context, we would like to request again to consider and approve the painting envisaged for inside surfaces of lime stone silo (cylindrical portion).													
		NTPC comments: Sl no: 12 of FGD, why isn't clause 1.04.01 of Part A, Sub section -III page 2 of 5 is used?													
BHEL reply: Sl no: 12 is of Air oxidation system which comprises of Oxidation blowers and its small auxiliaries. This will be kept inside the acoustic hood which is again housed in a building. It is exposed to operating temperature below 95 deg C and hence clause no: 20.03.00 is used. The clause 1.04.00 is for components where no specific requirement is stipulated. Since the requirements of painting of this PGMA is clearly stipulated in Clause 20.03.00, we have used that clause. Also we would like to submit that we have envisaged the same painting for Barh-I, Barh-II, North Karanpura and Dadri projects also which is approved by M/s NTPC.															
NTPC comments: Sl no: 19 of FGD, Is it same as Ethyl silicate zinc primer?															
BHEL reply: We wish to submit that given paint is Red Oxide Zinc phosphate primer as it is exposed to flue gas in the inside. Red Oxide Zinc phosphate primer will provide protection till erection only, once the system is commissioned, paint will get peeled off due to the flue gases. This is not same as Ethyl silicate zinc primer. This Ethyl silicate zinc primer is given only to the civil structures as it is exposed to atmosphere.															
NTPC comments: Sl no: 20 of FGD, this should be in line with specification. This temp is less than 90.															
BHEL reply: Incorporated in the document.															
NTPC comments: Sl no: 29 of FGD, why isn't clause 1.04.01 of Part A, Sub section -III page 2 of 5 is used?															
BHEL reply: We wish to submit that Miscellaneous FGD system consists of only small orifices, overflow nozzles, vents etc which are very small items and exposed to operating temperature below 95 deg C. Hence primer with finish as per clause 20.03.00 is followed since the painting requirement is stipulated in that clause. Clause 1.04.00 of Part-A, Subsection III is for components where no requirement is stipulated.															

SI No	SURFACE LOCATION	PGMA	SURFACE PREPARATION	PRIMER		FINISH		TOTAL DFT IN (μ min.)
				PAINT	DFT (μ min.)	PAINT	DFT (μ min.)	

1. FANS

1	Axial Fan tool & fixtures (Clause 20.03.00 of Part- C Section VI)	55 000	Power Tool Cleaning to st3 (SSPC-SP3)	Red Oxide Zinc Phosphate Primer to IS: 12744 (Two coats)	60	Synthetic Enamel to IS 2932 Shade: Grey white RAL 9002 (Two coats)	40	100
2	Booster Fan foundation material	55 081		Temporary rust preventive fluid application as per PRQA 523 DFT- 20 μ All Threaded and other surfaces of foundation bolt and its materials shall be coated with temporary rust preventive fluid. During execution of civil works the dried film of coating will be removed using Organic Solvents.				
3	Booster Fan Handrails & Insert (Clause 31.06.00 of Sec.VI, Part-B, Subsection- IV-D)	55 082	Blast cleaning to Sa 2½/ Acid pickling	Hand rails, Gratings, Ladders- Hot dip galvanizing to 610gms/sq.m (minimum) and to a coating thickness of 87 μ m (min).				
4	Booster Fan Handrails & Insert- Structural items other than the above (Clause 31.03.00 of Sec.VI, Part-B, Subsection- IV-D)	55 082	Blast cleaning to Sa 2½ (Near white metal) with surface profile 40- 60 μ m conforming to ISO 8501-1	Primer: One coat of Two component moisture curing zinc (ethyl) silicate primer coat (Min 80% metallic zinc content in dry film, solid by volume minimum 60% ± 2). Zinc dust composition and properties shall be as per Type II as per ASTM D520-00 DFT- 70 μ Intermediate: One coat of Two component polyamide cured epoxy with MIO content (containing lamellar MIO Min 30% on pigment, solid by volume min. 80% ± 2) DFT- 100 μ	70 100	Finish: Two coats of two pack aliphatic isocyanate cured acrylic polyurethane paint to IS 13213 solid by volume min.55% ± 2) DFT- 35 μ / coat Shade: Grey white, RAL 9002 With gloss retention (SSPC paint spec no.36, ASTM D4587, D2244, D523 of level 2 after min. 1000 hrs exposure, gloss less than 30 and colour change less than 2.0 Δ E)	70	240
5	Axial booster cooling/ seal fan (Clause 1.04.00 of Part- A Section VI)	55 084	Blast cleaning to Sa 2½ (SSPC-SP 10)	Primer: Two coats of Epoxy resin based Epoxy Zinc phosphate primer to IS 13238 DFT- 50 μ /coat	100	Finish: One coat of Epoxy based finish paint to IS 14209; DFT- 75 μ	75	300

SI No	SURFACE LOCATION	PGMA	SURFACE PREPARATION	PRIMER		FINISH		TOTAL DFT IN (μ min.)
				PAINT	DFT (μ min.)	PAINT	DFT (μ min.)	

				Intermediate: One coat of Two component epoxy based intermediate paint pigmented with MIO/Tio2 DFT- 100 μ	100	Finish: One coat of acrylic aliphatic polyurethane paint to IS 13213 DFT-25 μ Shade: Grey White, RAL9002	25	
6	Booster fan canopy for motor (Clause 1.04.00 of Part- A Section VI)	55 089	Blast cleaning to Sa 2½	Primer: Two coats of Epoxy resin-based Epoxy Zinc phosphate primer to IS 13238 DFT- 50 μ /coat Intermediate: One coat of Two component epoxy based intermediate paint pigmented with MIO/Tio2 DFT- 100 μ	100	Finish: One coat of Epoxy based finish paint to IS 14209; DFT- 75 μ Finish: One coat of acrylic aliphatic polyurethane paint to IS 13213 DFT-25 μ Shade: Grey White, RAL9002	75	300
7	Axial booster fan rotor (Clause 20.03.00 of Part- C Section VI)	55 287	Power Tool Cleaning to St3 (SSPC-SP3)	Two coats of Epoxy based Zinc phosphate primer (Two pack system) to IS 13238; DFT- 30 μ /coat	60	NIL	--	60
8	Axial booster fan stator (Clause 20.03.00 of Part- C Section VI)	55 587	Power Tool Cleaning to St3 (SSPC-SP3)	Red Oxide Zinc Phosphate Primer to IS: 12744 (Two coats)	60	Synthetic Enamel to IS 2932 Shade: Grey white RAL 9002 (Two coats)	40	100
9	Axial booster fan coupling (Clause 1.04.00 of Part- A Section VI)	55 880	Blast cleaning to Sa 2½	Primer: Two coats of Epoxy resin based Epoxy Zinc phosphate primer to IS 13238 DFT- 50 μ /coat Intermediate: One coat of Two component epoxy based intermediate paint pigmented with MIO/Tio2 DFT- 100 μ	100	Finish: One coat of Epoxy based finish paint to IS 14209; DFT- 75 μ Finish: One coat of acrylic aliphatic polyurethane paint to IS 13213 DFT-25 μ Shade: Grey White, RAL9002	75	300

SI No	SURFACE LOCATION	PGMA	SURFACE PREPARATION	PRIMER		FINISH		TOTAL DFT IN (μ min.)
				PAINT	DFT (μ min.)	PAINT	DFT (μ min.)	
10	Booster fan LOS with lubricant (Clause 1.04.00 of Part- A Section VI)	55 980	Blast cleaning to Sa 2½	Primer: Two coats of Epoxy resin based Epoxy Zinc phosphate primer to IS 13238 DFT- 50 μ /coat Intermediate: One coat of Two component epoxy based intermediate paint pigmented with MIO/Tio2 DFT- 100 μ	100 100	Finish: One coat of Epoxy based finish paint to IS 14209; DFT- 75 μ Finish: One coat of acrylic aliphatic polyurethane paint to IS 13213 DFT-25 μ Shade: Grey White, RAL9002	75 25	300
11	Booster fan actuator (Clause 1.04.00 of Part- A Section VI)	55 983	Blast cleaning to Sa 2½	Primer: Two coats of Epoxy resin based Epoxy Zinc phosphate primer to IS 13238 DFT- 50 μ /coat Intermediate: One coat of Two component epoxy based intermediate paint pigmented with MIO/Tio2 DFT- 100 μ	100 100	Finish: One coat of Epoxy based finish paint to IS 14209; DFT- 75 μ Finish: One coat of acrylic aliphatic polyurethane paint to IS 13213 DFT-25 μ Shade: Grey White, RAL9002	75 25	300

SI No	SURFACE LOCATION	PGMA	SURFACE PREPARATION	PRIMER		FINISH		TOTAL DFT IN (μ min.)
				PAINT	DFT (μ min.)	PAINT	DFT (μ min.)	

2. FGD SYSTEM

1	Slurry recirculation pump System (Clause 1.04.00 of Part- A Section VI)	FW 212	Blast cleaning to Sa 2½	Primer: Two coats of Epoxy resin-based Epoxy Zinc phosphate primer to IS 13238 DFT- 50 μ /coat Intermediate: One coat of Two component epoxy based intermediate paint pigmented with MIO/TiO ₂ DFT- 100 μ	100	Finish: One coat of Epoxy based finish paint to IS 14209; DFT- 75 μ Finish: One coat of acrylic aliphatic polyurethane paint to IS 13213 DFT-25 μ Shade: Grey White, RAL9002	75	300
2	Absorber System Internals – Structural items (Clause 1.04.00 of Part- A Section VI)	FW 213	Blast cleaning to Sa 2½	Primer: Two coats of Epoxy resin based Epoxy Zinc phosphate primer to IS 13238 DFT- 50 μ /coat Intermediate: One coat of Two component epoxy based intermediate paint pigmented with MIO/TiO ₂ DFT- 100 μ	100	Finish: One coat of Epoxy based finish paint to IS 14209; DFT- 75 μ Finish: One coat of acrylic aliphatic polyurethane paint to IS 13213 DFT-25 μ Shade: Grey White, RAL9002	75	300
3	Mist eliminator and accessories- Structural items (Clause 1.04.00 of Part- A Section VI)	FW 215	Blast cleaning to Sa 2½	Primer: Two coats of Epoxy resin based Epoxy Zinc phosphate primer to IS 13238 DFT- 50 μ /coat Intermediate: One coat of Two component epoxy based intermediate paint pigmented with MIO/TiO ₂ DFT- 100 μ	100	Finish: One coat of Epoxy based finish paint to IS 14209; DFT- 75 μ Finish: One coat of acrylic aliphatic polyurethane paint to IS 13213 DFT-25 μ Shade: Grey White, RAL9002	75	300

SI No	SURFACE LOCATION	PGMA	SURFACE PREPARATION	PRIMER		FINISH		TOTAL DFT IN (μ min.)
				PAINT	DFT (μ min.)	PAINT	DFT (μ min.)	
4	Absorber System- Base (Clause 31.03.00 of Sec.VI, Part-B, Subsection- IV-D)	FW 219	Blast cleaning to Sa 2½ (Near white metal) with surface profile 40-60 μ m conforming to ISO 8501-1	Primer: One coat of Two component moisture curing zinc (ethyl) silicate primer coat (Min 80% metallic zinc content in dry film, solid by volume minimum 60% ± 2). Zinc dust composition and properties shall be as per Type II as per ASTM D520-00 DFT- 70 μ Intermediate: One coat of Two component polyamide cured epoxy with MIO content (containing lamellar MIO Min 30% on pigment, solid by volume min. 80% ± 2) DFT- 100 μ	70 100	Finish: Two coats of two pack aliphatic isocyanate cured acrylic polyurethane paint to IS 13213 solid by volume min.55% ± 2) DFT- 35 μ / coat Shade: Grey white, RAL 9002 With gloss retention (SSPC paint spec no.36, ASTM D4587, D2244, D523 of level 2 after min. 1000 hrs exposure, gloss less than 30 and colour change less than 2.0 Δ E)	70	240
5	Absorber system structures (Clause 31.03.00 of Sec.VI, Part-B, Subsection- IV-D)	FW 220	Blast cleaning to Sa 2½ (Near white metal) with surface profile 40-60 μ m conforming to ISO 8501-1	Primer: One coat of Two component moisture curing zinc (ethyl) silicate primer coat (Min 80% metallic zinc content in dry film, solid by volume minimum 60% ± 2). Zinc dust composition and properties shall be as per Type II as per ASTM D520-00 DFT- 70 μ Intermediate: One coat of Two component polyamide cured epoxy with MIO content (containing lamellar MIO Min 30% on pigment, solid by volume min. 80% ± 2) DFT- 100 μ	70 100	Finish: Two coats of two pack aliphatic isocyanate cured acrylic polyurethane paint to IS 13213 solid by volume min.55% ± 2) DFT- 35 μ / coat Shade: Grey white, RAL 9002 With gloss retention (SSPC paint spec no.36, ASTM D4587, D2244, D523 of level 2 after min. 1000 hrs exposure, gloss less than 30 and colour change less than 2.0 Δ E)	70	240

SI No	SURFACE LOCATION	PGMA	SURFACE PREPARATION	PRIMER		FINISH		TOTAL DFT IN (μ min.)
				PAINT	DFT (μ min.)	PAINT	DFT (μ min.)	
6	Absorber system casing bottom (Clause 31.03.00 of Sec.VI, Part-B, Subsection- IV-D)	FW 221	Blast cleaning to Sa 2½ (Near white metal) with surface profile 40-60 μ m conforming to ISO 8501-1	Primer: One coat of Two component moisture curing zinc (ethyl) silicate primer coat (Min 80% metallic zinc content in dry film, solid by volume minimum 60% ± 2). Zinc dust composition and properties shall be as per Type II as per ASTM D520-00 DFT- 70 μ Intermediate: One coat of Two component polyamide cured epoxy with MIO content (containing lamellar MIO Min 30% on pigment, solid by volume min. 80% ± 2) DFT- 100 μ	70 100	Finish: Two coats of two pack aliphatic isocyanate cured acrylic polyurethane paint to IS 13213 solid by volume min.55% ± 2) DFT- 35 μ / coat Shade: Grey white, RAL 9002 With gloss retention (SSPC paint spec no.36, ASTM D4587, D2244, D523 of level 2 after min. 1000 hrs exposure, gloss less than 30 and colour change less than 2.0 Δ E)	70	240
7	Absorber system casing top (Clause 31.03.00 of Sec.VI, Part-B, Subsection- IV-D)	FW 222	Blast cleaning to Sa 2½ (Near white metal) with surface profile 40-60 μ m conforming to ISO 8501-1	Primer: One coat of Two component moisture curing zinc (ethyl) silicate primer coat (Min 80% metallic zinc content in dry film, solid by volume minimum 60% ± 2). Zinc dust composition and properties shall be as per Type II as per ASTM D520-00 DFT- 70 μ Intermediate: One coat of Two component polyamide cured epoxy with MIO content (containing lamellar MIO Min 30% on pigment, solid by volume min. 80% ± 2) DFT- 100 μ	70 100	Finish: Two coats of two pack aliphatic isocyanate cured acrylic polyurethane paint to IS 13213 solid by volume min.55% ± 2) DFT- 35 μ / coat Shade: Grey white, RAL 9002 With gloss retention (SSPC paint spec no.36, ASTM D4587, D2244, D523 of level 2 after min. 1000 hrs exposure, gloss less than 30 and colour change less than 2.0 Δ E)	70	240
8	Absorber system accessories (Clause 20.03.00 of Part- C Section VI)	FW 223	Power Tool Cleaning to St3 (SSPC-SP3)	Red Oxide Zinc Phosphate Primer to IS: 12744 (Two coats)	60	Synthetic Enamel to IS 2932 Shade: Grey white RAL 9002 (Two coats)	40	100

SI No	SURFACE LOCATION	PGMA	SURFACE PREPARATION	PRIMER		FINISH		TOTAL DFT IN (μ min.)
				PAINT	DFT (μ min.)	PAINT	DFT (μ min.)	
9	Emergency Quench water tank- Outside surfaces (Clause 31.03.00 of Sec.VI, Part-B, Subsection- IV-D)	FW 226	Blast cleaning to Sa 2½ (Near white metal) with surface profile 40-60 μ m conforming to ISO 8501-1	Primer: One coat of Two component moisture curing zinc (ethyl) silicate primer coat (Min 80% metallic zinc content in dry film, solid by volume minimum 60% ± 2). Zinc dust composition and properties shall be as per Type II as per ASTM D520-00 DFT- 70 μ Intermediate: One coat of Two component polyamide cured epoxy with MIO content (containing lamellar MIO Min 30% on pigment, solid by volume min. 80% ± 2) DFT- 100 μ	70 100	Finish: Two coats of two pack aliphatic isocyanate cured acrylic polyurethane paint to IS 13213 solid by volume min.55% $\pm 2DFT- 35\mu/ coatShade: Grey white, RAL 9002With gloss retention (SSPC paint spec no.36, ASTM D4587, D2244, D523 of level 2 after min. 1000 hrs exposure, gloss less than 30 and colour change less than 2.0\Delta E)$	70	240
10	Emergency Quench water tank- Inside surfaces	FW 226	Blast cleaning to Sa 2½ (Near white metal) with surface profile 35-50 μ m	Primer: Two coats of Red Oxide Zinc phosphate primer, DFT-30 μ /coat; Total-60 μ (Primer is only envisaged as lining is given in inside surfaces of the tank)				
11	Emergency quench system (Clause 20.03.00 of Part- C Section VI)	FW 227	Power Tool Cleaning to St3 (SSPC-SP3)	Red Oxide Zinc Phosphate Primer to IS: 12744 (Two coats)	60	Synthetic Enamel to IS 2932 Shade: Grey white RAL 9002 (Two coats)	60	120
12	Air oxidation system (Clause 20.03.00 of Part- C Section VI)	FW 230	Power Tool Cleaning to St3 (SSPC-SP3)	Red Oxide Zinc Phosphate Primer to IS: 12744 (Two coats)	60	Synthetic Enamel to IS 2932 Shade: Grey white RAL 9002 (Two coats)	40	100
13	Duct supports Bypass duct, Booster fan, Scrubber, Stack (Clause 31.03.00 of Sec.VI, Part-B, Subsection- IV-D)	FW 232 FW 233 FW 234	Blast cleaning to Sa 2½ (Near white metal) with surface profile 40-60 μ m conforming to ISO 8501-1	Primer: One coat of Two component moisture curing zinc (ethyl) silicate primer coat (Min 80% metallic zinc content in dry film, solid by volume minimum 60% ± 2). Zinc dust composition and properties shall be as per Type II as per ASTM D520-00	70	Finish: Two coats of two pack aliphatic isocyanate cured acrylic polyurethane paint to IS 13213 solid by volume min.55% $\pm 2DFT- 35\mu/ coatShade: Grey white, RAL 9002$	70	240

SI No	SURFACE LOCATION	PGMA	SURFACE PREPARATION	PRIMER		FINISH		TOTAL DFT IN (μ min.)
				PAINT	DFT (μ min.)	PAINT	DFT (μ min.)	
				DFT- 70 μ Intermediate: One coat of Two component polyamide cured epoxy with MIO content (containing lamellar MIO Min 30% on pigment, solid by volume min. 80% \pm 2) DFT- 100 μ	100	With gloss retention (SSPC paint spec no.36, ASTM D4587, D2244, D523 of level 2 after min. 1000 hrs exposure, gloss less than 30 and colour change less than 2.0 Δ E)		
14	Structures for RC pump house (Clause 31.03.00 of Sec.VI, Part-B, Subsection- IV-D)	FW 236	Blast cleaning to Sa 2½ (Near white metal) with surface profile 40-60 μ m conforming to ISO 8501-1	Primer: One coat of Two component moisture curing zinc (ethyl) silicate primer coat (Min 80% metallic zinc content in dry film, solid by volume minimum 60% \pm 2). Zinc dust composition and properties shall be as per Type II as per ASTM D520-00 DFT- 70 μ Intermediate: One coat of Two component polyamide cured epoxy with MIO content (containing lamellar MIO Min 30% on pigment, solid by volume min. 80% \pm 2) DFT- 100 μ	70 100	Finish: Two coats of two pack aliphatic isocyanate cured acrylic polyurethane paint to IS 13213 solid by volume min.55% \pm 2) DFT- 35 μ / coat Shade: Grey white, RAL 9002 With gloss retention (SSPC paint spec no.36, ASTM D4587, D2244, D523 of level 2 after min. 1000 hrs exposure, gloss less than 30 and colour change less than 2.0 Δ E)	70	240
15	Oxidation Air distribution system (Clause 1.04.00 of Part- A Section VI)	FW 244	Blast cleaning to Sa 2½	Primer: Two coats of Epoxy resin based Epoxy Zinc phosphate primer to IS 13238 DFT- 50 μ /coat Intermediate: One coat of Two component epoxy based intermediate paint pigmented with MIO/TiO ₂ DFT- 100 μ	100 100	Finish: One coat of Epoxy based finish paint to IS 14209; DFT- 75 μ Finish: One coat of acrylic aliphatic polyurethane paint to IS 13213 DFT-25 μ Shade: Grey White, RAL9002	75 25	300

SI No	SURFACE LOCATION	PGMA	SURFACE PREPARATION	PRIMER		FINISH		TOTAL DFT IN (μ min.)
				PAINT	DFT (μ min.)	PAINT	DFT (μ min.)	
16	Expansion joint between bypass (Clause 20.03.00 of Part- C Section VI)	Flue gas swept surface	FW 251	Power Tool Cleaning to St3 (SSPC-SP3)	Red Oxide Zinc Phosphate Primer to IS: 12744 (two coats)	60	--	-- 60
		Insulated surfaces		Power Tool Cleaning to St3 (SSPC-SP3)	HR Aluminium paint to IS 13183 Gr.II (upto 400 deg C)	40	NIL	-- 40
17	Expansion joint between scrubbers (Clause 20.03.00 of Part- C Section VI)	Flue gas swept surface	FW 253	Power Tool Cleaning to St3 (SSPC-SP3)	Red Oxide Zinc Phosphate Primer to IS: 12744 (Two coats)	60	NIL	-- 60
		Insulated surfaces		Power Tool Cleaning to St3 (SSPC-SP3)	HR Aluminium paint to IS 13183 Gr.II (upto 400 deg C)	40	NIL	-- 40
18	Ducts between bypass duct inlet& booster fan (Clause 20.03.00 of Part- C Section VI)	Flue gas swept surface	FW 255	Power Tool Cleaning to St3 (SSPC-SP3)	Red Oxide Zinc Phosphate Primer to IS: 12744 (Two coats)	60	NIL	-- 60
		Insulated surfaces		Power Tool Cleaning to St3 (SSPC-SP3)	HR Aluminium paint to IS 13183 Gr.II (upto 400 deg C)	40	NIL	-- 40
19	Ducts between Booster fan& Scrubber (Clause 20.03.00 of Part- C Section VI)	Flue gas swept surface	FW 256	Power Tool Cleaning to St3 (SSPC-SP3)	Red Oxide Zinc Phosphate Primer to IS: 12744 (Two coats)	60	NIL	-- 60
		Insulated surfaces		Power Tool Cleaning to St3 (SSPC-SP3)	HR Aluminium paint to IS 13183 Gr.II (upto 400 deg C)	40	NIL	-- 40

SI No	SURFACE LOCATION	PGMA	SURFACE PREPARATION	PRIMER		FINISH		TOTAL DFT IN (μ min.)
				PAINT	DFT (μ min.)	PAINT	DFT (μ min.)	

20	Ducts between Scrubber& Stack (Clause 20.03.00 of Part- C Section VI)	FW 257	Power Tool Cleaning to St3 (SSPC-SP3)	Red Oxide Zinc Phosphate Primer to IS: 12744 (Two coats)	60	NIL	--	60
			Power Tool Cleaning to St3 (SSPC-SP3)	Red Oxide Zinc Phosphate Primer to IS: 12744 (Two coats)	60	Synthetic Enamel to IS 2932 Shade: Grey white RAL 9002 (Two coats)	40	100
21	Duct structure between ducts (Clause 31.03.00 of Sec.VI, Part-B, Subsection- IV-D)	FW 260	Blast cleaning to Sa 2½ (Near white metal) with surface profile 40-60 μ m conforming to ISO 8501-1	Primer: One coat of Two component moisture curing zinc (ethyl) silicate primer coat (Min 80% metallic zinc content in dry film, solid by volume minimum 60% ± 2). Zinc dust composition and properties shall be as per Type II as per ASTM D520-00 DFT- 70 μ Intermediate: One coat of Two component polyamide cured epoxy with MIO content (containing lamellar MIO Min 30% on pigment, solid by volume min. 80% ± 2) DFT- 100 μ	70 100	Finish: Two coats of two pack aliphatic isocyanate cured acrylic polyurethane paint to IS 13213 solid by volume min.55% ± 2) DFT- 35 μ / coat Shade: Grey white, RAL 9002 With gloss retention (SSPC paint spec no.36, ASTM D4587, D2244, D523 of level 2 after min. 1000 hrs exposure, gloss less than 30 and colour change less than 2.0 Δ E)	70	240
22	Duct structure between scrubber (Clause 31.03.00 of Sec.VI, Part-B, Subsection- IV-D)	FW 261	Blast cleaning to Sa 2½ (Near white metal) with surface profile 40-60 μ m conforming to ISO 8501-1	Primer: One coat of Two component moisture curing zinc (ethyl) silicate primer coat (Min 80% metallic zinc content in dry film, solid by volume minimum 60% ± 2). Zinc dust composition and properties shall be as per Type II as per ASTM D520-00 DFT- 70 μ Intermediate: One coat of Two component polyamide cured epoxy	70 100	Finish: Two coats of two pack aliphatic isocyanate cured acrylic polyurethane paint to IS 13213 solid by volume min.55% ± 2) DFT- 35 μ / coat Shade: Grey white, RAL 9002 With gloss retention (SSPC paint spec no.36, ASTM D4587, D2244, D523 of level 2 after min. 1000 hrs	70	240

SI No	SURFACE LOCATION	PGMA	SURFACE PREPARATION	PRIMER		FINISH		TOTAL DFT IN (μ min.)
				PAINT	DFT (μ min.)	PAINT	DFT (μ min.)	
				with MIO content (containing lamellar MIO Min 30% on pigment, solid by volume min. 80% \pm 2) DFT- 100 μ		exposure, gloss less than 30 and colour change less than 2.0 Δ E)		
23	Duct structure between scrubber (Clause 31.03.00 of Sec.VI, Part-B, Subsection- IV-D)	FW 262	Blast cleaning to Sa 2½ (Near white metal) with surface profile 40-60 μ m conforming to ISO 8501-1	Primer: One coat of Two component moisture curing zinc (ethyl) silicate primer coat (Min 80% metallic zinc content in dry film, solid by volume minimum 60% \pm 2). Zinc dust composition and properties shall be as per Type II as per ASTM D520-00 DFT- 70 μ Intermediate: One coat of Two component polyamide cured epoxy with MIO content (containing lamellar MIO Min 30% on pigment, solid by volume min. 80% \pm 2) DFT- 100 μ	70 100	Finish: Two coats of two pack aliphatic isocyanate cured acrylic polyurethane paint to IS 13213 solid by volume min.55% \pm 2) DFT- 35 μ / coat Shade: Grey white, RAL 9002 With gloss retention (SSPC paint spec no.36, ASTM D4587, D2244, D523 of level 2 after min. 1000 hrs exposure, gloss less than 30 and colour change less than 2.0 Δ E)	70	240

SI No	SURFACE LOCATION	PGMA	SURFACE PREPARATION	PRIMER		FINISH		TOTAL DFT IN (μ min.)
				PAINT	DFT (μ min.)	PAINT	DFT (μ min.)	
24	Foundation material for duct structures, scrubbers, Elevators, tanks, pipe racks	FW 280 FW 281 FW 282 FW 740 FW 763		Temporary rust preventive fluid application as per PRQA 523 DFT- 20 μ All Threaded and other surfaces of foundation bolt and its materials shall be coated with temporary rust preventive fluid. During execution of civil works the dried film of coating will be removed using Organic Solvents.				
25	Structures for Elevator (Clause 31.03.00 of Sec.VI, Part-B, Subsection- IV-D)	FW 292	Blast cleaning to Sa 2½ (Near white metal) with surface profile 40-60 μ m conforming to ISO 8501-1	Primer: One coat of Two component moisture curing zinc (ethyl) silicate primer coat (Min 80% metallic zinc content in dry film, solid by volume minimum 60% ± 2). Zinc dust composition and properties shall be as per Type II as per ASTM D520-00 DFT- 70 μ Intermediate: One coat of Two component polyamide cured epoxy with MIO content (containing lamellar MIO Min 30% on pigment, solid by volume min. 80% ± 2) DFT- 100 μ	70 100	Finish: Two coats of two pack aliphatic isocyanate cured acrylic polyurethane paint to IS 13213 solid by volume min.55% ± 2) DFT- 35 μ / coat Shade: Grey white, RAL 9002 With gloss retention (SSPC paint spec no.36, ASTM D4587, D2244, D523 of level 2 after min. 1000 hrs exposure, gloss less than 30 and colour change less than 2.0 Δ E)	70	240
26	Elevator and accessories (Clause 20.03.00 of Part- C Section VI)	FW 293 FW 716	Power Tool Cleaning to st3 (SSPC-SP3)	Red Oxide Zinc Phosphate Primer to IS: 12744 (Two coats)	60	Synthetic Enamel to IS 2932 Shade: Grey white RAL 9002 (Two coats)	60	120

SI No	SURFACE LOCATION	PGMA	SURFACE PREPARATION	PRIMER		FINISH		TOTAL DFT IN (μ min.)
				PAINT	DFT (μ min.)	PAINT	DFT (μ min.)	

27	Structures for booster fan handling (Clause 31.03.00 of Sec.VI, Part-B, Subsection- IV-D)	FW 310	Blast cleaning to Sa 2½ (Near white metal) with surface profile 40-60 μ m conforming to ISO 8501-1	Primer: One coat of Two component moisture curing zinc (ethyl) silicate primer coat (Min 80% metallic zinc content in dry film, solid by volume minimum 60% ± 2). Zinc dust composition and properties shall be as per Type II as per ASTM D520-00 DFT- 70 μ Intermediate: One coat of Two component polyamide cured epoxy with MIO content (containing lamellar MIO Min 30% on pigment, solid by volume min. 80% ± 2) DFT- 100 μ	70 100	Finish: Two coats of two pack aliphatic isocyanate cured acrylic polyurethane paint to IS 13213 solid by volume min.55% $\pm 2DFT- 35\mu/ coatShade: Grey white, RAL 9002With gloss retention (SSPC paint spec no.36, ASTM D4587, D2244, D523 of level 2 after min. 1000 hrs exposure, gloss less than 30 and colour change less than 2.0\Delta E)$	70	240
28	Handling Equipment- Booster Fan (Clause 20.03.00 of Part-C Section VI)	FW 311	Power Tool Cleaning to st3 (SSPC-SP3)	Red Oxide Zinc Phosphate Primer to IS: 12744 (Two coats)	60	Synthetic Enamel to IS 2932 Shade: Grey white RAL 9002 (Two coats)	60	120
29	Miscellaneous – FGD system (Clause 20.03.00 of Part-C Section VI)	FW 314	Power Tool Cleaning to st3 (SSPC-SP3)	Red Oxide Zinc Phosphate Primer to IS: 12744 (Two coats)	60	Synthetic Enamel to IS 2932 Shade: Grey white RAL 9002 (Two coats)	40	100
30	Galleries and railings for Scrubbers, Tanks, Stair (Clause 31.06.00 of Sec.VI, Part-B, Subsection- IV-D)	FW 237 FW 610 FW 722	Blast cleaning to Sa 2½/ Acid pickling	Hand rails, Gratings- Hot dip galvanizing to 610gms/sq.m (minimum) and to a coating thickness of 87 μ m (minimum)				

SI No	SURFACE LOCATION	PGMA	SURFACE PREPARATION	PRIMER		FINISH		TOTAL DFT IN (μ min.)
				PAINT	DFT (μ min.)	PAINT	DFT (μ min.)	
31	Galleries and railings for Scrubbers, Tanks, Stair – Structures other than the above (Clause 31.03.00 of Sec.VI, Part-B, Subsection- IV-D)	FW 237 FW 610 FW 722	Blast cleaning to Sa 2½ (Near white metal) with surface profile 40-60 μ m conforming to ISO 8501-1	Primer: One coat of Two component moisture curing zinc (ethyl) silicate primer coat (Min 80% metallic zinc content in dry film, solid by volume minimum 60% ± 2). Zinc dust composition and properties shall be as per Type II as per ASTM D520-00 DFT- 70 μ Intermediate: One coat of Two component polyamide cured epoxy with MIO content (containing lamellar MIO Min 30% on pigment, solid by volume min. 80% ± 2) DFT- 100 μ	70 100	Finish: Two coats of two pack aliphatic isocyanate cured acrylic polyurethane paint to IS 13213 solid by volume min.55% ± 2 DFT- 35 μ / coat Shade: Grey white, RAL 9002 With gloss retention (SSPC paint spec no.36, ASTM D4587, D2244, D523 of level 2 after min. 1000 hrs exposure, gloss less than 30 and colour change less than 2.0 Δ E)	70	240
32	Slurry pumps & accessories. (Referred from cl. 7.05.00 of Section-VI, Part-B, Sub section-I-M5)	FW 701	Power Tool Cleaning to St3 (SSPC-SP3)	Primer: Red Oxide Zinc Phosphate Primer to IS: 12744 (Two coats) Intermediate: One coat of Synthetic Enamel intermediate coat to IS 2932; DFT- 50 μ	60 50	Two coats of Synthetic Enamel to IS 2932, DFT- 50 μ / coat Shade: Light blue RAL 5012	100	210
33	Monorail for hoist & cranes (Clause 31.03.00 of Sec.VI, Part-B, Subsection- IV-D)	FW 710	Blast cleaning to Sa 2½ (Near white metal) with surface profile 40-60 μ m conforming to ISO 8501-1	Primer: One coat of Two component moisture curing zinc (ethyl) silicate primer coat (Min 80% metallic zinc content in dry film, solid by volume minimum 60% ± 2). Zinc dust composition and properties shall be as per Type II as per ASTM D520-00 DFT- 70 μ Intermediate: One coat of Two component polyamide cured epoxy with MIO content (containing lamellar MIO Min 30% on pigment, solid by volume min. 80% ± 2) DFT- 100 μ	70 100	Finish: Two coats of two pack aliphatic isocyanate cured acrylic polyurethane paint to IS 13213 solid by volume min.55% ± 2 DFT- 35 μ / coat Shade: Grey white, RAL 9002 With gloss retention (SSPC paint spec no.36, ASTM D4587, D2244, D523 of level 2 after min. 1000 hrs exposure, gloss less than 30 and colour change less than 2.0 Δ E)	70	240

SI No	SURFACE LOCATION	PGMA	SURFACE PREPARATION	PRIMER		FINISH		TOTAL DFT IN (μ min.)
				PAINT	DFT (μ min.)	PAINT	DFT (μ min.)	
34	Handling Equipment in FGD (Clause 20.03.00 of Part-C Section VI)	FW 715	Power Tool Cleaning to st3 (SSPC-SP3)	Red Oxide Zinc Phosphate Primer to IS: 12744 (Two coats) Idler roller shall be applied with two coats of 70 microns at shop	70	Synthetic Enamel to IS 2932 Shade: Grey white RAL 9002 (Two coats)	60	130
35	Agitator support Clause 31.03.00 of Sec.VI, Part-B, Subsection- IV-D)	FW 721	Blast cleaning to Sa 2½ (Near white metal) with surface profile 40-60 μ m conforming to ISO 8501-1	Primer: One coat of Two component moisture curing zinc (ethyl) silicate primer coat (Min 80% metallic zinc content in dry film, solid by volume minimum 60% ± 2). Zinc dust composition and properties shall be as per Type II as per ASTM D520-00 DFT- 70 μ Intermediate: One coat of Two component polyamide cured epoxy with MIO content (containing lamellar MIO Min 30% on pigment, solid by volume min. 80% ± 2) DFT- 100 μ	70 100	Finish: Two coats of two pack aliphatic isocyanate cured acrylic polyurethane paint to IS 13213 solid by volume min.55% ± 2) DFT- 35 μ / coat Shade: Grey white, RAL 9002 With gloss retention (SSPC paint spec no.36, ASTM D4587, D2244, D523 of level 2 after min. 1000 hrs exposure, gloss less than 30 and colour change less than 2.0 Δ E)	70	240
36	Limestone silo structures Clause 31.03.00 of Sec.VI, Part-B, Subsection- IV-D)	FW 730	Blast cleaning to Sa 2½ (Near white metal) with surface profile 40-60 μ m conforming to ISO 8501-1	Primer: One coat of Two component moisture curing zinc (ethyl) silicate primer coat (Min 80% metallic zinc content in dry film, solid by volume minimum 60% ± 2). Zinc dust composition and properties shall be as per Type II as per ASTM D520-00 DFT- 70 μ Intermediate: One coat of Two component polyamide cured epoxy with MIO content (containing lamellar MIO Min 30% on pigment, solid by volume min. 80% ± 2) DFT- 100 μ	70 100	Finish: Two coats of two pack aliphatic isocyanate cured acrylic polyurethane paint to IS 13213 solid by volume min.55% ± 2) DFT- 35 μ / coat Shade: Grey white, RAL 9002 With gloss retention (SSPC paint spec no.36, ASTM D4587, D2244, D523 of level 2 after min. 1000 hrs exposure, gloss less than 30 and colour change less than 2.0 Δ E)	70	240

SI No	SURFACE LOCATION	PGMA	SURFACE PREPARATION	PRIMER		FINISH		TOTAL DFT IN (μ min.)
				PAINT	DFT (μ min.)	PAINT	DFT (μ min.)	
37	Limestone Silo- Outside surfaces Clause 31.03.00 of Sec.VI, Part-B, Subsection- IV-D)	FW 731	Blast cleaning to Sa 2½ (Near white metal) with surface profile 40-60 μ m conforming to ISO 8501-1	Primer: One coat of Two component moisture curing zinc (ethyl) silicate primer coat (Min 80% metallic zinc content in dry film, solid by volume minimum 60% ± 2). Zinc dust composition and properties shall be as per Type II as per ASTM D520-00 DFT- 70 μ Intermediate: One coat of Two component polyamide cured epoxy with MIO content (containing lamellar MIO Min 30% on pigment, solid by volume min. 80% ± 2) DFT- 100 μ	70 100	Finish: Two coats of two pack aliphatic isocyanate cured acrylic polyurethane paint to IS 13213 solid by volume min.55% $\pm 2DFT- 35\mu/ coatShade: Grey white, RAL 9002With gloss retention (SSPC paint spec no.36, ASTM D4587, D2244, D523 of level 2 after min. 1000 hrs exposure, gloss less than 30 and colour change less than 2.0\Delta E)$	70	240
38	Lime stone Silo- Inside surfaces (Conical portion)	FW 731	Blast cleaning to Sa 2½ (Near white metal) with surface profile 35-50 μ m conforming to ISO 8501-1	Primer: Two coats of Red Oxide Zinc phosphate primer to IS: 12744 (SS lining is inside the Limestone silo conical portion, hence primer is only envisaged; SS lining will be done at shops itself)	60	NIL	--	60
39	Lime stone Silo- Inside surfaces (Cylindrical portion)	FW 731	Blast cleaning to Sa 2½ (Near white metal) with surface profile 40-60 μ m conforming to ISO 8501-1	Primer Coat: One coat of two component moisture curing Inorganic Ethyl Zinc Silicate Primer to IS 14946, (Solid by volume- 60% (min)), (Metallic zinc content 80% (min)) DFT = 70 μ m per coat (min.) Zinc dust composition shall be Type-II as per ASTM D520-00	70	--	--	70
40	Limestone silo & Tank accessories (Clause 20.03.00 of Part-C Section VI)	FW 732 FW 750	Power Tool Cleaning to St3 (SSPC-SP3)	Red Oxide Zinc Phosphate Primer to IS: 12744 (Two coats)	60	Synthetic Enamel to IS 2932 Shade: Grey white RAL 9002 (Two coats)	40	100

SI No	SURFACE LOCATION	PGMA	SURFACE PREPARATION	PRIMER		FINISH		TOTAL DFT IN (μ min.)
				PAINT	DFT (μ min.)	PAINT	DFT (μ min.)	
41	Limestone silo approach platform, Platform for Pipe racks (Clause 31.06.00 of Sec.VI, Part-B, Subsection- IV-D)	FW 733 FW 766	Blast cleaning to Sa 2½/ Acid pickling	Hand rails, Ladders, Gratings- Hot dip galvanizing to 610gms/sq. m (minimum) and to a coating thickness of 87 μ m (minimum)				
42	Limestone silo approach platform, Pipe racks platform- Structures other than the above (Clause 31.03.00 of Sec.VI, Part-B, Subsection- IV-D)	FW 733 FW 766	Blast cleaning to Sa 2½ (Near white metal) with surface profile 40-60 μ m conforming to ISO 8501-1	Primer: One coat of Two component moisture curing zinc (ethyl) silicate primer coat (Min 80% metallic zinc content in dry film, solid by volume minimum 60% ± 2). Zinc dust composition and properties shall be as per Type II as per ASTM D520-00 DFT- 70 μ Intermediate: One coat of Two component polyamide cured epoxy with MIO content (containing lamellar MIO Min 30% on pigment, solid by volume min. 80% ± 2) DFT- 100 μ	70 100	Finish: Two coats of two pack aliphatic isocyanate cured acrylic polyurethane paint to IS 13213 solid by volume min.55% ± 2 DFT- 35 μ / coat Shade: Grey white, RAL 9002 With gloss retention (SSPC paint spec no.36, ASTM D4587, D2244, D523 of level 2 after min. 1000 hrs exposure, gloss less than 30 and colour change less than 2.0 Δ E)	70	240
43	Limestone Mill – Outside surfaces (Clause 1.04.00 of Part- B Section VI)	FW 734	Blast cleaning to Sa 2½	Primer: Two coats of Epoxy resin based Epoxy Zinc phosphate primer to IS 13238 DFT- 50 μ /coat Intermediate: One coat of Two component epoxy based intermediate paint pigmented with MIO/TiO ₂ DFT- 100 μ	100 100	Finish: One coat of Epoxy based finish paint to IS 14209; DFT- 75 μ Finish: One coat of acrylic aliphatic polyurethane paint to IS 13213 DFT-25 μ Shade: Grey White, RAL9002	75 25	300
44	Lime stone mill- Inside surfaces	FW 734	Blast cleaning to Sa 2½ (Near white metal)	Primer Coat: One coat of two component moisture curing Inorganic Ethyl Zinc Silicate Primer to IS 14946,	70	--	--	70

SI No	SURFACE LOCATION	PGMA	SURFACE PREPARATION	PRIMER		FINISH		TOTAL DFT IN (μ min.)
				PAINT	DFT (μ min.)	PAINT	DFT (μ min.)	

			with surface profile 40-60 μ m conforming to ISO 8501-1	(Solid by volume- 60% (min)), (Metallic zinc content 80% (min)) DFT = 70 μ m per coat (min.) Zinc dust composition shall be Type-II as per ASTM D520-00				
45	Primary Hydro cyclone and accessories Structural items (Clause 1.04.00 of Part- B Section VI)	FW 736	Blast cleaning to Sa 2½	Primer: Two coats of Epoxy resin based Epoxy Zinc phosphate primer to IS 13238 DFT- 50 μ /coat Intermediate: One coat of Two component epoxy based intermediate paint pigmented with MIO/TiO2 DFT- 100 μ	100 100	Finish: One coat of Epoxy based finish paint to IS 14209; DFT- 75 μ Finish: One coat of acrylic aliphatic polyurethane paint to IS 13213 DFT-25 μ Shade: Grey White, RAL9002	75 25	300
46	Secondary Hydro cyclone and accessories Structural items (Clause 1.04.00 of Part- B Section VI)	FW 737	Blast cleaning to Sa 2½	Primer: Two coats of Epoxy resin based Epoxy Zinc phosphate primer to IS 13238 DFT- 50 μ /coat Intermediate: One coat of Two component epoxy based intermediate paint pigmented with MIO/TiO2 DFT- 100 μ	100 100	Finish: One coat of Epoxy based finish paint to IS 14209; DFT- 75 μ Finish: One coat of acrylic aliphatic polyurethane paint to IS 13213 DFT-25 μ Shade: Grey White, RAL9002	75 25	300
47	Gypsum belt filter and accessories Structural items (Clause 1.04.00 of Part- B Section VI)	FW 738	Blast cleaning to Sa 2½	Primer: Two coats of Epoxy resin based Epoxy Zinc phosphate primer to IS 13238 DFT- 50 μ /coat Intermediate: One coat of Two component epoxy based	100 100	Finish: One coat of Epoxy based finish paint to IS 14209; DFT- 75 μ	75 25	300

SI No	SURFACE LOCATION	PGMA	SURFACE PREPARATION	PRIMER		FINISH		TOTAL DFT IN (μ min.)
				PAINT	DFT (μ min.)	PAINT	DFT (μ min.)	

				intermediate paint pigmented with MIO/Tio2 DFT- 100 μ		Finish: One coat of acrylic aliphatic polyurethane paint to IS 13213 DFT-25 μ Shade: Grey White, RAL9002		
48	Lime stone slurry storage tank, Auxiliary absorber tank, Filtrate tank, Wastage water tank, Hydro cyclone waste water tank, Process Water tank, Belt filter washing tank, Primary Hydro cyclone feed tank Outside surfaces (Clause 31.03.00 of Sec.VI, Part-B, Subsection- IV-D)	FW 742 FW 743 FW 744 FW 745 FW 747 FW 748 FW 785 FW 786	Blast cleaning to Sa 2½ (Near white metal) with surface profile 40-60 μ m conforming to ISO 8501-1	Primer: One coat of Two component moisture curing zinc (ethyl) silicate primer coat (Min 80% metallic zinc content in dry film, solid by volume minimum 60% ± 2). Zinc dust composition and properties shall be as per Type II as per ASTM D520-00 DFT- 70 μ Intermediate: One coat of Two component polyamide cured epoxy with MIO content (containing lamellar MIO Min 30% on pigment, solid by volume min. 80% ± 2) DFT- 100 μ	70 100	Finish: Two coats of two pack aliphatic isocyanate cured acrylic polyurethane paint to IS 13213 solid by volume min.55% ± 2) DFT- 35 μ / coat Shade: Grey white, RAL 9002 With gloss retention (SSPC paint spec no.36, ASTM D4587, D2244, D523 of level 2 after min. 1000 hrs exposure, gloss less than 30 and colour change less than 2.0 Δ E)	70	240
49	Lime stone slurry storage tank, Auxiliary absorber tank, Filtrate tank, Wastage water tank, Hydrocyclone waste water tank, Process Water tank, Belt filter washing tank, Primary Hydro cyclone feed tank Inside surfaces	FW 742 FW 743 FW 744 FW 745 FW 747 FW 748 FW 785 FW 786	Blast cleaning to Sa 2½ (Near white metal) with surface profile 35-50 μ m	Red Oxide Zinc Phosphate Primer to IS: 12744 (Two coats) (Liner is inside the tank, hence primer is only envisaged; Protection till erection only)	60	NIL	--	60

SI No	SURFACE LOCATION	PGMA	SURFACE PREPARATION	PRIMER		FINISH		TOTAL DFT IN (μ min.)
				PAINT	DFT (μ min.)	PAINT	DFT (μ min.)	

50	Process water pipe accessories (Referred from cl. 7.05.00 of Section-VI, Part-B, Sub section-I-M5)	FW 751	Power Tool Cleaning to St3 (SSPC-SP3)	Primer: Red Oxide Zinc Phosphate Primer to IS: 12744 (Two coats) Intermediate: One coat of Synthetic Enamel intermediate coat to IS 2932; DFT- 50 μ	60 50	Two coats of Synthetic Enamel to IS 2932, DFT- 50 μ / coat Shade: Grey white RAL 9002 Identification Tag: Sea Green Shade no: 217 as per IS 5	100	210
51	Slurry pipe accessories (Referred from cl. 7.05.00 of Section-VI, Part-B, Sub section-I-M5)	FW 753	Power Tool Cleaning to St3 (SSPC-SP3)	Primer: Red Oxide Zinc Phosphate Primer to IS: 12744 (Two coats) Intermediate: One coat of Synthetic Enamel intermediate coat to IS 2932; DFT- 50 μ	60 50	Two coats of Synthetic Enamel to IS 2932, DFT- 50 μ / coat Shade: Grey white RAL 9002 Identification Tag: Sea Green Shade no: 217 as per IS 5	100	210
52	Service Air pipe accessories (Referred from cl. 10.00 .00 of Section-VI, Part-B, Sub section-I-M3)	FW 754	Power Tool Cleaning to St3 (SSPC-SP3)	Red Oxide Zinc Phosphate Primer to IS: 12744 (Two coat)	60	Synthetic Enamel to IS 2932 Shade: Grey white RAL 9002 (Two coats)- 30 μ / coat Identification Tag: Sky Blue Shade no: 101 as per IS 5	60	120
53	Instrument air pipe accessories (Referred from cl. 10.00 .00 of Section-VI, Part-B, Sub section-I-M3)	FW 755	Power Tool Cleaning to St3 (SSPC-SP3)	Red Oxide Zinc Phosphate Primer to IS: 12744 (Two coat)	60	Synthetic Enamel to IS 2932 Shade: Grey white RAL 9002 (Two coats)- 30 μ / coat Identification Tag: Sky Blue Shade no: 101 as per IS 5	60	120
54	Valves and fittings (Temp <95 deg C)	FW 758	Power Tool Cleaning to St3 (SSPC-SP3)	Red Oxide Zinc Phosphate Primer to IS: 12744 (Two coats)	60	Synthetic Enamel to IS 2932 Shade: Grey white RAL 9002 (Two coats)- 30 μ / coat	60	120

SI No	SURFACE LOCATION	PGMA	SURFACE PREPARATION	PRIMER		FINISH		TOTAL DFT IN (μ min.)
				PAINT	DFT (μ min.)	PAINT	DFT (μ min.)	
55	Structure for Pipe racks Trestle for pipe racks (Clause 31.03.00 of Sec.VI, Part-B, Subsection- IV-D)	FW 761 FW 769	Blast cleaning to Sa 2½ (Near white metal) with surface profile 40-60 μ m conforming to ISO 8501-1	Primer: One coat of Two component moisture curing zinc (ethyl) silicate primer coat (Min 80% metallic zinc content in dry film, solid by volume minimum 60% ± 2). Zinc dust composition and properties shall be as per Type II as per ASTM D520-00 DFT- 70 μ Intermediate: One coat of Two component polyamide cured epoxy with MIO content (containing lamellar MIO Min 30% on pigment, solid by volume min. 80% ± 2) DFT- 100 μ	70 100	Finish: Two coats of two pack aliphatic isocyanate cured acrylic polyurethane paint to IS 13213 solid by volume min.55% ± 2 DFT- 35 μ / coat Shade: Grey white, RAL 9002 With gloss retention (SSPC paint spec no.36, ASTM D4587, D2244, D523 of level 2 after min. 1000 hrs exposure, gloss less than 30 and colour change less than 2.0 Δ E)	70	240
56	Structures inside Gypsum dewatering building & Ball Mill Building (Referred from cl. 7.05.00 of Section-VI, Part-B, Sub section-I-M5)	FW 787	Power Tool Cleaning to St3 (SSPC-SP3)	Primer: Red Oxide Zinc Phosphate Primer to IS: 12744 (Two coats) Intermediate: One coat of Synthetic Enamel intermediate coat to IS 2932; DFT- 50 μ	60 50	Two coats of Synthetic Enamel to IS 2932, DFT- 50 μ / coat Shade: Grey White RAL 9002	100	210
57	Supports for Cable trays, Tools, Air receivers, (Clause 20.03.00 of Part-C Section VI)	FW 779 FW 790 FW 798	Power Tool Cleaning to St3 (SSPC-SP3)	Red Oxide Zinc Phosphate Primer to IS: 12744 (Two coats)	60	Synthetic Enamel to IS 2932 Shade: Grey white RAL 9002 (Two coats)	40	100

SI No	SURFACE LOCATION	PGMA	SURFACE PREPARATION	PRIMER		FINISH		TOTAL DFT IN (μ min.)
				PAINT	DFT (μ min.)	PAINT	DFT (μ min.)	

3. GATES & DAMPERS

01	Gates & Dampers > 95° C Insulated Surfaces & Uninsulated surfaces	57 540 57 550 57 583	Power Tool Cleaning to St3 (SSPC-SP3)	HR Aluminium paint to IS 13183 Gr.II (upto 400 deg C)	40	--	--	40
02	Seal air piping (Referred from cl. 10.00 .00 of Section-VI, Part-B, Sub Section-I-M3)	57 141	Power Tool Cleaning to St3 (SSPC-SP3)	Red Oxide Zinc Phosphate Primer to IS: 12744 (Two coat)	60	Synthetic Enamel to IS 2932 Shade: Grey white RAL 9002 (Two coats)- 30 μ / coat Identification Tag: Sky Blue Shade no: 101 as per IS 5	60	120
03	Blower with Motor Knife Gate valve Mounting bracket	57 491 57 497 57 209	Power Tool Cleaning to St3 (SSPC-SP3)	Red Oxide Zinc Phosphate Primer to IS: 12744 (Two coats)	60	Synthetic Enamel to IS 2932 Shade: Grey white RAL 9002 (Two coats)	40	100
04	Ladder, Cage for Ladder Toe Guard Plate Floor Grill, Hand Rails, Hand Rail Post Clause 31.06.00 of Sec.VI, Part-B, Subsection- IV-D	57 566	Blast cleaning to Sa 2½/ Acid Pickling	Hot Dip Galvanizing to 610 gm per sq. Meter (minimum) and to a coating thickness of 87 μ (minimum)				
05	Other Structural Items- Other than sl.no. 3 of above (Clause 31.03.00 of Sec.VI, Part-B, Subsection- IV-D)	57 566	Blast cleaning to Sa 2½ (Near white metal) with surface profile 40- 60 μ m conforming to ISO 8501-1	Primer: One coat of Two component moisture curing zinc (ethyl) silicate primer coat (Min 80% metallic zinc content in dry film, solid by volume minimum 60% ± 2). Zinc dust composition and properties shall be as per Type II as per ASTM D520-00 DFT- 70 μ	70	Finish: Two coats of two pack aliphatic isocyanate cured acrylic polyurethane paint to IS 13213 solid by volume min.55% ± 2) DFT- 35 μ / coat Shade: Grey white, RAL 9002	70	240

SI No	SURFACE LOCATION	PGMA	SURFACE PREPARATION	PRIMER		FINISH		TOTAL DFT IN (μ min.)
				PAINT	DFT (μ min.)	PAINT	DFT (μ min.)	

				Intermediate: One coat of Two component polyamide cured epoxy with MIO content (containing lamellar MIO Min 30% on pigment, solid by volume min. 80% \pm 2) DFT- 100 μ	100	With gloss retention (SSPC paint spec no.36, ASTM D4587, D2244, D523 of level 2 after min. 1000 hrs exposure, gloss less than 30 and colour change less than 2.0 Δ E)		
--	--	--	--	---	-----	--	--	--

SI No	SURFACE LOCATION	PGMA	SURFACE PREPARATION	PRIMER		FINISH		TOTAL DFT IN (μ min.)
				PAINT	DFT (μ min.)	PAINT	DFT (μ min.)	

4. PAINTING OF DAMAGED AREAS

Areas where paint has deteriorated badly by erosion and areas where the paint film has lost its adhesion property and where the steel has got rusted appreciably - these areas are to be repainted as per the following procedure:

SL NO	SURFACE LOCATION	SURFACE PREPARATION	PRIMER, INTERMEDIATE & FINISH
1	Paint damaged Components falling under Sl.no. 04,05,06,09,10,11 of Fans, Sl no. 01,02,03,04, 05,06,07, 09, 13, 14, 15, 21, 22, 23,25, 27, 31, 33,35, 36, 37, 42,43, 45,46, 47, 48, 55 of FGD and Sl no. 5 of GAD.	Hand/ Power Tool cleaning to Bare metal to minimum 6 inches peripheral area adjoining to damaged area	Primer: Epoxy Zinc rich primer to IS 14589, DFT-70 μ (If Metal surface exposed) followed by intermediate & finish coat as per respective scheme If primer is intact- Intermediate & finish as per respective scheme
2	Paint damaged components failing under other Sl.nos of Fans, FGD& GAD	Power Tool Cleaning to Bare metal	Primer and Finish : As given in respective scheme

SI No	SURFACE LOCATION	PGMA	SURFACE PREPARATION	PRIMER		FINISH		TOTAL DFT IN (μ m min.)
				PAINT	DFT (μ m min.)	PAINT	DFT (μ m min.)	

GENERAL NOTES

1. No painting is required for Galvanized, non-ferrous & stainless steel items, except as indicated above.
2. Machined items are to be applied with coat of temporary rust preventive oil
3. PGAs covered in sub-supplier (ie., Purchased) items viz., Agitator/ slide bearing and other sub-delivery components etc., are not indicated in the above list. However, the Painting Schedule for all items supplied by all sub-suppliers and BOI under the scope of BHEL shall be same as for main equipment covered in this document.
4. In sub-assy, wherever plates / sheets of thickness less than or equal to 5mm and rods are used - Power Tool or Hand Tool Cleaning to SSPC - SP 3 / SP 2 shall be followed and painting under SI no:01 of Fans shall be followed.
5. Ground shade/colour of finish paints and identification tag/band for equipments, fans, piping, pipe services, supporting structures and other components is followed as per NTPC doc no: QS-01-DIV-W-4 at site.
6. All components covered under different PGAs are to be painted. In case any component is left out, the same shall be deemed to be included under the relevant section.
7. All threaded and other surfaces of foundation bolts and its materials, insulation pins, Anchor channels, Sleeves shall be coated with temporary rust preventive fluid and during execution of civil works; the dried film of coating shall be removed using organic solvents.
8. Painting requirement for all electrical equipment shall be as per the details identified in specification for the respective equipment.
9. All steel structures shall be provided with painting as given in the specification. Further, painting system shall also meet the requirements of corrosivity category C3 (durability high) as per ISO 12944.
10. Finish coat to be applied after an interval of min 10 hrs and within 6 months (after completion of intermediate coat).
11. Primer coat on steel shall be applied in shop immediately after blast cleaning by airless spray technique.
12. For the portion of steel surfaces embedded in concrete, the surface shall be prepared by Manual cleaning and provided with Primer coat of Chlorinated Rubber based Zinc Phosphate Primer of Minimum 50 Micron DFT.

SI No	SURFACE LOCATION	PGMA	SURFACE PREPARATION	PRIMER		FINISH		TOTAL DFT IN (μ min.)
				PAINT	DFT (μ min.)	PAINT	DFT (μ min.)	

PAINTING SCHEME- DETAILS OF PROCUREMENT & APPLICATION PROCESSES

SL NO	TYPE OF PAINT	SPECIFICATION OF PAINT	NO OF PACK	VOLUME OF SOLIDS (% Min)	MODE OF APPLICATION	MIN. OVER COATING INTERVAL (hours)	SHADE
01	Epoxy Zinc phosphate primer	IS 13238	2	40	Spray	24	Grey
02	Zinc Ethyl silicate primer (% Zn on dry film= 80 (min))	IS 14946	2	60	Airless Spray only At Shop	24	Grey
03	Epoxy High solid-Polyamide cured Epoxy based MIO pigmented intermediate coat	--	2	80	Airless Spray only At Shop	16	Brown
04	Epoxy based finish paint	IS 14209	2	62	Spray	16	Corresponding shade no
05	Aliphatic isocyanate acrylic polyurethane paint	IS 13213	2	55	Spray At Shop	16	Corresponding shade no
06	Heat resistant aluminium paint	IS 13183 Grade II	1	--	Brush/ Spray	24	--
07	Long oil alkyd Synthetic enamel finish paint	IS 2932	1	35	Brush/ Spray	12	Corresponding shade no
08	Synthetic Enamel undercoat	IS 2932	1	40	Brush/Spray	12	
09	Red oxide Zinc phosphate primer	IS 12744	1	--	Brush/ spray	12	--

SI No	SURFACE LOCATION	PGMA	SURFACE PREPARATION	PRIMER		FINISH		TOTAL DFT IN (μ m min.)
				PAINT	DFT (μ m min.)	PAINT	DFT (μ m min.)	

PGMA DETAILS

SNO	PGMA	PGMA DESCRIPTION	PGMA DETAILS
01	FW 212	Slurry recirculation pump system	RC Pumps incl Shaft seal Common Base Plate Coupling and Guard Gear Box Expansion Bellow Anchor Bolts & Fasteners Special Tools
02	FW 219	Absorber system base	Absorber tank bottom plate
03	FW 220	Absorber system structures	Absorber tank structure Absorber tower structure Spray headers structure
04	FW 221	Absorber system casing bottom	Absorber tank wall casing- bottom
05	FW 222	Absorber system casing top	Absorber Tank wall casing –Top Mist Eliminator supports Spray pipe supports Internal Beam Shim plates in Absorber area Internal Struts
06	FW 223	Absorber system accessories	Nozzles and flanges Inspection doors & Man holes Viewing ports Antifoam dosing equipment Suction strainers- FRP
07	FW 226	Emergency Quench water tank	Base Plate & its supports Roof, Shell
08	FW 227	Emergency Quench System	Emergency Quenching Spray Pipe Nozzle for Emergency Pipe Fasteners Gaskets
09	FW 230	Air oxidation System	Oxidation Blowers Common Base Plate Coupling and Guard Anchor Bolts & Fasteners Expansion Bellow Suction & Discharge Silencers Acoustic Enclosure Water Injection cooling system

SI No	SURFACE LOCATION	PGMA	SURFACE PREPARATION	PRIMER		FINISH		TOTAL DFT IN (μ min.)
				PAINT	DFT (μ min.)	PAINT	DFT (μ min.)	

		Pipe, Valves & Instruments Special Tools
--	--	---

SNO	PGMA	PGMA DESCRIPTION	PGMA DETAILS
10	FW 244	Oxidation air distribution System	Pipe & Fittings Flanges Pipe Hanger, Bottom Elbow, Bottom sliding supports
11	FW 251	Expansion joint between bypass	Expansion joints Seal Plates & Fasteners
12	FW 253	Expansion joint between scrubbers	Fabric & its fixing fasteners Sleeves & Flanges Gaskets
13	FW 255	Ducts between bypass duct inlet & booster fan	Plates & Stiffeners Guide Vanes
14	FW 256	Ducts between Booster fan & Scrubber	Plates & Stiffeners Guide Vanes
15	FW 257	Ducts between scrubber & stack	Plates & Stiffeners Guide Vanes
16	FW 260	Duct structure between ducts	Duct Supports Gusset Plate Divider plate Internal Struts Support bearings
17	FW 261 FW 262	Duct structure between scrubber	Duct Supports Gusset Plate Divider plate Internal Struts Support bearings
18	FW 292	Structures for Elevator	Columns Seal Plate Bracings Enclosure (Purlin& sheeting)
19	FW 293	Elevator and accessories	Base Frame Buffer Spring Mast Section Cage Control Panel & AC Mandatory Spares

SI No	SURFACE LOCATION	PGMA	SURFACE PREPARATION	PRIMER		FINISH		TOTAL DFT IN (μ min.)
				PAINT	DFT (μ min.)	PAINT	DFT (μ min.)	

SNO	PGMA	PGMA DESCRIPTION	PGMA DETAILS
20	FW 310	Structures for booster fan handling	Columns Beams Bracings Seal plate
21	FW 311	Handling Equipment- Booster fan	Electric hoist
22	FW 314	Miscellaneous- FGD system	Services & other small items like vents, over flow nozzles, orifices if any
23	FW 610 FW 722	Galleries & railings for Scrubbers, Tank	Stairs Handrail Step treads Floor grills Ladders Foundation bolts Fasteners
24	FW 701	Slurry pumps & accessories	Slurry Pumps incl Shaft seal Common Base Plate Coupling and Guard Belt & Pulley Expansion Bellow Anchor Bolts & Fasteners Motor & accessories Sump Pumps incl Shaft seal Common Base Plate Coupling and Guard Belt & Pulley Anchor Bolts & Fasteners Motor & accessories
25	FW 710	Monorail for hoist& cranes	Insert Plate Stiffener plate Monorail beam
26	FW 715	Handling Equipment in FGD	Electrically operated Hoists Underslung Cranes Chain Pulleys
27	FW 721	Agitator support	Channels & Beams
28	FW 730	Limestone silo structures	Columns Beams Bracings Seal plate Angles, channels

SI No	SURFACE LOCATION	PGMA	SURFACE PREPARATION	PRIMER		FINISH		TOTAL DFT IN (μ min.)
				PAINT	DFT (μ min.)	PAINT	DFT (μ min.)	

SNO	PGMA	PGMA DESCRIPTION	PGMA DETAILS
29	FW 731	Limestone silo	Base plate & its supports Shell, Roof
30	FW 732	Limestone silo accessories	Bag filter Air cannon bin activator Slide gate & bar gate for day silo
31	FW 733	Limestone silo approach platforms	Stairs Handrail Step treads Floor grills Ladders Foundation bolts Fasteners
32	FW 734	Limestone mill	Wet ball mill Hydro cyclone- Mill area Mill circuit pump Mill separator tank with Agitator
33	FW 742	Lime stone slurry storage tank	Base plate & its supports Shell, Roof
34	FW 743	Auxiliary Absorber tank	Base plate & its supports Shell, Roof
35	FW 744	Filtrate tank	Base plate & its supports Shell, Roof
36	FW 745	Wastage water tank	Base plate & its supports Shell, Roof
37	FW 747	Hydro cyclone waste water tank	Base plate & its supports Shell, Roof
38	FW 748	Process Water tank	Base plate & its supports Shell, Roof
39	FW 751	Process water pipe accessories	CS/FRP Pipes & Fittings Sight Glass R Orifice Gaskets & Fasteners
40	FW 753	Slurry pipe accessories	CSRL/FRP Pipes & Fittings Strainer (Cone) Expansion Joint-Rubber R Orifice Gaskets & Fasteners

SI No	SURFACE LOCATION	PGMA	SURFACE PREPARATION	PRIMER		FINISH		TOTAL DFT IN (μ min.)
				PAINT	DFT (μ min.)	PAINT	DFT (μ min.)	

SNO	PGMA	PGMA DESCRIPTION	PGMA DETAILS
41	FW 754	Service air pipe accessories	GI Pipes & Fittings Flexible Hose Expansion Joint (Metallic) Hose connector R Orifice Gaskets & Fasteners
42	FW 755	Instrument air pipe accessories	SS Pipes & Fittings Strainer(Y Type) Gaskets & Fasteners
43	FW 758	Valves and fittings	Globe valves Ball Valves Butterfly Valves Diaphragm Valves Gate Valves CheckValves Pinch Valves Knife Gate Valves Control Valves Relief Valves
44	FW 761	Structures for Pipe racks	Bracings Columns
45	FW 280 FW 281 FW 740 FW 763	Foundation material for duct structure Foundation material for scrubber Foundation material for Tanks Foundation material for Pipe racks	Foundation bolts Template
46	FW 766	Platforms for Pipe rack	Stairs Handrail Step treads Floor grills Ladders Foundation bolts Fasteners
47	FW 769	Trestle for Pipe racks	Truss Beams, Supports for all Pipes
48	FW 779	Supports for cable tray	Double Sup Channel & Base plates Single Sup Channel & Base plates Cantilever Arm Fasteners & clamps Brackets
49	FW 790	Tools	Erection , commissioning, special tools

SI No	SURFACE LOCATION	PGMA	SURFACE PREPARATION	PRIMER		FINISH		TOTAL DFT IN (μ m min.)
				PAINT	DFT (μ m min.)	PAINT	DFT (μ m min.)	

SNO	PGMA	PGMA DESCRIPTION	PGMA DETAILS
50	FW 798	Air receivers	Instrument Air receivers Any Instruments/Valves
51	FW 800	Clarified water tank	Base plate & its supports Shell, Roof
52	FW 802	Neutralization tank & accessories	Base plate & its supports Shell, Roof
53	FW 988	Commissioning spares	Startup & commissioning spares