



CORPORATE PURCHASING SPECIFICATION

AA101 19

Rev No.14

PREFACE SHEET

STRUCTURAL STEEL – WELDABLE QUALITY (PLATES, SECTIONS, STRIPS, FLATS AND BARS)

FOR INTERNAL USE ONLY

REMOVE THIS PREFACE BEFORE ISSUE TO SUPPLIERS

Equivalent/Comparable Standards:

1. IS: 2060 Grade: E250-BR (With impact test)
2. DIN EN 10025 Grade: S 275J2G3

Suggested/Probable Suppliers and Grades:

Refer Plant Vendors List

User Plants and Replaced Plant Specifications/References:

1. BHOPAL :
2. HEEP, HARDWAR :
3. HYDERABAD :

Revisions:
As per 37.9 of 37th MOM of S&GPS

APPROVED:
INTERPLANT MATERIAL RATIONALISATION
COMMITTEE – MRC(S&GPS)

Rev No.14	Amd No.	Reaffirmed	Prepared	Issued	Dt. of 1 st Issue
Dt:12-12-2013	Dt:	Year:	HPEP, Hyderabad	Corp.R&D	JULY, 1976

This page intentionally left blank



CORPORATE PURCHASING SPECIFICATION

AA101 19

Rev No.14

PAGE 1 of 2

STRUCTURAL STEEL – WELDABLE QUALITY (PLATES, SECTIONS, STRIPS, FLATS AND BARS)

ORDERING DESCRIPTION

1.0 GENERAL:

The material shall conform to the latest version of IS 2062, Grade. E250 Gr. BR (With impact test) DIN EN 10025, Gr. S275J2G3 and comply with following additional requirements.

2.0 APPLICATION:

For general engineering purposes, suitable for welding.

3.0 CONDITION OF DELIVERY:

3.1. Bars & Sections: Hot rolled in straight lengths without twists and bends.

3.2. Plates:

3.2.1. Plates as per IS: 2062 E250 Gr. BR (with mandatory impact test)

3.2.2. All plates below 10 mm thickness shall be free from mill scales and suitably protected with rust preventive coating at the time of supplies.

3.2.3. Any other additional requirement as per BHEL Purchase order

4.0 DIMENSIONS AND TOLERANCES:

4.1. Sizes:

Material shall be supplied to the dimensions specified in BHEL Order

4.2. Tolerances:

The tolerances on hot rolled material shall comply with IS: 1852 or any other equivalent National standard.

4.3. Straightness for hot rolled bars:

Unless otherwise specified, the permissible deviation in straightness shall not exceed 5 mm in any 1000 mm length.

5.0 TEST SAMPLES:

5.1. Tensile Test Pieces:

One tensile test sample shall be made from finished steel of each melt per size for each class of product viz. plated, sections, strips, flats and bars size of the product.

Revisions:
As per 37.9 of 37th MOM of S&GPS

APPROVED:
INTERPLANT MATERIAL RATIONALISATION
COMMITTEE – MRC(S&GPS)

Rev No.14	Amd No.	Reaffirmed	Prepared	Issued	Dt. of 1 st Issue
Dt:12-12-2013	Dt:	Year:	HPEP, Hyderabad	Corp.R&D	JULY, 1976

CORPORATE PURCHASING SPECIFICATION



5.2. Bend Test Pieces:

Bend test piece shall be made from finished steel of each melt per size of the product.

6.0 ULTRASONIC EXAMINATION:

Plates shall be ultrasonically examined in accordance with BHEL standard M 085 01 20 (or ASTM-A 435) as detailed below and shall comply with the acceptance standards specified therein.

6.1. For plates above 40mm thick:

Shall be ultrasonically examined unless otherwise specified in order.

7.0 TEST CERTIFICATES:

Unless otherwise specified, three copies of test certificates shall be supplied.

In addition, the supplier shall ensure to enclose one copy of the test certificate along with their dispatch documents to facilitate quick clearance of the material.

The test certificate shall bear the following information:

M 101 19-Rev. No.13 / IS : 2062-Gr:E250 BR (with impact test) or DIN EN 100 25 Gr. S275J2G3, BHEL order No,

Melt No, Size & Quantity, Batch No with heat treatment details, Results of Chemical analysis, Mechanical tests & NDT, Supplier's name, Identification No, TC No, Signature of Competent authority, etc.

8.0 RUST PREVENTION:

(Refer CI.3.2.2)

9.0 PACKING AND MARKING:

Plates shall be transported suitably to avoid damage during transit.

Each plate shall be marked with Melt No. Material grade and specification, BHEL Order No, Supplier's Name Identification No, Size & weight, on any one corner and encircled with paint preferably of white color.

10.0 REJECTION AND REPLACEMENT

If the material does not comply with the requirements of this specification during receipt inspection at BHEL or if any defect is found during further processing of material, BHEL reserves the right to reject the whole consignment and the supplier shall replace the material free of cost. The rejected material shall be taken back by the supplier after fulfilling the commercial terms and conditions.