

**Technical Delivery Conditions for Welded Pipes
conforming to ASME SA134 / ASTM A134****Project : BIFPCL MAITREE STPP - 2X660 MW****Records of Revn:00 :-** Fresh Issue.**Records of Revn:01 :-** Cl.No: 8.2 & 8.4 modified.**1.0 SCOPE**

- 1.1 This Technical Delivery Conditions specify the requirements for Electric-Fusion-Welded Steel Pipe (with Filler metal added) **conforming to ASME SA134 / ASTM A134.**
- 1.2 The pipes are intended for water services (under Non-IBR Piping system only).
- 1.3 The pipes shall conform to the size and quantity as specified in the purchase order.

Pipe Grade : ASME SA134 – SA283 Gr-D (or) ASTM A134 – A283 Gr-D**2.0 RAW MATERIAL**

The raw material used for pipe shall meet all the mandatory requirements as per ASME SA283 Gr-D / ASTM A283 Gr-D.

Carbon content shall be limited to 0.25% max and fully killed.

3.0 DIMENSIONAL TOLERANCES

The tolerances limits are:

- a) OD:- Upto NB 1600 mm: ± 4 mm; Above NB 1600 mm: ± 6 mm
- b) Thickness:- Upto 14mm : +1.3mm / -0.8mm; Above 14 mm : +1.4mm / - 0.8mm.
- c) Ovality (Difference between major and minor inside diameter): 0.5% maximum
- d) Squareness of ends: The ends of pipe section shall not vary by more than 3mm at any point from a true plane perpendicular to the axis of the pipe and passing through the center of the pipe at the end.
- e) Length and quantity tolerance as per P.O.
- f) All other tolerances shall be as per respective specification.

4.0 MANUFACTURING

- 4.1 The pipe shall be of **Longitudinal / Spiral welded** as indicated in the P.O.
- 4.2 The ends shall be edge prepared as indicated in the purchase order.
- 4.3 Circumferential seams shall be minimum 1500 mm apart from each other and from ends.
- 4.4 The offset between any two subsequent Longitudinal joints **shall not be less than 90deg.**
- 4.5 All pipes shall be completely finished and free from surface, sub surface defects such as pits, cracks, weld spatters & laminations etc..
- 4.6 **Heat Treatment :** Heat treatment is **not mandatory** when the nominal thickness of a weld does not exceed 3 / 4 in. (19 mm), and a minimum preheat of 200°F (95°C) is applied when the nominal material thickness of any of the base metals in the weld joint exceeds 1 in. (25 mm).
- 4.7 **Mechanical Test :** One Test Coupon for each 900m of weld length per size per lot.
- a) Transverse Tension test for weld seam
- b) Guided bend test (Face & Root)

 Vivekananda Yellu Dy.Mgr/QA	 K. Rajitha SDGM/MM	 C Vaithianathan AGM/QA	 C. Karunakaran AGM/Engg	 P. Ravi Shankar AGM/Quality
Prepared By	Reviewed By			Approved By

**Technical Delivery Conditions for Welded Pipes
conforming to ASME SA134 / ASTM A134****Project : BIFPCL MAITREE STPP - 2X660 MW**

4.8 **Product analysis** : One Test Coupon for each 900m of weld length per size per lot.

5.0 HYDRO TEST

All Pipes shall be Hydro tested as per ASME SA134 / ASTM A134.

6.0 INSPECTION

6.1 All pipes shall be inspected by the vendor prior to BHEL / **Customers'** Inspection.

6.2 BHEL or BHEL authorized inspector / **Customer** will select the pipes at random and carryout the inspection. The necessary Material Despatch Clearance Certificate is to be obtained by the vendor prior to the despatch of material.

7.0 PAINTING AND PACKING

7.1 The pipes if despatched to BHEL Stores shall be coated with resin type translucent rust preventive on the outside unless otherwise specified in the P.O. Pipes of diameter above NB 350 mm, shall be coated inside also.

7.2 The pipes if despatched to project site directly shall be painted outside & coated inside as indicated in P.O.

7.3 In case of any special coating like Polyurethane, Rubber Lining, etc.. the vendor shall get BHEL approval for their QP and Procedure for application of internal coating.

7.4 Internal un-coated length (cut-back length) from both ends of the pipe shall be maintained as per drawing attached in P.O. to facilitate site joints.

7.5 Spiders & End Caps are to be provided on both ends of the pipes as per the drawing indicated in the enquiry / Purchase Order.

7.6 Sea worthy packing to be followed and shall be done as per the instructions given in Purchase order.

8.0 MARKING

8.1 The pipes despatched to **BHEL Stores** shall be paint stencilled & hard punched with the following details.

- 1) PO Number 2) Supplier's emblem/code 3) Size & Specification 4) Heat number
5) Pipe number 6) Inspector's seal

8.2 The pipes despatched to Indian Sea Port as per Enquiry/P.O., the following details (furnished in the P.O. or separately) shall be paint stencilled & hard punched on both ends of the pipes in addition to the above.

- Work order No ➤ DU No
➤ Pipe Length (in mtr) ➤ Weight per Pipe length

8.3 For the pipe dia 1000mm and above marking-hard punch shall be done on internal surface in the uncoated area (i.e) within 100mm from pipe ends in addition to the paint stencilling on external surface. The hard punching shall be done at one end and paint stencilling at other end. In case of pipes of dia less than 1000mm the marking shall be done on outside surface.

 Vivekananda Yellu Dy.Mgr/QA	 K. Rajitha SDGM/MM	 C Vaithianathan AGM/QA	 C. Karunakaran AGM/Engg	 P. Ravi Shankar AGM/Quality
Prepared By	Reviewed By			Approved By



**Technical Delivery Conditions for Welded Pipes
conforming to ASME SA134 / ASTM A134**

Project : BIFPCL MAITREE STPP - 2X660 MW



8.4 **Any other Marking & Identification which is not mentioned above Sl. No: 8.1, 8.2 & 8.3 shall be as per Enquiry/P.O.**

9.0 CERTIFICATES

9.1 Three original test certificates typed in English shall be submitted along with the inspection report.

9.2 The test certificate shall furnish the following details.

- a. BHEL P.O Number & Amendment Number (if any)
- b. BHEL P.O. Serial Number
- c. Test Certificate number.
- d. Specification, grade, size, quantity
- e. Heat number of plate (or pipe number with traceability to heat number)
- f. Chemical composition and Mechanical properties
- g. Hydrostatic test report
- h. Dimensional report
- i. Painting details
- j. *Appropriate ASME Certificate of Authorization and copy of Certification Mark if applicable.*

 Vivekananda Yellu Dy.Mgr/QA	 K. Rajitha SDGM/MM	 C Vaithianathan AGM/QA	 C. Karunakaran AGM/Engg	 P. Ravi Shankar AGM/Quality
Prepared By	Reviewed By			Approved By