

 BHARAT HEAVY ELECTRICALS LIMITED PIPING CENTRE, CHENNAI- 17 QUALITY ASSURANCE & CONTROL DEPT.			PAINTING SCHEME FOR LP PIPING (CW / ACW / ECW / Plant water, Air Piping, etc...,) PROJECT NAME : - UPPUR TPS - 2X800 MW BHEL CUSTOMER Nos : 7319, 7320(Main Boiler) & 7322(Aux.Boiler)								QPNo: 7319:QPC:12 REV.NO: 00 Dt : 21.06.2017	
SI. NO	PGMA / Description	Surface Preparation & Surface Profile	Primer coat		Intermediate coat			Finish coat			Total DFT Microns (Min.)	REMARKS
			Primer	No of coats	Paint	No of coats	Shade	Paint	No of coats	Shade		
1	2	3	4	5	6	7	8	9	10	11	12	13
1	(a) Internal Surface - Steel Pipe - Seawater handling	Blast Cleaning SSPC SP-10 / SA 2½ (Refer Note 1)	Isophthalic polyester / acrylic co-polymer filled with glass flakes coating								1000 Microns (min)	(Refer Note 2)
	(b) Holiday test (Refer Note 3)	Holiday testing as per Paint Manufacturer's Quality Plan approved by BHEL. Holiday test Equipment shall be calibrated before testing.										
2	External Surface --Buried Piping / Encased in concrete (Temporary Protection for transportation from works to site). **Further protection to be done by BHEL Erection Group as per Contract requirement.	SSPC-SP3 / Power Tool Cleaning	Red Oxide Zinc Phosphate (Alkyd base to IS 12744)	1 (30 Microns per coat)	----	----	----	----	----	----	30 Microns	
2A	External Surface --Buried Piping - Not Encased in concrete	Blast cleaning to SSPC SP-10 / SA 2½	Primer : Coal Tar primer compatible with coal tar enamel grade. 2 coats of 35 microns each. Total DFT:70microns. Finish Coat : Coal tar enamel (25mm overlap min) Type-I to IS7193-1974 conforming to table of 10 of IS10221-1982. Tickness - 4.0mm (or) Coal Tar Wrapping conforming to IS 15337-2003; Tickness - 4.0mm Test : Bond/Adhesion; Holiday test									Shall be done by BHEL's Erection Group.
3	Internal Surface -Other than Sea water handling - (For 800Nb and above diameters)	Blast cleaning to SSPC SP-10 / SA 2½	Epoxy Polyamide resin based Zinc Phosphate Primer	2 (35 microns per coat)	Epoxy resin with MIO	1 (75 microns per coat.)	----	Epoxy Polyamide finish Paint	1 \$ (40 microns per coat)	Smoke Grey Shade No 692 of IS 5 (Refer Note-4)	145 at shop + 40 at site	\$: 1 coat of DFT-40 microns finish coat at site
4	External Surface - Over ground piping (For all diameters)	Blast cleaning to SSPC SP-10 / SA 2½	Epoxy Polyamide resin based Zinc Phosphate Primer	2 (35 microns per coat)	Epoxy resin with MIO	1 (75 microns per coat.)	----	Epoxy Polyamide finish Paint	1 \$ (40 microns per coat)	Smoke Grey Shade No 692 of IS 5 (Refer Note-4)	145 at shop + 40 at site	\$: 1 coat of DFT-40 microns finish coat at site
5	Galvanised and Stainless steel Piping	No painting . Site painting requirements as indicated in specification (Vol-III, cl.13.10.5) shall be done by BHEL's erection group.										
Notes: 1. Blast cleaning to near white metal to obtain roughness as per paint manufacturer's recommendations. 2. Application and inspection (including DFT) of Isophthalic polyester / acrylic co-polymer filled with glass flakes shall be as per Paint manufacturer's QP and Painting procedure approved by BHEL. 3. Witness by BHEL / BHEL nominated inspection agency. 4. Shade for finish coat to be done at site shall be as per project specification/contract requirement.												
 PREPARED BY : VIVEKANANDA YELLU, Dy.Mgr/QA			 APPROVED BY: A.P.MADHAVANKUTTY, AGM/Q			For Customer use :					Page 1/1	