

This page intentionally left blank

	CORPORATE PURCHASING SPECIFICATION	AA51401 Rev No.03 PAGE 1 of 6																					
CONIFEROUS TIMBER FOR GENERAL PACKING PURPOSES																							
1.0 GENERAL: This specification governs the quality requirements of Coniferous timber supplied in the form of planks, battens beams and sleepers. The coniferous timber differs from non-coniferous (broad leave) timber in its gross appearance, anatomical structure and properties. In general, it works more easily under the tools and can be easily nailed.																							
2.0 APPLICATION: Used for general packing purposes.																							
3.0 COMPLIANCE WITH NATIONAL STANDARDS: There is no National standard covering this material. However, assistance has been derived from the following National standards: IS: 190 – 1991 Grade I : Coniferous Sawn Timber(Baulks & Scantling) IS: 6662 – 1993 Groups III & IV : Timber Species Suitable For Wooden Packaging																							
4.0 TERMINOLOGY: For the purpose of this specification, the definitions given in IS: 707 (Glossary of terms applicable to timber and timber products) shall apply except for the beam which is defined as follows: Beam is defined as converted timber whose cross-sectional dimensions exceed 50mm in both directions.																							
5.0 SPECIES: Shall be as stated on the order. Some standard species are: <table style="width: 100%; margin-top: 10px;"> <thead> <tr> <th style="text-align: left;"><u>Trade Name</u></th> <th style="text-align: left;"><u>Botanical Name</u></th> <th style="text-align: left;"><u>Abbreviation</u></th> </tr> </thead> <tbody> <tr> <td>Fir</td> <td>Abiespindrow</td> <td>FIR</td> </tr> <tr> <td>Deodar</td> <td>Cedrusdeodara</td> <td>DEO</td> </tr> <tr> <td>Chir</td> <td>Pinusroxburghil</td> <td>CHR</td> </tr> <tr> <td>Kali</td> <td>Pinuswallichians</td> <td>KAL</td> </tr> <tr> <td>Khasi Pine</td> <td>Pinuskhasya</td> <td>KPI</td> </tr> <tr> <td>Spruce</td> <td>Piccasmithianaboiss</td> <td>SPR</td> </tr> </tbody> </table>			<u>Trade Name</u>	<u>Botanical Name</u>	<u>Abbreviation</u>	Fir	Abiespindrow	FIR	Deodar	Cedrusdeodara	DEO	Chir	Pinusroxburghil	CHR	Kali	Pinuswallichians	KAL	Khasi Pine	Pinuskhasya	KPI	Spruce	Piccasmithianaboiss	SPR
<u>Trade Name</u>	<u>Botanical Name</u>	<u>Abbreviation</u>																					
Fir	Abiespindrow	FIR																					
Deodar	Cedrusdeodara	DEO																					
Chir	Pinusroxburghil	CHR																					
Kali	Pinuswallichians	KAL																					
Khasi Pine	Pinuskhasya	KPI																					
Spruce	Piccasmithianaboiss	SPR																					
Revisions: Cl. 6.2.2 of MOM of WG – (T&PM)		APPROVED: INTERPLANT MATERIAL RATIONALISATION COMMITTEE – MRC(T&PM)																					
Rev No.03	Amd No.01	Reaffirmed																					
Dt:01-10-1995	Dt:02-05-2002	Year:2013																					
Prepared HEP, Bhopal		Issued Corp.R&D																					
		Dt. of 1 st Issue MAR. '80																					

CORPORATE PURCHASING SPECIFICATION



6.0 DIMENSIONS AND TOLERANCES:

6.1 Sizes:

Width, thickness and length of timber shall be clearly stated on the order.

6.2 Tolerances:

6.2.1 Width :50 to 250 mm Tolerance : +3 mm

6.2.2 Thickness: 20 to 250 mm Tolerance: +3 mm
- 1 mm

6.2.3 Length:

Standard length : 1 to 12 metres in multiples of 0.5 metre
Tolerance: $\pm 2\%$ or ± 25 mm whichever is less.

Note:

1.0 Measurements:

1.1 When nominal sizes are ordered, length, width and thickness shall be measured on the basis of accepted sizes. Plus tolerances shall not be added while computing the volume.

1.2 The measurements of length, width, thickness and computation of volume shall be as follows:

- The length shall be measured in metres in midline of a piece. The fractions of a metre shall be rounded off to the nearest lower 10 mm.
- The width shall be measured at the narrowest place in millimetres and shall be rounded off to the nearest lower one millimetre.
- The thickness shall be measured at the narrowest place in millimeters and shall be rounded off to the nearest lower one millimeter.
- The volume shall be computed in cubic meters correct to three places of decimal on the basis of accepted sizes

2.0 Single sampling plan based on IS:2500 shall be followed.

7.0 MOISTURE CONTENT:

The timber shall have moisture content as stated below within a depth of 15mm from the surface excluding a length of 300mm from each end at the time of inspection. The moisture content will be determined in accordance with IS: 287

October to June : 30%

July to September (Rainy season): 40%



CORPORATE PURCHASING SPECIFICATION

AA51401

Rev No.03

PAGE 3 of 6

8.0 FREE FROM DEFECTS:

Timber shall be free from the following defects:

Brashness, splits across the grain, shakes, spring, twist, insect attack, any kind of decay (rot), any sign of infection, open centre heart, centres heart on planks and any other defect.

Defects to the extent specified below are permissible. These defects shall be measured in accordance with IS: 3364.

8.1 Bow:

Shall be permissible up to a maximum of 2mm for 300mm length.

8.2 Cud:

Shall be permissible up to a maximum of 6mm for 300mm width

8.3 Centre heart:

Shall be permissible only on sleepers when it is not further than 35mm from the nearest edge. This does not apply to beams of cross sections above 200 X 200 mm.

8.4 Wane:

- a) For sections up to and including 150 X 150 mm:

Shall be permissible upto 1/5 of the width on the broad face subject to a maximum of 70mm and upto 1/3 of the width on the narrow face subject a maximum of 50mm, provided that one broad face is completely free from this defect. The wane shall be measured at its deepest part

- b) For sections above 150 X 150 mm:

The cumulative lengths of waness on all the sides should not be more than one length of the piece.

8.5 End splits:

The longest end split at each end shall be measured and the lengths added together. The total length of these shall not exceed 80mm per meter run of the piece.

8.6 Live knots:

8.6.1 Knots on the surface:

- a) Up to & including 25mm diameter:

A maximum of 5 knots/meter length are permissible. However, the knots shall not be so grouped or located as to affect the strength of the piece.

- b) Over 25mm and up to and including 70mm diameter:

A maximum of 2 knots/metre length are permissible.

CORPORATE PURCHASING SPECIFICATION



8.6.2 Knots on the edges:

- a) Up to and including 10mm diameter and for full thickness:

A maximum of 2 knots/metre length are permissible

- b) Over 10mm and up to & including 50mm diameter and for less than half thickness:

A maximum of 2 knots/metre length are permissible.

8.7 Dead knots:

- a) Below 10mm diameter:

A maximum of 3 knots/metre length are allowed provided that the knots are not so grouped or located as to affect the strength.

- b) From 10mm to up to and including 25mm diameter:

A maximum of 2 knots allowed to the extent of 1 knot/metre length.

- c) Above 25mm diameter:

Not allowed

Note: (For clauses 8.6 & 8.7): Major axis of the knot should be taken as the diameter of the knot

8.8 Surface cracks:

Surface cracks with a maximum depth of 10% of the thickness are permissible. A continuous crack of any depth all along the length is not permissible.

8.9 Sap Wood:

Permissible up to a maximum of 12 percent of the cross sectional area.

9.0 END COATING:

Timber shall be coated with any of the following effective compositions upto a distance of 80 mm from each end

- 9.1 Thick coal tar or bituminous paint.

- 9.2 Resin and lamp black (10:1) melted, mixed and applied hot.

- 9.3 Hardened gloss oil.

- 9.4 Paraffin wax.

- 9.5 Molasses and lime (3:1).

- 9.6 Geru/Yellow clay



CORPORATE PURCHASING SPECIFICATION

AA51401

Rev No.03

PAGE 5 of 6

10.0 INSPECTION AT SUPPLIER'S WORKS:

Whenever specified, tests and inspection are to be conducted in the presence of BHEL's representative. BHEL representative shall have free access at all times while work on the contract is being performed to all parts of the manufacturer works. The manufacture shall offer BHEL's representative all reasonable facilities, without charge, to satisfy the latter that the material is being furnished in accordance with this specification.

The manufacturer shall prepare and provide necessary test specimens for testing to be carried out at his premises. If facilities are not available at his works the manufacturer, shall make necessary arrangements for carrying out the prescribed tests elsewhere. The manufacturer shall notify BHEL in advance about the readiness of the material for inspection and testing. BHEL reserves the right to test the material at BHEL's Works and the final acceptance of the material shall be based on these test results

11.0 TEST CERTIFICATES:

Three copies of test certificate shall be supplied unless otherwise stated on the order.

In addition, supplier shall ensure to enclose one copy of test certificate along with their dispatch documents to facilitate quick clearance of the material.

The test certificate shall have the following information:

AA51401(Rev.No.03):CONIFEROUS TIMBER FOR GENERAL PACKING PURPOSES

BHEL order No.:

Supplier's References:

Type & Specie:

Treatment, if any:

Results of Dimensional Inspection:

Moisture content:

Defects as per clause 8.0:

Size:

Quantity supplied:

12.0 MARKING:

The timber shall be marked/painted with the following:

AA 514 01

BHEL order No. :

Supplier's Name :

Size & Quantity :

CORPORATE PURCHASING SPECIFICATION



13.0 REJECTION AND REPLACEMENT:

If the material does not conform to the requirements of this specification or found defective during further processing, such material shall be rejected notwithstanding any previous certification of satisfactory testing and/or inspection. The supplier shall under take to replace the rejected consignment at his own cost and the rejected material shall be taken back by the supplier after fulfilling the commercial terms and conditions.

14.0 REFERRED STANDARDS:

The following is the list of the latest standards, as published by the respective issuing bodies, referred to in this specification.

- | | | |
|-------------|-------------|-------------|
| 1) IS: 190 | 2) IS: 287 | 3) IS: 707 |
| 4) IS: 2500 | 5) IS: 3364 | 6) IS: 6662 |