

PSGSG / 14-15/ 005, Rev-02	Process Specifications for Electrical Grade PTFE Bushes	Drg.No.	
		Date	31.07.2018
		Product	GSM-400
S.NO	BHEL Specification	Vendor compliance	
		YES/NO	Remarks
1.0	APPLICATION: PTFE bushes are used as nozzles in gas circuit breakers for effective short circuit current interruption.		
2.0	SPECIFICATIONS:		
2.1	Configuration: Hollow cylindrical bush.		
2.2	Material : MoS ₂ filled PTFE PTFE – 99.8% (By weight) Molybdenum disulphide ~ 0.2% (By weight) Color - Light Grey		
2.3	Dimensions & Quantities: Ø150±0.5 mm x Ø20±0.5 mm x 350±1 mm long – 15 Nos.		
2.4	Exposure to high current arcing should not carbonize the material and result in deep penetration burns, impairing the dielectric strength of the material. Quality control check certificate should be furnished.		
2.5	Compression-molded PTFE bush with MoS ₂ filler uniformly distributed, free from occlusion and air pockets suitable for High Voltage Applications.		
Page 1/3	PSGSG / 14-15 / 005	Signature	

PSGSG / 14-15/ 005, Rev-02	Process Specifications for Electrical Grade PTFE Bushes	Drg.No.																																		
		Date	31.07.2018																																	
		Product	GSM-400																																	
S.NO	BHEL Specification	Vendor compliance																																		
		YES/NO	Remarks																																	
2.6	Properties: <table border="0"> <tr> <td>#</td><td>Property</td><td>Value</td></tr> <tr> <td>1.</td><td>Density</td><td>2.14 to 2.18 gm/cc</td></tr> <tr> <td>2.</td><td>Water absorption</td><td>< 0.01% max</td></tr> <tr> <td>3.</td><td>Melting point</td><td>320 to 340°C</td></tr> <tr> <td>4.</td><td>Continuous use</td><td>-260/ +280 °C</td></tr> <tr> <td>5.</td><td>Compressive strength</td><td>≥ 4.3 N/mm²</td></tr> <tr> <td>6.</td><td>Hardness</td><td>55+/- 2</td></tr> <tr> <td>7.</td><td>Elongation at break</td><td>>250 %</td></tr> <tr> <td>8.</td><td>Impact strength</td><td>~ 3.0 J/cm</td></tr> <tr> <td>9.</td><td>Static coefficient of friction</td><td><0.1</td></tr> <tr> <td>10.</td><td>Dielectric break down Strength (0.5mm sample)</td><td>40 –60 kV/mm</td></tr> </table>	#	Property	Value	1.	Density	2.14 to 2.18 gm/cc	2.	Water absorption	< 0.01% max	3.	Melting point	320 to 340°C	4.	Continuous use	-260/ +280 °C	5.	Compressive strength	≥ 4.3 N/mm ²	6.	Hardness	55+/- 2	7.	Elongation at break	>250 %	8.	Impact strength	~ 3.0 J/cm	9.	Static coefficient of friction	<0.1	10.	Dielectric break down Strength (0.5mm sample)	40 –60 kV/mm		
#	Property	Value																																		
1.	Density	2.14 to 2.18 gm/cc																																		
2.	Water absorption	< 0.01% max																																		
3.	Melting point	320 to 340°C																																		
4.	Continuous use	-260/ +280 °C																																		
5.	Compressive strength	≥ 4.3 N/mm ²																																		
6.	Hardness	55+/- 2																																		
7.	Elongation at break	>250 %																																		
8.	Impact strength	~ 3.0 J/cm																																		
9.	Static coefficient of friction	<0.1																																		
10.	Dielectric break down Strength (0.5mm sample)	40 –60 kV/mm																																		
2.7	This filler shall improve surface hardness, stiffness, and to reduce the starting coefficient of friction and steady-state wear. Its effect on electrical and chemical properties must be negligible.																																			
2.8	Tests: Test reports for the properties like density, hardness shall be furnished along with the supply.																																			
Page 2/3	PSGSG / 14-15 / 005	Signature																																		

PSGSG / 14-15/ 005, Rev-02	Process Specifications for Electrical Grade PTFE Bushes	Drg.No.	
		Date	31.07.2018
		Product	GSM-400
S.NO	BHEL Specification	Vendor compliance	
		YES/NO	Remarks
2.9	General: Material must be free from defects, cavities, pin holes and the same shall be ensured by the supplier. Uniform composition of the material shall be ensured. The finished bush shall not have any ovality, bend and the outer surface should be free from dents/visible surface defects. Perpendicularity of the flat surface (base) shall be maintained at +/- 0.1. The component shall be free from dirt, grease and moisture.		
2.10	Packing: Each bush should be individually wrapped in polyethylene and packed in separate high density, dust free card board boxes. The lot should be supplied in shock proof, unbreakable containers.		
Page 3/3	PSGSG / 14-15 / 005	Signature	