 Ranipet	TECHNICAL DELIVERY CONDITIONS FOR PLATES TO SPECIFICATION ASTM B 575 UNS N06059	DOC No: TDC: RTS: 001 Rev: 00 Effective Date: 14/12/2017 Page: 1 of 2
--	--	---

1.0 SCOPE

- 1.1 This TDC specifies the requirements for the supply of structural plates conforming to ASTM B575 UNS N06059 to the latest edition.
- 1.2 The Size and Quantity shall be as specified in Enquiry/Purchase order.

2.0 MATERIAL SPECIFICATION:

- 2.1 PLATES : Alloy 59, NiCr23Mo16A1 (2.4605)
- 2.2 Additional Requirement : As listed below (This TDC gives requirements over and above the mandatory requirements of the specification)

3.0 CHEMICAL COMPOSITION

As per ASTM B575-17 Table 1.

4.0 DIMENSIONAL TOLERANCES

4.1	The following tolerances shall apply	
	a) Thickness/Width/Length tolerance	As per ASTM B906
	b) Straightness	Edgewise curvature(depth of chord) of plate shall not exceed 0.04 mm multiplied by the length in cm.
	c) Squareness	For plates of all thickness and widths of 152.4mm or more, the angle between adjacent sides shall be 90± 0.015°.
	d) Edges	Plates shall have sheared or cut (machines, abrasive cut, powder cut) edges as specified.

5.0 HEAT TREATMENT:









Plate should be solution annealed between 1100-1180°C and cooled quickly. Water Quenching is preferred to obtain maximum corrosion resistance.

6.0 MECHANICAL TESTS:

- a) Frequency of tests: Minimum of 2 samples per heat.
- b) All mandatory tests shall be as per the applicable materials specifications.

7.0 MECHANICAL PROPERTIES

	Metric
Tensile strength (Min)	690 MPa
Yield strength (Min)	310 MPa
Elongation at break (Min)	45%
Rockwell Hardness (Max)	100 HRB

Prepared by	Reviewed by	Signature	Name	Approved by
	ENGG (AQCS)		K.B. Padhi	 21/12/2017 (Head/QA)
	ENGG (FGD)		K.M.KABILASH	
	QC (PROC)		R. Kesavan	
MATERIAL PLANNING		P. ANNAMALAI		
	QA		R. Annadale	

Issued by QUALITY ASSURANCE



**TECHNICAL DELIVERY CONDITIONS
FOR PLATES TO SPECIFICATION
ASTM B 575 UNS N06059**

DOC No: **TDC: RTS: 001**
Rev: **00**
Effective Date: 14/12/2017
Page: **2 of 2**

8.0 PHYSICAL PROPERTIES:

	Metric
Density	8.6g/cm ³
Thermal expansion coefficient(@20-100°C/68-212°F)	11.9 µm/m°C
Thermal conductivity	10.4W/mK

9.0 FINISH AND REPAIR:

Plates shall be free from all mill scales, edge crack and other injurious defects. Repairs by fusion welding is prohibited. Mechanical removal of defects permitted subject to meeting minimum thickness and smooth surface.

10.0 MARKING (by mill):

1. Specification
2. Grade
3. Melt number
4. Maker's emblem/Code/ Identification and
5. Plate number. PO No (BHEL PO only), buyer name & Weight to be painted on the product. Marking shall be done as indicated below:
 - i. Sl no: 1 to 5 by paint stenciling on the top of each pile/ packet.
 - ii. The markings shall have no deleterious effect on the material or its performance and shall be sufficiently stable to withstand normal handling.

11.0 INSPECTION AND CERTIFICATION:

Products must be inspected & tested at supplier's works. Test certificate, in English, shall accompany each product with the following details:

- a) Purchase Order No. (BHEL PO only), TDC No. & its Revision No., Test certificate No. & Date, Size, Plate number and Quantity-Melt wise.
- b) Material Specification and Grade with applicable year of code, Heat Number, Steel making process, de-oxidation process (Specification designation)
- c) Chemistry, Carbon equivalent and Heat Treatment details.
- d) Mechanical test values, including impact values and through thickness ductility (where applicable), shall be reported.
- e) NDE results with reference and acceptance standards.

Prepared by	Reviewed by	Signature	Name	Approved by
	ENGG (AQCS)		K. B. Padhi	 21/12/2017
	ENGG (FGD)		K.M. KABILASH	
	QC (PROC)		R. Kesavan	
	MATERIAL PLANNING		P. ANNAMALAI	
	QA		R. Annamalai	
Issued by QUALITY ASSURANCE				(Head/QA)