

TITLE : FLEXIBLE SEPARATOR (AIR CELL)

1.CONSTRUCTION

POLYIMIDE NYLON FABRIC COATED ON BOTH SIDES WITH SYNTHETIC RUBBER AND MEETING THE COMPLETE REQUIREMENT OF THIS SPECIFICATION SHALL BE USED FOR FABRICATION OF FLEXIBLE SEPARATORS. CONSTRUCTION OF THE SEPARATOR SHALL BE AS SHOWN IN FIGURE-1. ADHESIVES USED SHALL BE COMPATIBLE WITH AIR AND TRANSFORMER OIL AT 100 °C. JOINTS SHALL BE PROPERLY DESIGNED & SUITABLY VALCANIZED. FURTHER, SEPARATOR SHALL BE REINFORCED AT BOTTOM FACE AS SHOWN IN FIGURE 1. TO AVOID DAMAGE DUE TO CONTACT WITH MAGNETIC OIL GAUGE FLOAT. THERE SHALL NOT BE ANY PATCH WORK. ADAPTOR USED SHALL BE MADE FROM STRUCTURAL STEEL CONFORMING TO Fe-410-S TO IS:226. ADAPTOR AND BOLTS SHALL BE CADMIUM PLATED AND PASSIVATED (CD-8 OF IS:1572) OR ZINC PLATED AND PASSIVATED.(Fe/Zn 12.5 OF IS:1573).. THE WIDTH OF THE OVERLAP AT THE JOINTS TO BE SUCH THAT THERE IS NO POSSIBILITY OF JOINT OPENING AND LEAKAGE AND SHOULD BE MINIMUM 75 mm. THE WIDTH OF SIDE JOINTS SHALL BE AS IN FIGURE 1.

2. FUNCTIONAL REQUIREMENT

- (I) FLEXIBLE SEPARATOR SHALL BE SUITABLE FOR CONTINUOUS USE IN TRANSFORMER OIL AT -20°C TO 100°C
- (II) INSIDE COATING SHALL BE VERY GOOD WEATHER AND OZONE RESISTANT, OUTSIDE COATING SHALL BE TRANSFORMER OIL RESISTANT, COMPOUNDS USED FOR COATING SHALL NOT DETERIORATE IN SERVICE

SHEET REAFFIRMED

विभाग
DISTRIBUTION
प्रति प्रति
प्रति प्रति

५. संस्कृत किया :

APPROVED: S. J. BSE, SNA

1997-1998

DATE



Form No. 2038

उत्पाद मानक

परिणामित्र

शॉप/अभि. निर्देश

PRODUCT STANDARD

TRANSFORMER

SHOP/ENGG INSTRUCTIONS

TR 10150A

पृष्ठ 02

PAGE 2 OF 10

TITLE : FLEXIBLE SEPARATOR (AIR CELL)

(III) SEPARATOR SHALL BE SUITABLE FOR INFLATION AND DEFLATION

DUE TO CHANGE IN OIL VOLUME IN THE CONSERVATOR. FURTHER, SEPARATOR SHALL BE DESIGNED TO COLLAPSE SLOWLY AS OIL LEVEL RISES IN THE CONSERVATOR.

(IV) SEPARATOR SHALL NOT DEVELOP CRACKS AT -20°C.

(V) FIXATION LUGS AND ADAPTER SHALL BE PROVIDED ON THE SEPARATOR AS SHOWN IN FIGURE-1.

3. MATERIALS**3.1 BASIC FABRIC**

BASIC FABRIC USED FOR MAKING COATED FABRIC FOR MANUFACTURING FLEXIBLE SEPARATORS SHALL MEET THE FOLLOWING REQUIREMENT
MATERIAL - POLYAMIDE 6/NYLON 6, PLAIN WEAVE FABRIC OF SUITABLE CONSTRUCTION.

3.2 COATING COMPOUNDS

THE RUBBER COMPOUNDS USED FOR INSIDE AND OUTSIDE COATING ON THE POLYAMIDE/NYLON FABRIC SHALL MEET THE REQUIREMENT AS GIVEN BELOW-

3.2.1. OIL SIDE COATING

MATERIAL ACRYLONITRILE BUTADINE RUBBER (NBR) COMPOUND BA - 70 OF BS BS: 2751.

COPYRIGHT AND CONFIDENTIAL
Information on this document is the property of BHARAT HEAVY ELECTRICALS LIMITED. It must not be used directly or indirectly in any way detrimental to the interest of the Company.

Page 2 of 10

Rev. 04

SPECIFICATION REVISION

वितरण
DISTRIBUTION
निर्माण
MANUFACTURE
परीक्षण
TESTING
संशोधन
RESEARCH

मं. योक्तु क्रिया :
APPROVED : SUBS. SNA

नया विषय प्रमाणित : प्रमाणित : प्रमाणित

दिनांक
DATE
07-01-02

13-07-88
2010



Form No. 2038

उत्पाद मानक

परिणामित्र

शाप/अभि. निर्देश

PRODUCT STANDARD

TRANSFORMER

SHOP/ENGG INSTRUCTIONS

TR 10150A

10 पृष्ठों में 3

PAGE 3 OF 10

TITLE : **FLEXIBLE SEPARATOR (AIR CELL)**

MATERIAL - COMPOUND FOR OIL SIDE COATING BA -70 OF BS: 2751

SL. NO.	PROPERTY	REQUIREMENT	TYPE OF TEST	TEST METHOD
(i)	HARDNESS	$\begin{matrix} +5 \\ 65 \\ -2 \end{matrix}$ IRHD Shore A.	T	IS: 3400 (Pt 2)
(ii)	SPECIFIC GRAVITY	1.33 $\pm$ 0.04	T	METHOD B OF IS: 3400 (Pt-9)
(iii)	TENSILE STRENGTH	12.6 MPa MIN.	T	IS:3400(Pt-2)
(iv)	ELONGATION AT BREAK	250% MIN..	T	IS:3400 (Pt-1)
(v)	COMPRESSION SET $\begin{matrix} +0 \\ 24 \\ -2 \end{matrix}$ HRS. AT 70°C	20 % MAX.	T1	IS:3400 (Pt-10) LARGE TYPE TEST SPECIMEN.
(vi)	ADHESION TO AND CORROSION OF METALS FOR 168HRS AT 70°C	THERE SHALL BE NO CORROSION OR PITTING OF THE METALS. COMPOUND SHALL NOT ADHERE TO THE METAL OR SHOW ANY SIGN OF LIQUID EXTRACTION	T1	BS 903 PT A 37 METHOD A, USING CARBON STEEL
(vii)	ADHESION TO POLYIMIDE 6 FABRIC	45 N / 2.5 cm WIDTH OF STRIP (MIN.)	T1	TEST SPECIMEN TO IS:3400 (Pt-5) TESTING BY MANUFACTURER'S GLUE METHOD
(viii)	RESISTANCE TO HEAT AGEING FOR 168 HRS AT 100°C IN AIR a) CHANGE IN HARDNESS b) CHANGE IN TENSILE STRENGTH c) CHANGE IN ELONGATION AT BREAK	$\begin{matrix} +10\% \text{ MAX.} \\ -25\% \text{ MAX.} \\ -40\% \text{ MAX.} \end{matrix}$	T1	IS:3400 (Pt-4) IS: 3400 (Pt-2) IS: 3400 (Pt-1) IS: 3400 (Pt-1)

COPYRIGHT AND CONFIDENTIAL
Information on this document is the property of BHARAT HEAVY ELECTRICALS LIMITED. It must not be used directly or indirectly in any way detrimental to the interest of the Company.

Page 3 of 10

Rev 04

13/7/

SPECIFICATION REVISED

विनियम

DISTRIBUTION
INTERNAL
EXTERNAL
OTHERS

म.

व्याकृत किया

APPROVED: sd BSB, SNA

आपका प्रोप. अधिकार सुरक्षित

दिनांक

DAY

MONTH



Form No. 2038

उत्पाद मानक

परिणामित्र

आप/अभि. निर्देश

PRODUCT STANDARD

TRANSFORMER

SHOP/ENGG INSTRUCTIONS

TR 10150A

10 पृष्ठों में 4

PAGE 4 OF 10

TITLE : FLEXIBLE SEPARATOR (AIR CELL)

(ix)	AGEING IN TRANSFORMER OIL TO IS:335 AT 100°C FOR 168 HRS CHANGE IN PROPERTIES OF RUBBER COMPOUND AFTER AGEING.		T1	IS : 3400 (Pt-6)
	(a) MASS (b) VOLUME (c) HARDNESS (d) TENSILE STRENGTH (e) ELONGATION AT BREAK	+ 3 % MAX. + 10% MAX ± 3 IRHD MAX. -15% MAX. -35% MAX.		IS: 3400 (Pt-9) IS : 3400 (Pt-6) IS : 3400 (Pt-2) IS : 3400 (Pt-1) IS : 3400 (Pt-1)
(x)	AGEING OF OIL AS PER BS 5354 (a) INCREASE IN ACIDITY (b) INCREASE IN SLUDGE CONTENT	0.1 Mg KOH/gm MAX. 0.05% MAX.	T2	IS: 1448 (Pt-2) IS: 12177 TO BE TESTED AT BHEL USING ONE STD. TEST SLAB SUPPLIED BY MANUFACTURER . SIZE 3x12.5 x 75 mm
(xi)	AGEING IN TRANSFORMER OIL TO IS:335 AT 100 °C FOR 30 DAYS. (a) CHANGE IN HARDNESS (b) CHANGE IN VOLUME	±5 IRHD MAX... + 12% MAX.	T2	IS: 3400 (Pt-6) IS:3400 (Pt-2) IS:3400 (Pt-6)
(xii)	FLEXIBILITY AT LOW TEMPERATURE (-10°C)	SHALL NOT CRACK OR BECOME BRITTLE	T1	SAMPLE WILL BE KEPT IN COLD CHAMBER FOR 5 HRS AND THEN BENT BY 180°C ON A MANDREL OF 3mm DIA.
(xiii)	COLOUR	BLACK	T	VISUAL

COPYRIGHT AND CONFIDENTIAL
 The information on this document is the property of BHARAT HEAVY ELECTRICALS LIMITED. It must not be used directly or indirectly in any way detrimental to the interest of the Company.

PART 4 OF 10

Rev 04

13/7 2019

SPECIFICATION REVISED

वितरण

DISTRIBUTION

INTERNATIONAL

BY AIR

C. D. S. S. S. S.

P. S. S.

म.

प्रोक्त किया

APPROVED : sd BSB, SNA

प्रोक्त किया

प्रोक्त किया

प्रोक्त किया

प्रोक्त किया

प्रोक्त किया

प्रोक्त किया

प्रोक्त किया



Form No. 2038

उत्पाद मानक

परिणामित्र

श्रीप/अभि. निर्देश

PRODUCT STANDARD

TRANSFORMER

SHOP/ENGG INSTRUCTIONS

TR 10150A

109 पृष्ठा में 5

PAGE 5 OF 10

TITLE : FLEXIBLE SEPARATOR (AIR CELL)**3.2.2. AIR SIDE UNDER COATING****MATERIAL - CHLOROPRENE RUBBER COMPOUND C 60 OF BS 2752**

SL. NO	PROPERTY	REQUIREMENT	TYPE OF TEST	TEST METHOD
(i)	HARDNESS	$\begin{matrix} +5 \\ 60-64 \end{matrix}$ IRHD	T	IS:3400 (Pt-2)
(ii)	SPECIFIC GRAVITY	1.36 ± 0.04	T	IS:3400 (Pt-9) METHOD B
(iii)	TENSILE STRENGTH	13 Mpa MIN.	T	IS:3400 (Pt-1)
(iv)	ELONGATION AT BREAK	250 % MIN.	T	IS:3400 (Pt-1) LARGE TYPE TEST SPECIMEN
(v)	COMPRESSION SET $\begin{matrix} +10 \\ -2 \end{matrix}$ HRS. AT 70° C.	25 % MAX.	T1	IS:3400 (Pt-10)
(vi)	RESISTANCE TO HEAT AGEING, 168HRS AT 100°C IN AIR (a) CHANGE IN HARDNESS (b) CHANGE IN TENSILE STRENGTH (c) CHANGE IN ELONGATION AT BREAK	$\begin{matrix} + 10\% \text{ MAX.} \\ - 25\% \text{ MAX} \\ - 40\% \text{ MAX} \end{matrix}$	T1	$\begin{matrix} \text{IS:3400 (Pt-4)} \\ \text{IS:3400 (Pt-2)} \\ \text{IS:3400 (Pt-1)} \\ \text{IS:3400 (Pt-1)} \end{matrix}$
(vii)	ADHESION TO AND CORROSION OF METALS 168HRS AT 70°C.	THERE SHALL BE NO CORROSION OR PITTING OF THE METAL AND COMPOUND SHALL NOT ADHERE OR SHOW ANY SIGN OF LIQUID EXTRACTION	T1	BS 903 Pt-A 37 METHOD A USING CARBON STEEL
(viii)	ADHESION TO POLYAMIDE 6 FABRIC	45N/2.5 cm WIDTH OF STRIP. MIN.	T1	TEST SPECIMEN TO IS: 3400 (Pt-5) TESTING BY MANUFACTURER'S GLUE METHOD
(ix)	FLEXIBILITY AT LOW TEMP. (AT - 10° C)	SHALL NOT CRACK OR BECOME BRITTLE	T1	SAMPLE SHALL BE KEPT IN COLD CHAMBER FOR 5hrs AND THEN BENT BY 180° ON A MANDREL OF 3mm DIA
(x)	COLOUR	BLACK	I	VISUAL

COPYRIGHT AND CONFIDENTIAL
 Information on this document is the property of BHARAT HEAVY ELECTRICALS LIMITED. It must not be used directly or indirectly in any way detrimental to the interest of the Company.

SPECIFICATION REVISED

विनिर्माण

DISTRIBUTION

TRITEX/EMI

TRX/110

Q. No. 13-07

TRX/110

मं.

मं. किया :

APPROVED: SUBSB, SNA

निर्माण क्र. TR110 निर्माण क्र. TR110

निर्माण क्र. TR110 निर्माण क्र. TR110

निर्माण क्र. TR110

निर्माण क्र.

TR110

TR110

TR110

Rev

04

13-07

13-07

13-07



Form No. 2038

उत्पाद मानक

परिणामित्र

शाप/अभि. निर्देश

PRODUCT STANDARD

TRANSFORMER

SHOP/ENGG INSTRUCTIONS

TR 10150A

10 पृष्ठा में 6

PAGE 6 OF 10

TITLE : FLEXIBLE SEPARATOR (AIR CELL)

3.2.3 AIR SIDE OUTER COATING: COMPOUND MATERIAL-----HYPALON 40

SL. NO.	PROPERTY	REQUIREMENT	TYPE OF TEST	TEST METHOD
(i)	HARDNESS	65±5 IRHD SHORE A	T1	IS : 3400(Pt-2)
(ii)	SPECIFIC GRAVITY	1.6 ± 0.05	T1	IS : 3400 (Pt-9) METHOD - B
(iii)	TENSILE STRENGTH	8 M pa MIN.	T1	IS : 3400 (Pt-1)
(iv)	ELONGATION AT BREAK	250% MIN.	T1	IS : 3400 (Pt-1)
(v)	FLEXIBILITY AT LOW TEMP. (AT -10°C)	SHALL NOT CRACK OR BECOME BRITTLE	T1	SAMPLE SHALL BE KEPT IN COLD CHAMB- FOR 5 HRS. & THEN BENT BY 180° ON MANDREL OF 3mm DIA.
(vi)	RESISTANCE TO HEAT AGEING IN AIR 168HRS AT 100 °C (a) CHANGE IN HARDNESS (b) CHANGE IN TENSILE (c) CHANGE IN ELONGATION AT BR EAK	+10% MAX -25% MAX -40% MAX	T1	IS: 3400 (Pt-2) IS:3400 (Pt-1) IS :3400 (Pt-1)
(vii)	RESISTANCE TO OZONE (O3) FOR 96 HRS. AT 40°C O3 CONCENTRATION 200 ± 20 PPHM	SHALL NOT DEVELOP CRACKS	T2	IS: 3400 (Pt 20)
(viii)	COLOUR	OLIVE GREEN	T	VISUAL

COPYRIGHT AND CONFIDENTIAL
 The information on this document is the property of BHARAT HEAVY ELECTRICALS LIMITED. It must not be
 used directly or indirectly in any way detrimental to the interest of the Company.

PAGE 6 OF 10

REV 04

13/07

SPECIFICATION REVISED

वितरण

DISTRIBUTION

THE TRIPUR

TRIPUR

TRIPUR

TRIPUR

TRIPUR

मं.

गोपनीय किया :

APPROVED : S. R. S. S. N. A.

APPROVED : S. R. S. S. N. A.

APPROVED : S. R. S. S. N. A.

APPROVED : S. R. S. S. N. A.

APPROVED : S. R. S. S. N. A.

APPROVED : S. R. S. S. N. A.

दस्तावेज

दस्तावेज

दस्तावेज

दस्तावेज

दस्तावेज

TITLE : FLEXIBLE SEPERATOR (AIR CELL)

4.0 COATED FABRIC :-

Sl. No	PROPERTY	REQUIREMENT	TYPE OF TEST	TEST METHOD
(i)	MATERIAL	NYLON6, PLAIN WEAVE, FABRIC OF SUITABLE CONSTRUCTION	T	IS : 667 - 1981
(ii)	THICKNESS	POLYIMIDE FABRIC 0.5±0.05mm COATED FABRIC 1.25±0.1 mm	T	IS : 7702 IS : 7016 (Pt-1)
(iii)	MASS OF POLYIMIDE FABRIC	OIL SIDE COATING 455g/m ² MIN COMBINED AIR SIDE UNDER & OUTER COATING 615g/m ² MIN COATED FABRIC 1400 ⁺²⁰⁰ ₋₈₀ g/m ²	T	IS : 7016 (Pt-1)
(iv)	WEIGHT OF BASIC FABRIC	200 g/m ² MIN	T	IS : 7016 (Pt-1)
(v)	COLOUR OF	AIR SIDE OLIVE GREEN OIL SIDE BLACK	T	VISUAL
(vi)	TEAR STRENGTH ALONG THE WARP ALONG THE WEFT	300 N, MIN.	T	IS : 7016 (Pt-3)
(vii)	BREAKING STRENGTH ALONG THE WARP ALONG THE WEFT WIDTH MIN.	3 kN/50 mm	T	IS : 7016 (Pt-2)
(viii)	ELONGATION AT BREAK ALONG THE WARP ALONG THE WEFT	25% MIN 30% MIN	T	IS : 7016 (Pt-2)
(ix)	AIR PERMEABILITY	5X10 ⁻¹² cm ³ .cm MAX cm ² S.cm. Hg	T2	A STM - D 1334
(x)	LOW TEMP BEND TEST AT -20°C.	SHALL PASS	T1	IS : 7016 (Pt-10) SPECIMEN SHALL BE KEPT IN COLD CHAMBER FOR 5HRS AND THEN BENT BY 180° ON A MANDREL OF 3mm DIA
(xi)	BURSTING STRENGTH	7 MPa MIN.	T2	IS : 7016 (Pt - 6) METHOD -A : METHOD-B
(xii)	RESISTANCE TO PERFORATION	390 N MIN.	T1	MANUFACTURER'S METHOD
(xiii)	RESISTANCE TO DAMAGE BY FLEXING	SHALL WITH STAND 100000 CYCLES WITH OUT DAMAGE	T1	IS : 7016 (Pt-4) SPECIMEN SIZE WILL BE 25mm X 150 mm TESTING WITHOUT FOLDING
(xiv)	BLOCKING RESISTANCE	NO BLOCKING	T1	IS : 7016 (Pt-9)
(xv)	MEASUREMENT OF CUP GROWTH	SHALL PASS THE TEST	T1	MANUFACTURER'S METHOD

~~SPECIFICATION REVISED~~

नित्यगण

DESIRABLE LOSS

REF ID: A61111

$$|R_N| = 10$$

0 9 1 2 3 4 5 6 7 8 9 10

सं.

प्राकृत क्रिया :

APPROVED: SUBS. SNA

SEP 11 1981

निम्नलिखित

1994

1997, 1998, 1999, 2000, 2001, 2002, 2003, 2004, 2005, 2006, 2007, 2008, 2009, 2010, 2011, 2012, 2013, 2014, 2015, 2016, 2017, 2018, 2019, 2020, 2021, 2022, 2023, 2024, 2025, 2026, 2027, 2028, 2029, 2030, 2031, 2032, 2033, 2034, 2035, 2036, 2037, 2038, 2039, 2040, 2041, 2042, 2043, 2044, 2045, 2046, 2047, 2048, 2049, 2050, 2051, 2052, 2053, 2054, 2055, 2056, 2057, 2058, 2059, 2060, 2061, 2062, 2063, 2064, 2065, 2066, 2067, 2068, 2069, 2070, 2071, 2072, 2073, 2074, 2075, 2076, 2077, 2078, 2079, 2080, 2081, 2082, 2083, 2084, 2085, 2086, 2087, 2088, 2089, 2090, 2091, 2092, 2093, 2094, 2095, 2096, 2097, 2098, 2099, 2100, 2101, 2102, 2103, 2104, 2105, 2106, 2107, 2108, 2109, 2110, 2111, 2112, 2113, 2114, 2115, 2116, 2117, 2118, 2119, 2120, 2121, 2122, 2123, 2124, 2125, 2126, 2127, 2128, 2129, 2130, 2131, 2132, 2133, 2134, 2135, 2136, 2137, 2138, 2139, 2140, 2141, 2142, 2143, 2144, 2145, 2146, 2147, 2148, 2149, 2150, 2151, 2152, 2153, 2154, 2155, 2156, 2157, 2158, 2159, 2160, 2161, 2162, 2163, 2164, 2165, 2166, 2167, 2168, 2169, 2170, 2171, 2172, 2173, 2174, 2175, 2176, 2177, 2178, 2179, 2180, 2181, 2182, 2183, 2184, 2185, 2186, 2187, 2188, 2189, 2190, 2191, 2192, 2193, 2194, 2195, 2196, 2197, 2198, 2199, 2200, 2201, 2202, 2203, 2204, 2205, 2206, 2207, 2208, 2209, 2210, 2211, 2212, 2213, 2214, 2215, 2216, 2217, 2218, 2219, 2220, 2221, 2222, 2223, 2224, 2225, 2226, 2227, 2228, 2229, 2230, 2231, 2232, 2233, 2234, 2235, 2236, 2237, 2238, 2239, 2240, 2241, 2242, 2243, 2244, 2245, 2246, 2247, 2248, 2249, 2250, 2251, 2252, 2253, 2254, 2255, 2256, 2257, 2258, 2259, 2260, 2261, 2262, 2263, 2264, 2265, 2266, 2267, 2268, 2269, 2270, 2271, 2272, 2273, 2274, 2275, 2276, 2277, 2278, 2279, 2280, 2281, 2282, 2283, 2284, 2285, 2286, 2287, 2288, 2289, 2290, 2291, 2292, 2293, 2294, 2295, 2296, 2297, 2298, 2299, 2300, 2301, 2302, 2303, 2304, 2305, 2306, 2307, 2308, 2309, 2310, 2311, 2312, 2313, 2314, 2315, 2316, 2317, 2318, 2319, 2320, 2321, 2322, 2323, 2324, 2325, 2326, 2327, 2328, 2329, 2330, 2331, 2332, 2333, 2334, 2335, 2336, 2337, 2338, 2339, 2340, 2341, 2342, 2343, 2344, 2345, 2346, 2347, 2348, 2349, 2350, 2351, 2352, 2353, 2354, 2355, 2356, 2357, 2358, 2359, 2360, 2361, 2362, 2363, 2364, 2365, 2366, 2367, 2368, 2369, 2370, 2371, 2372, 2373, 2374, 2375, 2376, 2377, 2378, 2379, 2380, 2381, 2382, 2383, 2384, 2385, 2386, 2387, 2388, 2389, 2390, 2391, 2392, 2393, 2394, 2395, 2396, 2397, 2398, 2399, 2400, 2401, 2402, 2403, 2404, 2405, 2406, 2407, 2408, 2409, 2410, 2411, 2412, 2413, 2414, 2415, 2416, 2417, 2418, 2419, 2420, 2421, 2422, 2423, 2424, 2425, 2426, 2427, 2428, 2429, 2430, 2431, 2432, 2433, 2434, 2435, 2436, 2437, 2438, 2439, 2440, 2441, 2442, 2443, 2444, 2445, 2446, 2447, 2448, 2449, 2450, 2451, 2452, 2453, 2454, 2455, 2456, 2457, 2458, 2459, 2460, 2461, 2462, 2463, 2464, 2465, 2466, 2467, 2468, 2469, 2470, 2471, 2472, 2473, 2474, 2475, 2476, 2477, 2478, 2479, 2480, 2481, 2482, 2483, 2484, 2485, 2486, 2487, 2488, 2489, 2490, 2491, 2492, 2493, 2494, 2495, 2496, 2497, 2498, 2499, 2500, 2501, 2502, 2503, 2504, 2505, 2506, 2507, 2508, 2509, 2510, 2511, 2512, 2513, 2514, 2515, 2516, 2517, 2518, 2519, 2520, 2521, 2522, 2523, 2524, 2525, 2526, 2527, 2528, 2529, 2530, 2531, 2532, 2533, 2534, 2535, 2536, 2537, 2538, 2539, 2540, 2541, 2542, 2543, 2544, 2545, 2546, 2547, 2548, 2549, 2550, 2551, 2552, 2553, 2554, 2555, 2556, 2557, 2558, 2559, 2560, 2561, 2562, 2563, 2564, 2565, 2566, 2567, 2568, 2569, 2570, 2571, 2572, 2573, 2574, 2575, 2576, 2577, 2578, 2579, 2580, 2581, 2582, 2583, 2584, 2585, 2586, 2587, 2588, 2589, 2590, 2591, 2592, 2593, 2594, 2595, 2596, 2597, 2598, 2599, 2600, 2601, 2602, 2603, 2604, 2605, 2606, 2607, 2608, 2609, 2610, 2611, 2612, 2613, 2614, 2615, 2616, 2617, 2618, 2619, 2620, 2621, 2622, 2623, 2624, 2625, 2626, 2627, 2628, 2629, 2630, 2631, 2632, 2633, 2634, 2635, 2636, 2637, 2638, 2639, 2640, 2641, 2642, 2643, 2644, 2645, 2646, 2647, 2648, 2649, 2650, 2651, 2652, 2653, 2654, 2655, 2656, 2657, 2658, 2659, 2660, 2661, 2662, 2663, 2664, 2665, 2666, 2667, 2668, 2669, 2670, 2671, 2672, 2673, 2674, 2675, 2676, 2677, 2678, 26

पृष्ठ :
Rev
04

1275

157

TITLE : FLEXIBLE SEPARATOR (AIR CELL)

VISUAL TESTING:

1. LONGITUDINAL/VERTICAL FOLD ALONG THE LENGTH IS NOT ACCEPTABLE.
2. FABRIC FOLD UPTO 150 mm IS ALLOWED ACROSS THE WIDTH
3. PRESENCE OF FABRIC CONSECUTIVE KNOTS WITHIN DISTANCE OF 2 METERS IS NOT ACCEPTABLE.
4. MISSING CORDS, FABRIC HOLE MORE THAN 0.5 MM DIA IS NOT ACCEPTABLE
5. TIGHT EDGE, BAGGINESS ARE NOT ACCEPTABLE

5. TESTING OF FLEXIBLE SEPARATOR:

- (i) SURFACE FINISH (ROUTINE CHECK) :
SHALL HAVE GOOD SURFACE FINISH . FREE FROM DEEP LINES,PITS UNCOATED AREA, PIN HOLES, CRACKS, PAINT MARK ETC.SURFACE SHOULD BE CLEAN AND FREE FROM DUST, SOIL AND OTHER EXTRANEIOUS MATTER. COATING SHALL BE UNIFORM WITHOUT ANY PATCH WORK..
- (ii) SEPARATOR SHALL BE INFLATED & DEFLATED TEN TIMES.THE PRESSURE SHALL BE 10 Kpa (0.105kg cm2 OR 1.5 PSI). THERE SHALL NOT BE ANY VISIBLE SIGN OF DAMAGE TO SEPARATOR (ROUTINE TEST). *ADDITION TO THIS ALL THE AIR CELL ARE CHECK WITH THE AIR PRESSURE OF 0.1KG/cm2sq. FOR THIS SHIPPING AREA AFTER FITTING IN CONSERVATOR.*
- (iii) SEPARATOR SHALL BE INFLATED AT 10KPa (0.105Kg/cm2 OR 1.5 PSI) AND SHALL BE KEPT FOR 24HRS THERE SHALL NOT BE ANY LEAKAGE/SEEPAGE OF THE AIR (ROUTINE TEST).
- (iv) DIMENSIONS AS PER FIG.1 ON PAGE-9 OF TR 10150 A AND BHEL PURCHASE ORDER/ROUTINE CHECK)

6. PACKING:

FLEXIBLE SEPARATORS SHALL BE PROPERLY FOLDED AND WRAPPED IN POLYETHENE SHEET AND THEN PACKED IN PAPER BOARD BOXES TO AVOID DAMAGE IN TRANSIT BOXES TO BE PROPERLY STRAPPED.

7. GUARANTEE, WARRANTY CERTIFICATE, REPAIR INSTRUCTIONS STORAGE HANDLINE & INSTALLATION INSTRUCTIONS SHALL BE FURNISHED ALONG WITH EACH SEPARATOR.
8. THE MANUFACTURER'S LOGO SHALL BE SCREEN PRINTED ON AIR CELL. INK USED FOR PRINTING SHALL BE COMPATIBLE WITH TRANSF. OIL.
9. CODES FOR TYPE OF TEST INDICATED IN PARA 3 & 4 ABOVE ARE AS UNDER:

T1	ROUTINE TEST
T11	TYPE TEST (ONCE IN 3 YEARS)
T2	TYPE TEST (ONCE IN FIVE YEARS)

~~SPECIFICATION REVISED~~

विनायक
DISTRIBUTION
TRIPURMUKHI
TRIPURMUKHI
TRIPURMUKHI
TRIPURMUKHI
TRIPURMUKHI

म. प्रमाणित किया :
APPROVED : sd BSB, SNA

प्राप्त किया। 1981-82 वर्ष में प्राप्त किया। 1980-81


द्वितीयः

[[3 N 1 !


Abstract

REF ID: A66057
TITLE : FLEXIBLE SEPARATOR (AIR CELL)

OIL SIDE (OUTSIDE)




SECTION B-B
(DETAIL-Y)




JOINT DETAIL SECTION A-A


SIZE OF AIRCELL	Z
LARGE	35
MEDIUM	30
SMALL	25



SECTION C-C




DETAILS OF OVERLAP JOINT



A&D ARE CONSERVATOR LENGTH AND DIA

REINFORCEMENT ON
AIR CELL BOTTOM



DETAIL-X

FIG. — 1

REF. _____
COUNT. _____

ELECTRICALS

SI No. 2902276590



VR 10150A
PAGE 9 OF 10

REF: Sd/BSB, SNA



Form No. 2038

उत्पाद मानक

परिणामित्र

शाप/अभि. निर्देश

PRODUCT STANDARD

TRANSFORMER

SHOP/ENGG INSTRUCTIONS

TR 10150A

10पृष्ठों में 10

PAGE 10 OF 10

TITLE : FLEXIBLE SEPERATOR (AIR CELL)

DIMENSIONS AND TOLERANCES OF FLEXIBLE AIR CELL IN THE DEFLATED CONDITION

S.No.	WIDTH W $\pm$ 1.5%	LENGTH L $\pm$ 1.5%	DISTANCE BETWEEN LOOPS G $\pm$ 10	
1	825	3035	2010	SMALL
2	980	2350	1170	
3	982	3230	2050	
4	1140	2620	1280	
5	1140	3270	1930	
6	1295	2755	1260	MEDIUM
7	1455	2435	780	
8	1295	3745	2250	
9	1455	3215	1560	
10	1455	3995	2340	
11	1610	3490	1680	LARGE
12	1610	4130	2320	
13	1770	3670	1700	
14	1770	4190	2220	
15	1925	3775	1650	
16	1925	4665	2540	
17	2080	4230	1950	
18	2080	4980	2700	
19	2240	4550	2110	
20	2240	5200	2750	
21	2395	4795	2200	
22	2240	5850	2200	

NOTE: ALL DIMENSIONS ARE IN mm.

Page 10 of 10

SPECIFICATION REVISED

वितरण

DISTRIBUTION

TRITRUM

TRITRUM

TRITRUM

गो.

गो.कृत किया

APPROVED BY SIBSR, SNA

गो.कृत किया

गो.कृत किया

गो.कृत किया

गो.कृत किया

गो.कृत किया

गो.कृत किया

गो.कृत किया

गो.कृत किया

गो.कृत किया

13/07