



PLANT PURCHASE SPECIFICATION (CFFP - HARDWAR)

FF 05008 Rev 06

Page 1 of 3

HIGH CARBON FERRO CHROME

1. SCOPE

This specification governs the quality of High carbon Ferro Chrome with the following requirements.

2. APPLICATION

The material shall be used as alloying addition for manufacturing of alloy steel

3. CONDITION OF DELIVERY

The size should be in the range of 10-100 mm. However oversized material should not exceed 10% by weight and undersized material should not exceed 15% by weight.

4. COMPLIANCE WITH NATIONAL STANDARDS

The specification in general is based on Indian standard IS: 1170-1992, Grade: 7FeCr-65.

5. FREEDOM FROM CONTAMINATION

The material shall be free from extraneous contamination such as slag.

6. CHEMICAL COMPOSITION

The material shall conform to the following chemical composition when it is analyzed in accordance with IS: 1559. Composite sample shall be prepared by drawing samples from each consignment of 1000Kg or part thereof.

ELEMENT	% MIN	%MAX
Carbon	6.0	8.0
Chromium	60	70
Silicon	-	2.0
Sulphur	-	0.10
Phosphorus	-	0.10

Trace elements are for information purpose only.

The test results are to be rounded off as per IS 2-1960 (reaffirmed 2000).

PURCHASE	RANJAN KUMAR	<i>Ranjan</i>	SMS TECHNOLOGY	RANJAN	<i>Ranjan</i>
MPIC	SHANTANU	<i>Shantanu</i>	RMI	S.N.GHOSH	<i>Ranjan</i>
CHAIRMAN PPSC	R PARTHASARATHY	<i>4/12/10</i> <i>27.12.10</i>	SECRETARY PPSC	Dr M.S.RAWAT	<i>27/12/10</i>
			APPROVED : PLANT STANDARDS COMMITTEE		
			PREPARED : SMS TECH	ISSUED : Steel Melting Shop	DATE : <i>24-12-10</i>



PLANT PURCHASE SPECIFICATION

FF 05008 Rev 06

(CFFP - HARDWAR)

Page 2 of 3

7. INSPECTION AT SUPPLIER'S WORKS:

- CFFP reserves the right to witness the testing of the material at supplier works and therefore the supplier shall notify the readiness of the material in advance.
- CFFP may, at its discretion, test the material after receipt and acceptance of the material will be based on the CFFP'S test results.
- Supplier shall ensure that the material is free from extraneous contamination. The material shall be rejected if it is not free from extraneous material.
- For result of analysis and properties of material the decision of CFFP shall be final and binding on the supplier.

8. TEST CERTIFICATES

One Original and three copies of Test Certificate from the **Manufacturer** containing the following information **along with test result of clause 3 and the chemical composition as per clause 6** should be provided.

Manufacturer's Name
Name of the material
Quantity.

Note:

- a) A manufacturer supplying directly to BHEL should include BHEL's P.O. No. and Challan No. also in the TC.
- b) Any other supplier should provide a covering letter along with original Manufacturer's TC as above mentioning BHEL's P.O. No. and Challan No. Supplier shall give the packing detail of material in the guarantee certificate.

9. PACKING AND MARKING

The material shall be packed such as to prevent loss / deterioration in quality during handling, transport and storage. It should be in the manufacturer's packing. Each package should be marked with the following details.

Name of the material
Manufacturer's Name / Trade mark
Net weight.

10. REFFERED STANDARDS

IS: 1170 , IS: 1559

WORKED
BY

RANJAN

Ranjan 24/12/10

Handwritten signature and date: 27/12/10

COPYRIGHT AND CONFIDENTIAL

The information on this documents is the property of Bharat Heavy Electrical Limited. It must not be used, directly or indirectly, in any way detrimental to the interest of the company.

**REVISION RECORD SHEET**

SN	Revision No.	Revision date	Nature of Changes
01.	04	20.10.2006	- Clauses 3 & 7 modified.
02.	05	07.09.2009	- Clauses 8 and 9 revised incorporating requirement of manufacturer's packing and Test certificate.
03	06	24.12.2010	- Clause 3: Redefined. - Clause 6: The limit for S & P increased to 0.1 % from 0.05%. The sampling of material for chemical analysis will be done as per this specification. - Clause 8 & 9: Batch no & lot no removed.

WORKED
BY

RANJAN

Ranjan 24/12/10*Y. N. Mehta*
27.12.10