

VOLUME II

2 X 800 MW NTPC KARIMNAGAR SG PACKAGE PH1

TECHNICAL SPECIFICATION

FOR

LT XLPE POWER CABLES

SPECIFICATION NO: *PE-TS-424-507-E001*

REVISION: 0



BHARAT HEAVY ELECTRICALS LIMITED

POWER SECTOR

PROJECT ENGINEERING MANAGEMENT

NOIDA, UP (INDIA) – 201301



DOCUMENT TITLE

TECHNICAL SPECIFICATION FOR
LT XLPE POWER CABLES

SPECIFICATION NO. PE-TS- 424-507-E001

VOLUME II

REVISION 0

DATE: 28.11.17

SHEET

CONTENTS

<u>S. NO.</u>	<u>DESCRIPTION</u>	<u>NO. OF SHEETS</u>
1.	CONTENTS	01
2.	COMPLIANCE CERTIFICATE	01
3.	SECTION – I	
	a) SPECIFIC TECHNICAL REQUIREMENTS	02
	b) DATA SHEET-A	03
	c) DATA SHEET-C (GUARANTEED TECHNICAL PARTICULARS)	03
4.	SECTION – II	
	a) GENERAL TECHNICAL SPECIFICATION	01
	b) QUALITY PLAN (ALONGWITH ANNEXURE A TO QP)	13
	c) ANNEXURE-B TO SECTION-II	02
	d) ANNEXURE-C	04
	TOTAL NO. OF SHEETS=	33
	(INCLUDING COVER/ SEPARATOR SHEETS)	



DOCUMENT TITLE

TECHNICAL SPECIFICATION FOR
LT XLPE POWER CABLES

SPECIFICATION NO. PE-TS- 424-507-E001

VOLUME II

REVISION 0

DATE: 28.11.2017

SHEET 1 of 1

COMPLIANCE CERTIFICATE

The bidder shall confirm compliance to the following by signing/ stamping this compliance certificate and furnishing same with the offer.

1. The scope of supply, technical details, construction features, design parameters etc. shall be as per technical specification & there are no exclusion/ deviation with regard to same
2. There are no deviation with respect to specification other than those furnished in the 'schedule of deviations'
3. Only those technical submittals which are specifically asked for in NIT to be submitted at tender stage shall be considered as part of offer. Any other submission, even if made, shall not be considered as part of offer.
4. Any comments/ clarifications on technical/ inspection requirements furnished as part of bidder's covering letter shall not be considered by BHEL, and bidder's offer shall be construed to be in conformance with the specification.
5. Any changes made by the bidder in the price schedule with respect to the description/ quantities from those given in 'BOQ-Cum-Price schedule' of the specification shall not be considered (i.e., technical description & quantities as per the specification shall prevail).

BIDDER'S STAMP & SIGNATURE



DOCUMENT TITLE

TECHNICAL SPECIFICATION FOR
LT XLPE POWER CABLES

SPECIFICATION NO. PE-TS- 424-507-E001

VOLUME II

SECTION I

REVISION - 0

DATE: 28.11.2017

SECTION –I

SPECIFIC TECHNICAL REQUIREMENTS



DOCUMENT TITLE

TECHNICAL SPECIFICATION FOR
LT XLPE POWER CABLES

SPECIFICATION NO. PE-TS- 424-507-E001

VOLUME II

SECTION I

REVISION - 0

DATE: 28.11.2017

SHEET 1 OF 2

1.0 SCOPE OF ENQUIRY

- 1.1 Design, Manufacture, Inspection and Testing at Manufacturer's works, proper packing and delivery to site of LT XLPE POWER CABLES conforming to this specification.
- 1.2 General technical requirements of the LT XLPE Power cables are indicated in Section-II. Project specific technical/ quality requirements / changes are listed in Section-I.
- 1.3 The stipulations of Section-I, followed by those of Data Sheet-A shall prevail in case of any conflict between the stipulations of Section-I, Data Sheet - A & Section-II.
- 1.4 The documents shall be in English Language and MKS system of units.

2.0 BILL OF QUANTITIES:

- 2.1 Quantity requirements shall be as per 'BOQ-cum-price schedule' as part of NIT.

3.0 SPECIFIC TECHNICAL REQUIREMENTS

<u>S.No.</u>	<u>Reference Clause No. of Section- II</u>	<u>Specific Requirement/ Change</u>
1	3.1	BHEL Standard Quality Plan (PE-QP-999-507-E002) shall be read as "QP. NO. 0000-999-QOE-S-041, REV-00". Additionally, The QP. NO. 0000-999-QOE-S-041 REV-00 shall be read in conjunction with Annexure C (Quality Assurance & Inspection).
2.	3.3	Additionally, Successful bidder shall submit the reports of all the type tests as listed in this specification and carried out within last ten years from the date of bid opening i.e. 29.06.15. These reports should be for the test conducted on the equipment similar to those proposed to be supplied under this contract and the test(s) should have been either conducted at an independent lab or should have witnessed by a client. The reports of type test shall be submitted for one size of each LT XLPE power cable.

4.0 DRAWINGS & DOCUMENTS TO BE SUBMITTED



DOCUMENT TITLE

TECHNICAL SPECIFICATION FOR
LT XLPE POWER CABLES

SPECIFICATION NO. PE-TS- 424-507-E001

VOLUME II

SECTION I

REVISION - 0

DATE: 28.11.2017

SHEET 2 OF 2

4.1 Following documents/drawings shall be submitted after placement of order for BHEL & customer's approval:-

Sl. No.	Drawings/Document Description	Drawings / Document Number
1.	Technical Data sheet - LT XLPE power cables	PE-V0-424-507-E111
2.	Cross-sectional Drgs.- LT XLPE Power Cables	PE-V0-424-507-E113
3.	Quality Plan - LT XLPE Power Cables	PE-V0-424-507-E913 *
4.	Steel drum drawing - LT XLPE Power Cables (if applicable)	PE-V0-424-507-E115

Note:

* Standard Quality Plan as enclosed in the technical specification is to be appended with cover sheet bearing document number and description as stated above. The signed and stamped copy of the same shall be submitted to BHEL without making any changes in the contents of the document.



DOCUMENT TITLE

TECHNICAL SPECIFICATION FOR LT
XLPE POWER CABLES

SPECIFICATION NO. PE-TS- 424-507-E001

VOLUME II

SECTION I

REVISION 0

DATE: 05.12.2017

SHEET 1 OF 3

DATA SHEET-A

CABLE DETAILS OF LT XLPE POWER CABLES

1.0	Type of Cable	Flame Retardant Low Smoke (FR-LSH)	
2.0	Standard applicable in general(Latest amendment to be referred if any)	IS:7098 (Part-1), IS:8130, IS:5831, IS:10810, IS:3975, ASTM:2843, ASTM:2863, IEC-754-1,IEC:60332-3-23, IEEE:60383,IS-10418	
3.0	Voltage Grade	1.1kV	
4.0	Number of cores, cross sectional area of conductors and quantities	As per BOQ cum price schedule	
5.0	FAULT CHARACTERISTICS		
	Fault Level	50kA	
	Fault Clearing Time	1 sec	
6.0	CONDUCTOR		
(a)	Material	Aluminium (With Tensile strength more than 100N/sq.mm.)	Copper
	Grade and Class	Stranded, H2, Class 2	Stranded, annealed plain high conductivity, Class 2
(b)	Standard Applicable	IS: 8130	
(c)	Shape	Compacted Circular / shaped as per IS	
(d)	Min. number and diameter of strands for main and neutral conductor [Neutral conductor cross section w.r.t main conductor shall be as per Table-2 of IS: 7098 (Part-1)]	As per Table-2 of IS: 8130	
7.0	INSULATION		
(a)	Material	Cross-Linked Polyethylene(XLPE)	
(b)	Standard Applicable	IS: 7098 (Part-1)	
(c)	Continuous withstand temperature	90°C	
(d)	Short-circuit withstand temperature	250°C	
(e)	Method of application	By extrusion; sleeve extrusion not permitted.	
(f)	Nominal Thickness of insulation	As per IS: 7098 (Part-1)	
8.0	CORE IDENTIFICATION		Following colour scheme shall be adopted. 1 core - Red, Black, Yellow or Blue 2 core - Red & Black 3 core - Red, Yellow & Blue 4 core - Red, Yellow, Blue and Black. For reduced neutral conductors, the core shall be black.
9.0	INNER SHEATH		
(a)	Material	PVC Type ST-2	
(b)	Standard Applicable	IS: 7098 (Part-1) & IS: 5831	
(c)	Colour	Black	
(d)	Whether FR-LSH	NO	



DOCUMENT TITLE

TECHNICAL SPECIFICATION FOR LT
XLPE POWER CABLES

SPECIFICATION NO. PE-TS- 424-507-E001

VOLUME II

SECTION I

REVISION 0

DATE: 05.12.2017

SHEET 2 OF 3

(e)	Inner sheath applicable for single core cable	NO
(f)	Fillers	Acceptable
(g)	Material of fillers (if permitted)	Same as inner sheath (Material of filler to be compatible with that of inner sheath)
(h)	Method of application	
(1)	Multi-core cables:	
(i)	With fillers	Pressure/Vacuum extruded
(ii)	Without fillers	Pressure extruded
(2)	Single-core cables:	NA
10.0	ARMOUR	
(a)	Applicable	NA
(b)	Material:	
(i)	Single core cables	
(ii)	Multi-core cables	
(iii)	Standard Applicable	
(c)	Minimum Coverage	
(d)	Gap between armour wires	
(e)	Breaking load of joint	
11.0	OUTERSHEATH	
(a)	Material	PVC Type ST2 as per IS: 5831
(b)	Colour	Black
(c)	Whether FR-LSH	Yes
(d)	Method of application	Extruded
(e)	Thickness of outer sheath	As per Table-8 of IS: 7098 (Part-1)
(f)	Marking	Cable size (cross section area and no. of cores) and voltage grade @ 5m (by embossing) Word "XLPE" "FR-LSH" etc, @ 5m (by embossing) Manufacturer's name and/ or trade name, and year of manufacture @ 5m (by embossing) 'BHEL-PEM' and 'NTPC' Name @5m (by embossing) Progressive sequential marking @ 1m (by embossing/ printing)
12.0	FR-LSH CHARACTERISTICS	
(a)	Oxygen index	Min 29 (As per IS 10810 part-58), ASTM D 2863
(b)	Temperature index	Min. 250°C(As per ASTM D 2863)
(c)	Acid gas generation	Max. 20% by weight (As per IEC-60754-1)
(d)	Smoke density rating	Max. 60% (As per ASTM D 2843)
(e)	Flammability Test	
(i)	Flammability test for all cables	As per: IEC-60332 Part-3, CAT-B
13.0	TOLERANCE ON OUTER DIAMETER	± 2mm
14.0	MINIMUM BENDING RADIUS	
(a)	Single core cables	15 x O.D.
(b)	Multi core cables	12 x O.D.
15.0	SAFE PULLING FORCE	
(a)	Aluminium conductor cable	30 N/ sq. mm.
(b)	Copper conductor cable	50 N/ sq. mm.



DOCUMENT TITLE

TECHNICAL SPECIFICATION FOR LT
XLPE POWER CABLES

SPECIFICATION NO. PE-TS- 424-507-E001

VOLUME II

SECTION I

REVISION 0

DATE: 05.12.2017

SHEET 3 OF 3

16.0	CABLE DRUMS	
(a)	Type of Drum	Wooden as per IS 10418. OR Steel drum.
(b)	Standard drum length	750m ($\pm$) 5% - For sizes 150 sq. mm. & above 1000m ($\pm$) 5% - For all other sizes
(c)	Painting	Entire surface to be painted
(d)	Wooden Drum	The surface of the drum and the outer most cable layer shall be covered with water proof cover. Both the ends of the cables shall be properly sealed with heat shrinkable PVC/ rubber caps secured by 'U' nails so as to eliminate ingress of water during transportation, storage and erection. Wood preservative anti-termite treatment shall be applied to the entire drum.
(e)	Particular information on Drum	Each drum shall carry manufacturer's name, purchaser's name, address and contract no., item no. & type, size & length of cable and net gross weight stencilled on both sides of drum. A tag containing same information shall be attached to the leading end of the cable. An arrow & suitable accompanying wording shall be marked on one end of the reel indicating the direction in which it should be rolled.

	DOCUMENT TITLE TECHNICAL SPECIFICATION FOR LT XLPE POWER CABLES	SPECIFICATION NO. PE-TS-424- 507 –E001
		VOLUME II
		SECTION I
		REV NO. 0 DATE 28.11.2017
		SHEET 1 OF 3

DATASHEET C

GUARANTEED TECHNICAL PARTICULARS
(TO BE SUBMITTED BY SUCCESSFUL BIDDER)

S.No.		Unit	Description
1.0	General	-	
1.1	Name of manufacturer	-	
1.2	Place of Manufacture	-	
2.0	Standards Applicable		
2.1	IS: 7098 Part-I For general specification of XLPE Cables	-	YES
2.2	IS: 8130 For conductor material	-	YES
2.3	IS: 5831 For material of inner sheath & outer sheath.	-	YES
2.4	IS: 3975 / IS: 8130 For armour of 3 core/ single core cables	-	YES
2.5	IS: 10810 For method of tests	-	YES
2.6	IS:10418 For cable drums	-	YES
2.7	ASTMD-2863 For oxygen index test	-	YES
2.8	ASTMD-2843 For smoke density test	-	YES
2.9	SS:424-14-75 & IEC-332-III-Cat-B & CAT-A, IEC-332-I/ IEEE: 383 For flammability test	-	YES
2.10	IEC-754-1 For Acid gas generation	-	YES
2.11	Current rating of cables conforms to	-	
2.12	Short circuit rating conforms to	-	
2.13	Formula for calculating short circuit current for Different duration	-	
3.0	(a) Installation Conditions at site	deg. C	
	i) Ambient air temperature	deg. C	
	ii) Ground temperature	cm	
	iii) Depth of laying of cables buried in ground	deg. C cm/W	
	(b) Installation conditions for current rating specified at clause 6.3		
4.0	CHARACTERISTICS OF FRLS SHEATH		
	(a) Oxygen index		

NAME OF VENDOR			SEAL	REV.	
NAME	SIGNATURE	DATE			

	DOCUMENT TITLE TECHNICAL SPECIFICATION FOR LT XLPE POWER CABLES	SPECIFICATION NO. PE-TS-424- 507 –E001	
		VOLUME II	
		SECTION I	
		REV NO. 0 DATE 28.11.2017	
		SHEET 2 OF 3	

	(b) Temperature index		
	(c) Acid gas generation		
	(d) Smoke density rating		
5.0	CABLE DRUMS		
	(a) Type & construction		
	(b) Standard drum length		
	(c) Tolerance on drum length		
6.0	INFORMATION TO BE FILLED IN FOR EACH SIZE CABLE IN THE FORM OF TABLE		
6.1	No. of cores x size		
6.2	Voltage grade (Uo/U)	kV	
6.3	Base current ratings (*) based on Cl. 3.0		
	(a) In air	Amp	
	(b) In ground	Amp	
	(c) ducts	Amp	
6.4	Short circuit rating	kA,Sec	
6.5	(a) D.C. resistance of conductor at 20 deg C	ohm/km	
	(b) A.C. resistance of conductor at 90 deg. C	ohm/km	
	(c) Reactance of cable at Normal frequency	ohm/km	
	(d) Electrostatic capacitance of cable at normal frequency	mF/km	
6.6	CONDUCTOR		
	(a) Material type & grade	-	
	(b) No & dia of wires in each core before stranding	no x mm	
	(c) Shape	-	
6.7	XLPE INSULATION		
	(a) Nominal thickness of insulation	mm	
	(b) Method of Curing	-	
6.8	PVC ST2 INNERSHEATH		
	(a) Material	-	
	(b) Thickness (min.)	mm	
	(c) Method of application	-	
	1. Multi-core cables		
	(i) With fillers		
	(ii) With out fillers	Pressure Extruded	
	2. Single core cables		
	d) Type and shape of fillers (if used)		

NAME OF VENDOR			SEAL	REV.	
NAME	SIGNATURE	DATE			

	DOCUMENT TITLE TECHNICAL SPECIFICATION FOR LT XLPE POWER CABLES	SPECIFICATION NO. PE-TS-424- 507 –E001
		VOLUME II
		SECTION I
		REV NO. 0 DATE 28.11.2017
		SHEET 3 OF 3

	e) Colour		
6.9	ARMOUR		
	(a) Material		
	(i) Single core cables		
	(ii) Multi-core cables		
	(b) Size/ dimensions		
	(c) Minimum no. of wires /formed wires		
	(d) Tolerance on formed wire dimension		
	(e) Maximum resistivity of GS formed wire		
	(f) Maximum resistivity of Aluminium round wire		
6.10	PVC ST2 FRLS OUTERSHEATH		
	(a) Nominal thickness of outer sheath	mm	
6.11	DIAMETERS		
	(a) Diameter of insulated conductor	mm	
	(b) Cable diameter under armour	mm	
	(c) Cable diameter over armour	mm	
	(d) Overall diameter of cable	mm	
6.12	Tolerance on overall diameter	(±) mm	
6.13	Minimum bending radius	x O.D	
6.14	Safe Pulling Force	kG	
6.15	Weight of cable	kg./km	
	(a) Weight of conductor	MT/km	
	(b) Weight of XLPE insulation	MT/km	
	(c) Weight of PVC (Inner Sheath, Outer Sheath & Fillers)	kg./km	
	(d) Weight of Armour (As applicable)	kg./km	
6.16	Dimension of drum	mm	
6.17	Shipping weight	kg	
6.18	Cable marking on outer sheath		

(*) For single core cables, the continuous current rating shall be furnished separately for armour earthed at one end and at both ends.

NAME OF VENDOR			SEAL	REV.	
NAME	SIGNATURE	DATE			



DOCUMENT TITLE

TECHNICAL SPECIFICATION FOR
LT XLPE POWER CABLES

SPECIFICATION NO. PE-TS-424-507-E001

VOLUME II

SECTION II

REVISION 0

DATE: 28.11.2017

SECTION – II

GENERAL TECHNICAL SPECIFICATION



DOCUMENT TITLE

TECHNICAL SPECIFICATION FOR
LT XLPE POWER CABLES

SPECIFICATION NO. PE-TS-424-507-E001

VOLUME II

SECTION II

REVISION 0

DATE: 28.11.2017

SHEET 1 OF 1

1.0 TECHNICAL REQUIREMENTS

- 1.1 Technical requirements for LT XLPE POWER CABLES shall be as indicated in this section, in addition to those specified in Section I & Datasheet-A.
- 1.2 It is not the intent to specify herein all the details of design & manufacture. However, the equipment shall conform in all respects to high standards of design engineering and workmanship and shall be capable of performing in continuous commercial operation at site conditions.

2.0 CODES & STANDARDS

- 2.1 The design, material, construction, manufacture, inspection, testing and performance of LT XLPE POWER CABLES shall conform to the latest revision of relevant standards and codes of practices mentioned in Data Sheet - A.
- 2.2 In case of conflict between the applicable reference standard and this specification, this specification shall govern.

3.0 QUALITY ASSURANCE REQUIREMENTS

- 3.1 Bidder shall confirm compliance with the BHEL Standard Quality Plan (PE-QP-999-507-E002 as attached with the specification without any deviations. At contract stage, the successful bidder shall submit the same QP for BHEL/ultimate customer's approval. In case bidder has reference QP agreed with ultimate customer, same can be submitted for specific project after award of contract for BHEL/ultimate customer's approval. There shall be no commercial implication to BHEL on account of minor changes in QP during contract stage.
- 3.2 All materials shall be procured, manufactured, inspected and tested by vendor/ sub-vendor as per approved Quality Plan.
- 3.3 Type testing requirements, routine / acceptance testing and special testing requirements shall be as per Annexure –A to QP. Charges for all these tests for all the equipments & components shall be deemed to be included in the bid price (except UV Radiation & Hydraulic Stability test).
- 3.4 The charges of UV Radiation test & Hydrolytic Stability test (if applicable) shall be reimbursed extra at actual against original money receipt of Govt. Lab. (CPRI/ ERDA etc).
- 3.5 Cost of cables consumed for testing shall be to bidder's account.

4.0 Packing

- 4.1 Cables shall be supplied in non-returnable drums. Material of cable drums shall be as specified in Datasheet-A.
- 4.2 In case of wooden drums, all wooden parts shall be manufactured from seasoned wood treated with copper naphthenates / zinc naphthenates (refer IS: 401). Dimensions of wooden drums shall be as per IS 10418. All ferrous parts shall be treated with suitable rust protective finish or coating to avoid rusting during transit and storage. BIS certification mark shall be stamped on each cable drum. Over the cables polyethylene sheet shall be wrapped and then sealed properly.
- 4.3 In case of Steel drums, New or practically new cable drums made of steel and painted with epoxy resin paint are to be used. Cable ends are carefully protected before packing. Over the cables polyethylene sheet shall be wrapped and then sealed properly. For Typical details of Steel drums, Annexure-B to Section-II, may be referred by the bidder. Bidder may modify, to choose appropriate dimensions of steel drums to suite various sizes/weight/ lengths of LT XLPE POWER CABLES.



Sl. No		Component & Operations	Characteristics	Class	Type of check	Quantum of check		Reference Document	Acceptance Norms	Record Format	Agency				Remarks
						M	C/N				D*	M	C	N	
1		2	3	4	5	6		7	8	9	10				11
Instructions: 1) Cable manufacturer to maintain records to show co- relation of raw materials to finished cables i.e raw material batch/ lot no. should be traceable to the cable drum. 2) Cable manufacturer to maintain all quality control records identified as per all QP stages enumerated below whether it is identified for NTPC verification or witness or not.															
A Raw material/ Brought out Items															
1.01	Aluminum	1. Make	MA	Verify	100%	--		MANUFACTURER APPROVED SOURCES	MANUFACTURE R APPROVED SOURCES	QCR		V	--	--	
		2. Resistivity	MA	Elect	As per Cable Mnfr Std.	--		IS5082	IS5082	--do--		P	--	--	
1.02	PVC / XLPE/comp ound for insulation	1. Make	MA	Verify	--do--	100%		MANUFACTURER APPROVED SOURCES	MANUFACTURE R APPROVED SOURCES	--do--		V	V	--	
		2. Type/ Grade	MA	Verify	100%	100%		NTPC ADS	NTPC ADS	--do--		V	V	V	
		3. All acceptance test as per manufacturer norms including thermal stability test for PVC insulation	MA	Verify	As per manufacturer norms	As per manufactu rer norms		NTPC ADS	NTPC ADS	--do--		V	V	V	Refer note 1
1.03	PVC Compound for Inner sheath	1. Make	MA	Verify	--do--	--do--		MANUFACTURER APPROVED sources	MANUFACTURE R APPROVED sources	--do--		V	V	V	
		2. Type/ Grade	MA	Verify	--do--	--do--		NTPC ADS	NTPC ADS	--do--		V	V	V	
1.04	Steel wire / Formed Wire (As applicable)	1. Make	MA	Verify	--do--	--do--		MANUFACTURER APPROVED sources	MANUFACTURE R APPROVED sources	--do--		V	V	V	
		2. Dimension	MA	Meas	1 sample from each size / lot	--		NTPC APPROVED DATA SHEET & IS 3975	NTPC APPROVED DATA SHEET & IS 3975	--do--		P	--	--	
		3. All acceptance tests as per IS 3975	MA	Verify	As per IS 3975	--		IS 3975	IS 3975	Supplie r TC		V	V	--	
1.05	PVC compound for Sheath	1. Make	MA	Verify	As per manufacturer norms	100%		MANUFACTURER APPROVED sources	MANUFACTURE R APPROVED sources	QCR		V	V	--	
		2. Type / Grade	MA	Verify	100%	100%		NTPC ADS	NTPC ADS	QCR		V	V	V	
		3. All acceptance test as per manufacturer norms	MA	Verify	As per manufacturer norms	As per manufactu rer norms		NTPC ADS	NTPC ADS	QCR		V	V	V	Refer note 1

LEGEND:- *RECORDS, IDENTIFIED WITH "TICK" UNDER COLUMN "D" SHALL BE ESSENTIALLY INCLUDED BY SUPPLIER IN QA DOCUMENTATION.

-M:MANUFACTURER/SUPPLIER, C:MAIN SUPPLIER, N:NTPC, P:PERFORM W:WITNESS,V:VERIFICATION AS APPROPRIATE, CHP: NTPC SHALL IDENTIFY IN COLUMN "N" AS "W"

FORMAT NO:QS-01-QAL-P-10/F3-R1

		Item: 1.1 KV Power (XLPE & PVC) Insulated FRLS cables		STANDARD QUALITY PLAN (CONFORMING TO CODE: IS 1554 PART 1, IS 7098 Part-I AND NTPC TECHNICAL SPECIFICATION)			QP. NO. 0000-999- QOE- S-041 REV-00 DATE : 03-02-12 Page 2 of 11 VALID UP TO: 02-02-15		REVIEWED BY INDERJIT SINGH VIKRAM TALWAR RAJEEV GARG					
Sl. No	Component & Operations	Characteristics	Class	Type of check	Quantum of check		Reference Document	Acceptance Norms	Record Format	Agency				Remarks
					M	C/N				D*	M	C	N	
1	2	3	4	5	6		7	8	9	10				11
		4. Thermal Stability	MA	Chem	One sample / Batch	--	NTPC ADS	NTPC ADS	QCR		P	--	--	
		5. Oxygen Index	MA	Chem	--do--	--	NTPC ADS/ IS 10810 Part 58	NTPC ADS/ IS 10810 Part 58	--do--		P	--	--	
		6. Acid Gas Emission	MA	Chem	One sample / Batch	--	NTPC ADS / IEC60754	NTPC ADS / IEC60754	QCR		P	--	--	
1.06	Wooden Drum	1. Dimension	MI	Meas	Manuf. Std.	--	IS 10418	IS10418	--do--		P	--	--	
		2. Anti termite treatment	MI	Chem	Cable manuf. std	--	CABLE MANUF. STD.	CABLE MANUF. STD.	COC		V	V	V	COC from drum manuf.
1.07	Steel Drum	1. Dimension	MI	Meas	--do--	--	--do--	--do--	QCR		P	--	--	
		2. Surface finish	MI	Meas	--do--	--	--do--	--do--	--do--		P	--	--	
B Process & Stage Inspection														
2.01	Wire Drawing	1. Surface finish	MA	Visual	One sample/Settin g of each size	--	SHOULD BE SMOOTH & FREE FROM SCRATCHES	SHOULD BE SMOOTH & FREE FROM SCRATCHES	QCR		P	--	--	
		2. Wire Diameter	MA	Meas	--do--	--	NTPC ADS	NTPC ADS	--do--		P	--	--	
		3. Tensile test	CR	Mech	--do--	--do--	--do--	--do--	--do--		P	V	V	Refer Sl. No.3.03(iii)
		4. Wrapping test	CR	Mech	--do--	--do--	--do--	--do--	--do--		P	V	V	--do--
2.02	Bunching / stranding	1. No. of wires	MA	Meas	--do--	--	NTPC ADS	NTPC ADS	--do--		P	--	--	
		2. Dia of wire	MA	Meas	--do--	--	--do--	--do--	--do--		P	--	--	
		3. Dimension of Conductor	MA	Meas	--do--	--	--do--	--do--	--do--		P	--	--	
		4. Direction of lay	MA	Visual	--do--	---	--do--	--do--	--do--		P	--	--	
		5. Records of strand breakage / welding during conductor stranding	MA	Verify	--do--	--	IS 8130	IS8130	--do--		P	--	--	
		6. Surface finish	MA	Visual	--do--	-	--do--	--do--	--do--		P	--	--	
		7. DC Resistance	CR	Meas	--do--	-	IS8130/NTPC ADS	IS8130/ NTPC ADS	--do--		P	--	--	
2.03	Insulation extrusion	1. Surface finish	MA	Visual	One sample/Settin g of each size	-	NTPC spec	SHOULD BE SMOOTH. NO POROSITY IS PERMITTED.	QCR		P	--	--	XLPE/ PVC compound shall be preferably loaded in to extruder by suction method.

LEGEND:- *RECORDS, IDENTIFIED WITH "TICK" UNDER COLUMN "D" SHALL BE ESSENTIALLY INCLUDED BY SUPPLIER IN QA DOCUMENTATION.

-M:MANUFACTURER/SUPPLIER, C:MAIN SUPPLIER, N:NTPC, P:PERFORM W:WITNESS,V:VERIFICATION AS APPROPRIATE, CHP: NTPC SHALL IDENTIFY IN COLUMN "N" AS "W"

FORMAT NO:QS-01-QAI-P-10/F3-R1

Sl. No		Component & Operations	Characteristics	Class	Type of check	Quantum of check		Reference Document	Acceptance Norms	Record Format	Agency				Remarks
1		2	3	4	5	M	C/N	7	8	9	D*	M	C	N	11
1		2.Colour of cores	MA	Visual	One sample/Settin g of each size	-		NTPC ADS	NTPC ADS	QCR		P	--	--	
		3.Thickness	CR	Meas	--do--	--		NTPC ADS	NTPC ADS	--do--		P	--	--	
		4.Spark Test	CR	Elect	100%	100%		CABLE MANUF. STD.	No FAILURE	--do --		P	V	V	1.Spark test failure record is to be verified. 2.Core repairing not permitted
		5. Hot Set	CR	Mech	One sample/Settin g of each size	--		IS 7098- Part I	IS 7098- Part I	--do--		P	--	--	Sample is to be taken from both top & bottom end
2.04	Laying up	1. Core sequence	MA	Visual	--do--	--		IS 1554 (Part I) & IS 7098- Part I	IS 1554 (Part I) & IS 7098- Part I	--do--		P	--	--	
		2. Direction of lay	MA	Visual	--do--	--		-do-	--do--	--do--		P	--	--	
		3. Dia over laid up core	MA	Meas	--do--	--		NTPC ADS	NTPC ADS	--do--		P	--	--	
2.05	Inner Sheath	1.Colour	MA	Visual	-do--	-		--do--	--do--	--do--		P	--	--	
		2. Surface Finish	MA	Visual	100%	-		NTPC SPECIFICATION	FISH EYE, BLOW HOLE NOT PERMITTED	--do--		P	--	-	
		3.Thickness	MA	Meas	One sample/Settin g of each size	-		NTPC ADS	NTPC ADS	--do--		P	--	--	
		4.Dia over inner sheath	MI	Meas	--do--	-		--do--	---do--	--do--		P	--	--	
2.06	Armouring (As Applicable)	1.Dimension	MA	Meas	--do--	-		--do--	--do--	--do--		P	--	--	
		2.No. of wires / strip	MA	Meas.	--do--	-		--do--	--do--	--do--		P	--	--	
		3. Direction of lay	MA	Visual	--do--	--		IS 1554 (Part I) & IS 7098- Part I	IS 1554 (Part I) & IS 7098- Part I	QCR		P	--	--	

LEGEND:- *RECORDS, IDENTIFIED WITH "TICK" UNDER COLUMN "D" SHALL BE ESSENTIALLY INCLUDED BY SUPPLIER IN QA DOCUMENTATION.

-M:MANUFACTURER/SUPPLIER, C:MAIN SUPPLIER, N:NTPC, P:PERFORM W:WITNESS,V:VERIFICATION AS APPROPRIATE, CHP: NTPC SHALL IDENTIFY IN COLUMN "N" AS "W"

FORMAT NO:QS-01-QAI-P-10/F3-R1

		Item: 1.1 KV Power (XLPE & PVC) FRLS Insulated cables		STANDARD QUALITY PLAN (CONFORMING TO CODE: IS 1554 PART 1, IS 7098 Part-I AND NTPC TECHNICAL SPECIFICATION)			QP. NO. 0000-999- QOE- S-041 REV-00 DATE : 03-02-12 Page 4 of 11 VALID UP TO: 02-02-15		REVIEWED BY INDERJIT SINGH VIKRAM TALWAR RAJEEV GARG		 APPROVED BY अनुमोदित A.K. Garg Dr. ...			
Sl. No	Component & Operations	Characteristics	Class	Type of check	Quantum of check		Reference Document	Acceptance Norms	Record Format	Agent				Remarks
1	2	3	4	5	M	C/N	7	8	9	D*	M	C	N	11
		4.Coverage & Quality of armouring	MA	Meas.	100%	--	Min. area of coverage of armouring shall be 90%. The gap between amour wires / formed wires shall not exceed one amour wire/ formed wire space & there shall be no cross over/ over riding of amour wire / formed wire. Zn rich paint shall be applied on amour joint surface of G.S. Wire /formed wire. The breaking load of amour wire joint shall not be less than 95% of that amour wire / formed wire. (As per NTPC specification)		QCR		P	--	--	
		5 Dia over armouring	MA	Meas.	One sample/Settin g of each size	--	NTPC ADS		--do--		P	--	--	--
2.07	Outer Sheath	1. Surface finish	MA	Visual	100%	--	Pimple, Fish Eye, Burnt particles, Blow Hole not permitted. Repairing on outer sheath not permitted. (As per NTPC specification)		--do--		P	--	--	PVC FRLS compound shall be preferably loaded in to extruder by suction method
		2.Colour of sheath	MA	Visual	One sample/Settin g of each size	--	NTPC ADS	NTPC ADS	--do--		P	--	--	
		3. Dia over outer sheath	MA	Meas	--do--	--	NTPC ADS	NTPC ADS	--do--		P	--	--	
		4.Thickness of outer sheath	CR	Meas	--do--	-	--do--	--do--	--do--		P	--	--	
		5. Embossing quality	MA	Visual	100%	-	Drum no., IS1554-1 / IS7098-1,Cable size, Voltage grade & Words "FRLS" at every 5 meter is to be embossed. Embossing shall be automatic, in line & marking shall be legible & indelible. (As per NTPC specification)		--do--		P	--	--	Drum no. on cable may be embossed/print ed
		6. Sequential marking	MA	Visual	Full length	--	Sequential marking of length of cable in meter at every one meter is to be embossed / printed. Embossing / printing shall be progressive, automatic, in line & marking shall be legible & indelible. (A s per NTPC specification)		--do--		P	--	--	
C	Finished Cables													
3.01	Type test reports clearance from NTPC Engineering	All type tests as per NTPC specification	CR	Doc.	100%	100%	NTPC SPECIFICATION / NTPC ADS / IS 1554 (PartI) & IS 7098- Part I	NTPC SPECIFICATION / NTPC ADS / IS 1554 (PartI) & IS 7098- Part I	--do--	✓	P	V	V	

LEGEND:- *RECORDS, IDENTIFIED WITH "TICK" UNDER COLUMN "D" SHALL BE ESSENTIALLY INCLUDED BY SUPPLIER IN QA DOCUMENTATION.

-M:MANUFACTURER/SUPPLIER, C:MAIN SUPPLIER, N:NTPC, P:PERFORM W:WITNESS,V:VERIFICATION AS APPROPRIATE, CHP: NTPC SHALL IDENTIFY IN COLUMN "N" AS "W"

FORMAT NO:QS-01-QAI-P-10/F3-R1

Sl. No		Component & Operations	Characteristics	Class	Type of check	Quantum of check		Reference Document	Acceptance Norms	Record Format	Agency				Remarks
						M	C/N				D*	M	C	N	
1		2	3	4	5	6		7	8	9	10				11
3.02	Routine Tests	1.High Voltage test at room temperature	CR	Elect	100%	100%		NTPC ADS / IS 1554 (Part I) & IS 7098- Part I	NTPC ADS / IS 1554 (Part I) & IS 7098- Part I	Test certificate	✓	P	W	W	Refer note 2
		2.Conductor Resistance	CR	Elect	100%	100%		NTPC ADS / IS 1554 (Part I) & IS 7098- Part I	NTPC ADS / IS 1554 (Part I) & IS 7098- Part I	Test certificate	✓	P	W	W	Refer note 2
3.03 Acceptance Tests															
3.03 (i)	Construction of finished Cable	1. OD of Cable	MA	Meas.	Each type & size of cables as per sampling plan of IS 1554 (Part I) & IS 7098- Part I			NTPC ADS	NTPC ADS	--do--	✓	P	W	W	
		2. Laying of core	CR	Visual	--do--			NTPC ADS / IS 1554 (Part I) & IS 7098- Part I	NTPC ADS / IS 1554 (Part I) & IS 7098- Part I	--do--	✓	P	W	W	
		3. Core Identification	CR	Visual	--do--			--do--	--do--	--do--	✓	P	W	W	
		4. Colour of outer sheath	MA	Visual	--do--			NTPC ADS	NTPC ADS	--do--	✓	P	W	W	
		5. Inner sheath thickness	CR	Meas	- do -			--do--	--do--	--do--	✓	P	W	W	
		6. Inner sheath colour	MA	Visual	- do -			- do -	- do -	--do--	✓	P	W	W	
3.03 (ii)	Armour wires/ Formed wires (if applicable)	1.Dimensions	CR	Meas	--do--			NTPC ADS /IS1554(PartI)/IS3975	NTPC ADS /IS1554(PartI) /IS3975	--do--	✓	P	W	W	
		2. No. of wires/ formed wire	CR	Mech	-- do --			--do--	--do--	--do--	✓	P	W	W	
		3. Tensile test	CR	Mech	--do--			--do--	--do--	--do--	✓	P	W	W	
		4. Elongation test	CR	Mech	--do--			--do--	--do--	--do--	✓	P	W	W	
		5.Torsion test (for round wires only)	CR	Mech	--do--			--do--	--do--	--do--	✓	P	W	W	
		6. Wrapping test	CR	Mech	--do--			--do--	--do--	--do--	✓	P	W	W	
		7. Resistance test	CR	Mech	--do--			--do--	--do--	--do--	✓	P	W	W	

LEGEND:- *RECORDS, IDENTIFIED WITH "TICK" UNDER COLUMN "D" SHALL BE ESSENTIALLY INCLUDED BY SUPPLIER IN QA DOCUMENTATION.

-M:MANUFACTURER/SUPPLIER, C:MAIN SUPPLIER, N:NTPC, P:PERFORM W:WITNESS,V:VERIFICATION AS APPROPRIATE, CHP: NTPC SHALL IDENTIFY IN COLUMN "N" AS "W"

FORMAT NO:QS-01-QAL-P-10/F3-R1

Sl. No.		Component & Operations	Characteristics	Class	Type of check	Quantum of check		Reference Document	Acceptance Norms	Record Format	APPROVED BY				Remarks
1		2	3	4	5	M	C/N	7	8	9	10				11
											D*	M	C	N	
			8. Mass of Zinc coating	CR	Meas	Each type & size of cables as per sampling plan of IS 1554 (Part I) & IS 7098-Part I		NTPC ADS /IS1554(PartI)/IS3975	NTPC ADS /IS1554(PartI) /IS3975	Test certificate	✓	P	W	W	
			9. Uniformity of Zinc Coating	CR	Chem.	--do--		--do--	--do--	--do--	✓	P	W	W	
			10. Adhesion test	CR	Mech	--do--		--do--	--do--	--do--	✓	P	W	W	
			11. Freedom from defects	CR	Visual	--do--		--do--	--do--	--do--	✓	P	W	W	
3.03 (iii)	Conductor		1. Resistance Test	CR	Elect	--do--		--do--	--do--	--do--	✓	P	W	W	
			2. Tensile test (For aluminum conductor only)	CR	Mech	Each type & size of cables as per sampling plan of IS 1554 (Part I)/7098(Part-1)		NTPC ADS/ IS 8130	NTPC ADS/ IS 8130	--do--	✓	P	W	W	Test report of manufacturer to be reviewed as per Sl. No. 2.01 for Tensile test & wrapping test (for Aluminum) in case this test is not applicable for cable under inspection as per IS 8130 cl. 6.2
			3. Wrapping test (For aluminum conductor only)	CR	Mech	--do--		--do--	--do--	--do--	✓	P	P	W	--do--

LEGEND:- *RECORDS, IDENTIFIED WITH "TICK" UNDER COLUMN "D" SHALL BE ESSENTIALLY INCLUDED BY SUPPLIER IN QA DOCUMENTATION.

-M:MANUFACTURER/SUPPLIER, C:MAIN SUPPLIER, N:NTPC, P:PERFORM W:WITNESS,V:VERIFICATION AS APPROPRIATE, CHP: NTPC SHALL IDENTIFY IN COLUMN "N" AS "W"

FORMAT NO:QS-01-QAI-P-10/F3-R1

Sl. No		Component & Operations	Characteristics	Class	Type of check	Quantum of check		Reference Document	Acceptance Norms	Record Format	Agency				Remarks
1		2	3	4	5	M	C/N	7	8	9	D*	M	C	N	11
3.03 (IV)	PVC/XLPE/Insulation & PVC Sheath	1. Thickness of insulation & PVC Sheath	CR	Meas	Each type & size of cables as per sampling plan of IS 1554 (Part I)/IS7098(Part-I)			NTPC ADS/ IS 1554(PartI) & IS 7098 Part I	NTPC ADS/ IS 1554(PartI) & IS 7098 Part I	Test Certificate	✓	P	W	W	
		2. Tensile strength & elongation at break of insulation & outer sheath (before ageing)	CR	Mech	Each type & size of cables as per sampling plan of IS 1554 (Part I)/IS7098(Part-I)			NTPC ADS/ IS 1554(PartI) & IS 7098 Part I	NTPC ADS/ IS 1554(PartI) & IS 7098 Part I	Test Certificate	✓	P	W	W	Refer Note 3 Also
		3. Tensile strength & elongation at break of insulation & outer sheath (after Ageing)	CR	Mech	Refer Note 3			--do--	--do--	--do--	✓	P	W	W	Refer Note 3 ath)
		4. Insulation resistance (Volume resistivity method)	CR	Elect	Each type & size of cables as per sampling plan of IS 1554 (Part I) & IS 7098- Part I			--do--	--do--	--do--	✓	P	W	W	
		5. High voltage test at room temperature	CR	Elect	Each type & size of cables as per sampling plan of IS 1554 (Part I) & IS 7098- Part I			--do--	--do--	--do--	✓	P	W	W	
		6. Hot Set test (for XLPE insulation only)	CR	Phy	--do--			--do--	--do--	--do--	✓	P	W	W	
		7. Thermal stability on PVC Insulation and outer sheath	CR	Chem	One sample of each offered lot of all offered sizes			--do--	--do--	--do--	✓	P	W	W	



LEGEND:- *RECORDS, IDENTIFIED WITH "TICK" UNDER COLUMN "D" SHALL BE ESSENTIALLY INCLUDED BY SUPPLIER IN QA DOCUMENTATION.

-M:MANUFACTURER/SUPPLIER, C:MAIN SUPPLIER, N:NTPC, P:PERFORM W:WITNESS,V:VERIFICATION AS APPROPRIATE, CHP: NTPC SHALL IDENTIFY IN COLUMN "N" AS "W"

FORMAT NO:QS-01-QAI-P-10/F3-R1

Sl. No		Component & Operations	Characteristics	Class	Type of check	Quantum of check		Reference Document	Acceptance Norms	Record Format	Agency				Remarks
						M	C/N				D*	M	C	N	
1		2	3	4	5	6		7	8	9	10				11
			8.Oxygen index Test on outer sheath	CR	Chem	One sample of each offered lot of all offered sizes		NTPC ADS / IS10810 Part 58	NTPC A.D.S	--do--	✓	P	W	W	
			9.Smoke density rating test on outer sheath	CR	Chem	One sample of each offered lot of all offered sizes		NTPC ADS & ASTM D2843	NTPC ADS	-do--	✓	P	W	W	
			10.Acid gas generation test on outer sheath	CR	Chem	One sample of each offered lot of all offered sizes		NTPC ADS & IEC 60754-1	NTPC ADS	Test Certificate	✓	P	W	W	
			11.Flammability test on completed cable	CR	Chem	Refer Note 4	Refer Note 4	NTPC ADS & IEC 60332 Part-3 (Category-B)	NTPC ADS	--do--	✓	P	W	W	
			12.Surface finish & length measurement.	CR	Visual & Meas	One length of each size	One length of each size	(1) Drum no. (2) IS1554-1 /IS7098-1, Cable size, Voltage grade & Words "FRLS" at every 5 meter is to be embossed. Embossing shall be automatic, in line & marking shall be legible & indelible. (3) Sequential marking of length of cable in meter at every one meter is to be embossed / printed. Embossing / printing shall be progressive, automatic, in line & marking shall be legible & indelible	--do--	✓	P	W	W	Pimple, Fish Eye, Burnt particles, Blow Hole etc. not permitted. Repairing on outer sheath not permitted.	
			13. Sequence of cores armour coverage, gap between two consecutive armour/formed wire	CR	Visual & Meas	One length of each size	One length of each size	Min. area of coverage of armouring shall be 90%. The gap between armour wires / formed wires shall not exceed one armour wire/ formed wire space & there shall be no cross over/ over riding of armour wire / formed wire. Zn rich paint shall be applied on armour joint surface of G.S. Wire /formed wire	--do--	✓	P	W	W		
4	Packing	1. Sealing	MA	Visual	100%	100%	(1)IS1554(Part-I) & IS 7098-Part I (2) The surface of the drum and the outer most cable layer shall be covered with water proof cover. (3) Both the ends of cables shall be properly sealed with heat shrinkable PVC/ rubber caps secured by "U" nails.			QCR	✓	P	--	--	
4.01	Identification	NTPC Sealing	MA	Visual	100%	100%	Sealing shall be visible			QCR	✓	P	V	V	

LEGEND:- *RECORDS, IDENTIFIED WITH "TICK" UNDER COLUMN "D" SHALL BE ESSENTIALLY INCLUDED BY SUPPLIER IN QA DOCUMENTATION.

-M:MANUFACTURER/SUPPLIER, C:MAIN SUPPLIER, N:NTPC, P:PERFORM W:WITNESS,V:VERIFICATION AS APPROPRIATE, CHP: NTPC SHALL IDENTIFY IN COLUMN "N" AS "W"

FORMAT NO:QS-01-QAI-P-10/F3-R1



		Item: 1.1 KV Power (XLPE & PVC) FRLS Insulated cables		STANDARD QUALITY PLAN (CONFORMING TO CODE: IS 1554 PART 1, IS 7098 Part-I AND NTPC TECHNICAL SPECIFICATION)		QP. NO. 0000-999- QOE- S-041 REV-00 DATE : 03-02-12 Page 9 of 11 VALID UP TO: 02-02-15		REVIEWED BY INDERJIT SINGH VIKRAM TALWAR RAJEEV GARG		APPROVED BY Dt. A.K. Garg				
Sl. No	Component & Operations	Characteristics	Class	Type of check	Quantum of check		Reference Document	Acceptance Norms	Record Format	Agency				Remarks
					M	C/ N				D*	M	C	N	
1	2	3	4	5	6		7	8	9	10				11
Notes:														
1) If the compound manufacturer is carrying out Ageing test , test report of compound manufacturer is to be reviewed. If the compound manufacturer is not carrying out ageing test, then cable manufacturer is to carry out ageing test & test report is to be reviewed (quantum of ageing test sample shall be one sample /batch)														
2) (a) In case of manufacturers / supplier who have supplied cables in the past through Corporate Centre/ Regional Offices :- Routine Test of manufacturer internal test report are to be verified by NTPC at the time of final inspection. 2(b) In case of manufacturers / supplier WHO HAVE NOT SUPPLIED cables in the past through Corporate Centre/ Regional Offices, :- Routine Test are to be witnessed by Main Contractor & NTPC. This is in addition to manufacturer internal test report to be verified by NTPC at the time of final inspection.														
3) Refer table on page 10 & 11 of 11 for Sampling & Acceptance criteria.														
4) For PVC insulated LT power cable :- For cables with OD less than equal to 30 mm, any size of cable may be clubbed together. For cables where OD is more than 30 mm, clubbing to be done for cables having similar ODs. For XLPE insulated LT Power cable: Clubbing to be done for cables having similar ODs.														
LEGEND: NTPC ADS: NTPC approved data sheet, QCR: quality control records of cable manufacturer, CABLE MANUF STD- cable manufacturer's internal plant standard, MI: minor, MA: major, CR: critical, COC- certificate of conformance														

		Item: 1.1 KV Power (XLPE & PVC) Insulated FRLS cables		STANDARD QUALITY PLAN (CONFORMING TO CODE: IS 1554 PART 1, IS 7098 Part-I AND NTPC TECHNICAL SPECIFICATION)		QP. NO. 0000-999- QOE- S-041 REV-00 DATE : 03-02-12 Page 10 of 11 VALID UP TO: 02-02-15		REVIEWED BY Inderjit Singh Vikram Talwar Rajeev Garg					
Sl. No	Component & Operations	Characteristics	Class	Type of check	Quantum of check		Reference Document	Acceptance Norms	Record Format	Agency			Remarks
					M	C/N				D*	M	C	N
1	2	3	4	5	6		7	8	9	10			11

Sampling & Acceptance Criteria

Criteria	Manufacturer experience prerequisite	Condition	Testing procedure	Remarks
Samples as per relevant IS from every size/ type of cable in the offered lot shall be tested for Tensile Strength & Elongation (before ageing). The values will be compared with corresponding values mentioned in the Type Test report accepted by NTPC. These values of Tensile Strength & Elongation (before ageing) should be within +/- 15% tolerance (final values should be more than the minimum values indicated in relevant standard) of the Type Test report	In case of Manufacturers/ Supplier who have supplied cables in the past through Corporate Centre / Regional offices	In case of sizes/ type which meet the criteria	1 Sample of PVC insulation & outer sheath per type of cables offered which have met the criteria, will be put on accelerated ageing test (refer IRS specification no. IRS: S-63/2007 Rev 3.0). The samples shall be aged in air oven at temperature of 130°C +/- 2°C for 5 hours. 1 Sample of XLPE insulation per type of cables offered which have met the criteria, will be put on ageing test as per IS 7098. After wards the samples shall be tested for Tensile Strength & Elongation. Acceptance norms shall be as per relevant IS. This test shall be witnessed by NTPC.	In case the samples do not meet the requirement in accelerated ageing test then 1 sample of that size/ type will be put on ageing test as per IS.
		In case of size /type which do not meet the criteria	Particular size/ type will be put on ageing test as per IS. This test shall be witnessed by NTPC.	

LEGEND:- *RECORDS, IDENTIFIED WITH "TICK" UNDER COLUMN "D" SHALL BE ESSENTIALLY INCLUDED BY SUPPLIER IN QA DOCUMENTATION.

-M:MANUFACTURER/SUPPLIER, C:MAIN SUPPLIER, N:NTPC, P:PERFORM W:WITNESS,V:VERIFICATION AS APPROPRIATE, CHP: NTPC SHALL IDENTIFY IN COLUMN "N" AS "W"

FORMAT NO:QS-01-QA1-P-10/F3-R1



		Item: 1.1 KV Power (XLPE & PVC) Insulated cables		STANDARD QUALITY PLAN (CONFORMING TO CODE: IS 1554 PART 1, IS 7098 Part-I AND NTPC TECHNICAL SPECIFICATION)			QP. NO. 0000-999- QOE- S-041 REV-00 DATE : 03-02-12 Page 11 of 11 VALID UP TO: 02-02-15		REVIEWED BY Inderjit Singh Vikram Talwar Rajeev Gargi		APPROVED BY Approved D.K. Garg.			
Sl. No	Component & Operations	Characteristics	Class	Type of check	Quantum of check		Reference Document	Acceptance Norms	Record Format	Agency				Remarks
					M	C/N				D*	M	C	N	
1	2	3	4	5	6		7	8	9	10				11
				In case of Manufacturers/ Supplier WHO HAVE NOT SUPPLIED cables in the past through Corporate Centre / Regional offices	In case of size /type which meet the criteria		1 Sample per type out of all sizes which have met the criteria, will be put on aging test and witnessed by NTPC as per relevant IS							
					In case of size/ type which do not meet the criteria		Particular size / type will be put on ageing test as per IS. This test shall be witnessed by NTPC							

LEGEND:- *RECORDS, IDENTIFIED WITH "TICK" UNDER COLUMN "D" SHALL BE ESSENTIALLY INCLUDED BY SUPPLIER IN QA DOCUMENTATION.

-M:MANUFACTURER/SUPPLIER, C:MAIN SUPPLIER, N:NTPC, P:PERFORM W:WITNESS,V:VERIFICATION AS APPROPRIATE, CHP: NTPC SHALL IDENTIFY IN COLUMN "N" AS "W"

FORMAT NO:QS-01-QA1-P-10/F3-R1


CLAUSE NO.	TECHNICAL REQUIREMENTS			एनटीपीसी NTPC																																	
	ANNEXURE-A																																				
5.00.00	TESTS 1.0 All equipments to be supplied shall be of type tested design. During detailed engineering, the contractor shall submit for Employer’s approval the reports of all the type tests as listed in this specification and carried out within last ten years from the date of bid opening. These reports should be for the test conducted on the equipment similar to those proposed to be supplied under this contract and the test(s) should have been either conducted at an independent laboratory or should have been witnessed by a client. 2.0 However if the contractor is not able to submit report of the type test(s) conducted within last ten years from the date of bid opening, or in the case of type test report(s) are not found to be meeting the specification requirements, the contractor shall conduct all such tests under this contract at no additional cost to the Employer either at third party lab or in presence of client /Employers representative and submit the reports for approval. 3.0 All acceptance and routine tests as per the specification and relevant standards shall be carried out. Charges for these shall be deemed to be included in the equipment price. 4.0 The type test reports once approved for any projects shall be treated as reference. For subsequent projects of NTPC, an endorsement sheet will be furnished by the manufacturer confirming similarity and “No design Change”. Minor changes if any shall be highlighted on the endorsement sheet.																																				
5.01.00	Type Tests																																				
5.01.01	The reports for the following type tests shall be submitted for one size each of LT XLPE and LT PVC Power cables. Size shall be decided by the employer during detailed engineering: <table><tr><th>S.No.</th><th>Type test</th><th>Remarks</th></tr><tr><td colspan="3">For Conductor</td></tr><tr><td>1.</td><td>Resistance test</td><td></td></tr><tr><td>2.</td><td>Tensile test</td><td>For circular non-compacted conductors only</td></tr><tr><td>3.</td><td>Wrapping test</td><td>For circular non-compacted only</td></tr><tr><td colspan="3">For Armour Wires/ Formed Wires</td></tr><tr><td>4.</td><td>Measurement of Dimensions</td><td></td></tr><tr><td>5.</td><td>Tensile Test</td><td></td></tr><tr><td>6.</td><td>Elongation test</td><td></td></tr><tr><td>7.</td><td>Torsion test</td><td>For round wires only</td></tr><tr><td>8.</td><td>Wrapping test</td><td>For aluminium wires / formed wires only.</td></tr></table>				S.No.	Type test	Remarks	For Conductor			1.	Resistance test		2.	Tensile test	For circular non-compacted conductors only	3.	Wrapping test	For circular non-compacted only	For Armour Wires/ Formed Wires			4.	Measurement of Dimensions		5.	Tensile Test		6.	Elongation test		7.	Torsion test	For round wires only	8.	Wrapping test	For aluminium wires / formed wires only.
S.No.	Type test	Remarks																																			
For Conductor																																					
1.	Resistance test																																				
2.	Tensile test	For circular non-compacted conductors only																																			
3.	Wrapping test	For circular non-compacted only																																			
For Armour Wires/ Formed Wires																																					
4.	Measurement of Dimensions																																				
5.	Tensile Test																																				
6.	Elongation test																																				
7.	Torsion test	For round wires only																																			
8.	Wrapping test	For aluminium wires / formed wires only.																																			
TELANGANA SUPER THERMAL POWER PROJECT PHASE-I (2X800 MW) STEAM GENERATOR ISLAND PACKAGE		TECHNICAL SPECIFICATIONS SECTION VI, PART-B BID DOC. NO.: CS-9591-101-2	SUB-SECTION-B-03 LT POWER CABLES	PAGE 5 OF 6																																	



CLAUSE NO.	TECHNICAL REQUIREMENTS एनटीपीसी NTPC		
	9. Resistance test 10(a) Mass of zinc coating test For GS Formed wires/wires only 10(b) Uniformity of zinc coating For GS Formed wires /wires only 11. Adhesion test For GS Formed wires/wires only For PVC/XLPE insulation & PVC Sheath 12. Test for thickness 13. Tensile strength & elongation tests before ageing and after ageing 14. Ageing in air oven 15. Loss of mass test For PVC insulation and sheath only 16. Hot deformation test For PVC insulation and sheath only 17. Heat shock test For PVC insulation and sheath only 18. Shrinkage test 19. Thermal stability test For PVC insulation and sheath only 20. Hot set test For XLPE insulation only 21. Water absorption test For XLPE insulation only 22. Oxygen index test For outer sheath only 23. Smoke density test For outer sheath only 24. Acid gas generation test For outer sheath only For completed cables 25. Insulation resistance test (Volume resistivity method) 26. High voltage test 27. Flammability test as per IEC-332 Part-3 (Category-B) Indicative list of tests/checks, Routine and Acceptance tests shall be as per Quality Assurance & Inspection table of LT power cables enclosed.		
TELANGANA SUPER THERMAL POWER PROJECT PHASE-I (2X800 MW) STEAM GENERATOR ISLAND PACKAGE	TECHNICAL SPECIFICATIONS SECTION VI, PART-B BID DOC. NO.: CS-9591-101-2	SUB-SECTION-B-03 LT POWER CABLES	PAGE 6 OF 6

STEEL DRUM DRAWING (TYPICAL)

ANNEXURE-B TO SECTION-II

(Sheet 1 of 2)





DIMENSION in mm

ANNEXURE-C

CLAUSE NO.

QUALITY ASSURANCE



LT Power Cables

Attributes / Characteristics Item / Components / Sub System Assembly	Make, Type & T.C as per relevant standard	Dimension/surface finish	Mechanical properties	Chemical Composition	Spark Test(as applicable)	Electrical properties	Hot Set Test/ Eccentricity & Ovality	Lay length & Sequence	Armour coverage, cross over, looseness, gap between two	Sequential marking/ Batch marking/ surface finish/ cable length	T.S & elongation before & after ageing on outer sheath & insulation	Thermal stability	Anti termite coating on wooden	Constructional requirements feature as per NTPC specification	Routine & Acceptance Tests as per relevant standard & NTPC specification	FRLS Tests
Aluminum (IS-8130)	Y	Y	Y	Y		Y										
XLPE Compound (IS-7098)	Y		Y			Y	Y				Y					
PVC insulation Compound (IS: 5831)	Y		Y			Y					Y	Y				
FRLS PVC Compound (IS-5831, ASTM-D2843, IS10810(Part 58), IEC-60754 Part-1)	Y		Y								Y	Y				Y
Extrusion & curing /Manufacturing of Core (PVC / XLPE)		Y			Y	Y						Y				
Core Laying								Y								
Armour wire/strip	Y	Y	Y													
Inner sheath	Y	Y														
Armouring		Y							Y							
Outer Sheathing		Y								Y						
Power Cable (Finished) (IS-5831, ASTM- D2843, IS10810(Part 58), IEC-60754 Part-1, IEC 60332 part III cat B)								Y	Y	Y	Y	Y	Y	Y	Y	Y
Wooden drum(IS-10418) /Steel Drum		Y											Y	Y		

Notes:

1. This is an indicative list of tests / checks. The manufacturer is to furnish a detailed Quality Plan indicating the practice and procedure along with relevant supporting documents.
2. Make of all major Bought out items will be subject to NTPC approval.

TELANGANA SUPER THERMAL POWER PROJECT
PHASE-I (2X800 MW)
STEAM GENERATOR ISLAND PACKAGE

TECHNICAL SPECIFICATION
SECTION-VI, PART-B
BID DOC NO.:CS-9591-101-2

SUB-SECTION-E-17
LT POWER CABLE

PAGE
1 OF 4

ROUTINE TESTS	Following routine tests shall be carried out on each drum of finished cables for all types (PVC / XLPE insulated) & sizes.	
1)	Conductor Resistance test	
2)	High voltage test	
ACCEPTANCE TESTS	Following Acceptance tests shall be carried out on each size of each type (PVC / XLPE insulated) of cables, in the offered lot.	
A) For Conductor (as per sampling plan mentioned in IS: 1554 / 7098)		
	1)	Annealing test (Copper)
	2)	Tensile Test (Aluminum)
	3)	Wrapping Test (Aluminum)
	4)	Resistance test
B) For Armour Wires / Formed Wires (If applicable) (as per sampling plan mentioned in IS: 1554 / 7098)		
	1.	Measurement of Dimensions
	2.	Tensile Tests
	3.	Elongation Test
	4.	Torsion Test For Round wires only
	5.	Wrapping Test
	6.	Resistance Test
	7.	Mass of Zinc coating test For G S wires / Formed wires only
	8.	Uniformity of Zinc coating For G S wires / Formed wires only
	9.	Adhesion test For G S wires / Formed wires only
	10.	Freedom from surface defects
C) For PVC / XLPE insulation & PVC Sheath (as per sampling plan mentioned in IS: 1554 / 7098)		
	1)	Test for thickness
	2)	Tensile strength & Elongation before ageing (for tests after ageing see “D”)
	3)	Hot set test (For XLPE insulation)

D) Ageing test:

	Criteria	Condition	Test Requirements	Remarks
PVC insulation & outer sheath:	Samples as per relevant IS, from each size of cables in the offered lot, shall be tested for tensile strength & elongation (before ageing). Tensile & elongation testing shall preferably be done with a computerized machine. The values will be compared with corresponding values mentioned in the Type Test report accepted by NTPC. These values of Tensile Strength & Elongation (before ageing) should be within +/- 15% of the corresponding values of Type Test report. (Please note that test values should be more than the minimum values indicated in relevant standard).	All sizes which meet the criteria	The size which has maximum negative deviation from type test report values will be put on accelerated ageing test. The samples shall be aged in air oven at temperature of 130°C +/- 2°C for 5 hours and tested for TS & elongation. Acceptance norms shall be as per IS.	In case the size does not meet the requirement in accelerated ageing test then all sizes (which had met the criteria) will be put on ageing test as per IS.
		Sizes which do not meet the criteria	Every size will be put on ageing test as per IS.	----
XLPE insulation	Samples as per relevant IS, from each size of cables in the offered lot, will be put on ageing test as per IS.			

E) Following tests will be carried out on completed cables as per IS on each size of each type (PVC / XLPE insulated)

	1)	Insulation resistance test (Volume resistivity method)
	2)	High voltage test

F) Following tests shall be carried out on only one size of offered lot (comprising of all sizes & types)

	1)	Thermal stability test on PVC insulation and outer sheath
	2)	Oxygen index test on outer sheath

	3)	Smoke density rating test on outer sheath
	4)	Acid gas generation test on outer sheath
G) Flammability test as per IEC 60332 - Part- 3 (Category- B) on completed cables as per following sampling plan:		
		This test will be carried out using composite sampling i.e. irrespective of size; cables of one particular type (i.e. armoured PVC insulated, unarmoured PVC insulated, armoured XLPE insulated, unarmoured XLPE insulated) will be bunched together, as per calculations in line with the IEC. All sizes of PVC & XLPE insulated, armoured & unarmoured cables shall be covered. For one particular type, cables with OD less than or equal to 30 mm shall be clubbed together in touching formation while cables with OD greater than 30 mm shall be clubbed together leaving a gap equal to OD of cable having least diameter. Cable OD shall be taken as nominal overall diameter as per NTPC approved datasheet.
H) Following tests shall be carried on one length of each size of each type (PVC / XLPE insulated) of offered lot:		
	1)	Constructional / dimensional check, surface finish, length measurement, sequence of cores, armour coverage, Gap between two consecutive armour wires / formed wires, Sequential marking, drum / Batch (outer sheath extrusion batch)number marking on sheath
	2)	Measurement of Eccentricity & Ovality