

BHARATH HEAVY ELECTRICALS LIMITED ELECTROPORCELAINS DIVISION BANGALORE-560012

SPECIFICATIONS FOR RAW MATERIALS

ISSUE:03

REF : CLN:SPEC:02

REV : 00

DATE : NOV 2007

PAGE :1 OF 2

SPECIFICATION FOR SILICONE SEALANT/ ADHESIVE

1. APPLICATION

For fixing of ceramic tiles to other base materials like steel, plastic, ceramic, etc.

2. APPLICATION TEMPERATURE

Suitable for continuous operation at > 200 deg C and for intermediate operation (30 minutes) at more than 250 deg C.

3. PROPERTIES

a) Specific Gravity

b) Tack free time

c) Cure time (3 mm thickness) d) Hardness (Shore "A" Point)

e) Tensile strength

f) Sheer adhesive

: 1.03 minimum

: 10 to 15 minutes

: 24 hours

: 25 to 30

: 20 Kg/Cm², Min.

: Minimum 7 Kg/Cm²

4. TESTING METHODS

Material to be tested for above properties to the relevant ASTM/DIN Standards.

5. TEST SAMPLES

Supplier shall take appropriate quantity of sample and get the corresponding tests, as mentioned in C1-3, done in an independent laboratory and produce the test certificate along with every supply.

PREPARED BY

RAVI MULLUR MANAGER/CERALIN ENGG APPROVED BY

NIRMAL JOHN GAINNEOS SR.DGM/CERALIN

BHARATH HEAVY ELECTRICALS LIMITED ELECTROPORCELAINS DIVISION BANGALORE-560012



SPECIFICATION FOR RAW MATERIALS

REF : CLN :SPEC :02

ISSUE:03

REV : 00

DATE : NOV 2007

PAGE : 2 OF 2



6. TEST CERTIFICATE

Material accompanied by test certificates. Test certificate should include following:

- i) Batch No. and date of manufacture.
- ii) Actual test values and reference to the testing standards.

7. MATERIAL ACCEPTANCE

Materials to be accepted based on test certificate issued as evidence of satisfactory compliance to requirements stated above.

8. PACKING

- a) To be packed in 300-310 ml cartridges of suitable material.
- b) Supplier's name, batch No. and expiry date to be printed on cartridges.
- c) 12 to 20 cartridges to be packed in cardboard box. Cardboard boxes to be identified with supplier's name, quantity, date of expiry. These cardboard boxes to be further packed in bigger boxes to contain 6 to 8 cardboard boxes.

9. REJECTION AND REPLACEMENT

Material not conforming to the foregoing shall be rejected. Supplier shall undertake to replace the material free of cost without any delay and arrange to take back the material at his own cost.

PREPARED BY

RAVI MULLUR MANAGER/CERALIN ENGG APPROVED BY

NIRMAL JOHN GAINNEOS SR.DGM/CERALIN