



SPECIFICATIONS FOR RAW MATERIALS

ISSUE	: 05
SECTION	: 47.0
REV	: 01
DATE	: JAN 2013
PAGE	: 1 OF 1

CALCINED ALUMINA FOR HVAC PORCELAIN

1. General : This Specification governs the requirement of Calcined Alumina
2. Application : To serve as one of the constituents in HVAC Alumina porcelain.
3. Freedom from Defects : Shall be free from foreign Materials & supplier should guarantee min. 95% Alpha content.
4. Properties :
 - a) Al_2O_3 99.5 % Minimum
 - b) Na_2O 0.3 % Maximum
 - c) Average Particle Size (D50 Value) : 5.5 μm (Max.)

%Particle Size >10 μm :14 (Max.)

PREPARED BY

M.K.PANDEY
MANAGER / CER.LAB.TECH.&RM

APPROVED BY

S.K.BISWAS
AGM / IO. SER.LAB & TECH