



SPECIFICATIONS FOR RAW MATERIALS

ISSUE : 05
SECTION : 50.0
REV : 00
DATE : JUN 2009.
PAGE : 1 OF 1

CALCINED ALUMINA FOR CERALIN

1. General : This Specification governs the requirement of Calcined Alumina for Ceralin.
2. Application : To serve as one of the constituents in the manufacture of Ceralin
3. Freedom from Defects : Shall be free from foreign materials & supplier should guarantee minimum 90 % Alpha content
4. Properties :
 - % Al_2O_3 : 99.2 % Minimum
 - % Na_2O : 0.35 % Maximum
 - % Particle Size $>10 \mu\text{m}$: 20% Max.
 - Average Particle Size (D₅₀ Value) : 4.0 to 6 μm

PREPARED BY

P.V. Satyasandha
P.V.SATYASANDHA

SR.ENGINEER / CERAMIC LABORATORY

APPROVED BY

S.K. Biswas
S.K.BISWAS

HEAD / SH & CERAMIC LABORATORY