



ISO 9001:2000
& 14001:2004
NAVARATNA
COMPANY

सामग्री प्रबन्धन (क्रय विभाग)
MATERIAL MANAGEMENT(PURCHASE)
सेन्ट्रल फाउन्ड्री फोर्ज प्लांट, भारत हेवी इलेक्ट्रिकल्स लिमिटेड
CENTRAL FOUNDRY FORGE PLANT, BHEL HARDWAR
रानीपुर, हरिद्वार (भारत)
RANIPUR, HARIDWAR (INDIA) – 249403
Phone No. +91-1334-285326/284548, FAX No. 225892
e-mail lpbadoni@bhelhwr.co.in

Ref: FF/PPX/EOI/09
Dt. 01/06/2009

Sub: **EXPRESSION OF INTEREST FOR SUPPLY OF REFRACTORY
CASTABLE CLASS 'A' FOR STEEL MELTING SHOP.**

Dear Sir,

CFFP/BHEL has huge requirement for following item and thus desires Expression of Interest from interested vendors for supply of this item.

EOI NO.	Description	Due date
FF/PPX/EOI/09	Refractory Castable Class 'A' for Steel Melting Shop.	06/07/2009 2.00 P.M.

You are requested to please submit your interest along with Supplier Registration Form (which can be downloaded from our web site www.bhel.com).

Kindly note that supplier registration form is mandatory requirement for processing your application against this Expression of Interest .

Thanking you.

(L.P. Badoni)
Engineer (Pur)

6

3

CONTROLLED COPY

BHEL	PLANT PURCHASE SPECIFICATION	FF05025
	C.F.F.P. - HARDWARE	PAGE : 1 OF 3

REFRACTORY CASTABLE

1. GENERAL

This specification governs the quality requirements of Refractory castable used in Forge and Foundry Furnaces, Vacuum degassing spray limiter and roof etc. of Arc. Furnaces.

2. APPLICATION

Used for repair of Burner blocks, Spray limiter, Arc furnace launders, Delta portion of roof, ladle patching, Reheating Furn. Doors, Bogie repair and Preheater hoods, furnaces.

3. TEST SAMPLES

As per IS : 1528

4. PROPERTIES

When tested in accordance with the relevant clauses of IS-1527 and IS-12528, mentioned against each, the test sample shall show the following values.

4.1. CHEMICAL COMPOSITION

The material when analysed in accordance with IS-1527 shall conform to following composition :-

Elements	Class A	Class K.	Class F
Al 203 (%)min.	90	60	55%
Fe 203 (%)max.	0.8	1.0	4.5%

4.2 GRADING

	0to5mm	0to5mm	0to5mm
4.3 C.C.S min. (at 110°C, Kg/cm sq)	600	350	300
4.4 P.L.C. (%)	1.10	1.5	1.0
	AT 1500°C	1550°C	1350°C
	3 hrs	3 hrs	2 hrs

ISSUED :	SMS TECHNOLOGY	WORKED	<i>R. Prasad</i>
REVISION	01, DATE: 26.02.01	CHECKED	<i>Sun</i>
AGREED	PLANT PUR. SPEC. COMMITTEE	APPROVED	P.E.S.C.

CONTROLLED COPY

(2)

BHEL	PLANT PURCHASE SPECIFICATION	FF 05025
	C.F.E.P. HARDWARE	PAGE : 2 OF 3

	Elements	Class A	Class K,	Class F
4.5	Dry Density (Kg/m ³)min.	2800	2200	2100
4.6	Refractoriness (°C)	1820	1683	1620
4.7	Service Temp. (°C)	1750	1600	1350

5. Whenever specified, tests and inspection are to be conducted in presence of BHEL's representatives. The supplier shall notify BHEL in advance about the readiness of the material for inspection and testing

BHEL reserve the right to test one or all the properties of the material on surveillance basis at BHEL's works and final acceptance of material shall be based on these test results.

6. TEST CERTIFICATES

Unless and otherwise stated, three copies of test certificates shall be supplied along with each consignment giving following information. One copy may be enclosed with despatch documents to facilitate quick clearance of the material.

FF 05025.....

Class

BHEL Order No.

Manufactures Name

Trade Mark, If any

Batch/Lot No.

Quantity Supplied

Tests results of clause 4

REVISION	01	DATE	26.02.01	WORKED	Revised
				CHECKED	Swg